

โครงการวิจัยมีวัตถุประสงค์ที่จะพัฒนาขั้ววัด pH ที่เตรียมจากพอลิไพร์โรล (PPy) นำไฟฟ้า พิล์มพอลิไพร์โรลถูกสังเคราะห์ด้วยเทคนิคพอลิเมอร์ไรเซชันทางเคมีไฟฟ้าของมอนอเมอร์ไพร์โรลแบบขั้นตอนเดียว บนขั้วเหล็กกล้าไร้สนิม โดยมีไฮโดรควิโนน มอนอซัลโฟเนต (HQS) เป็นสารได้ป ผลการตอบสนองของขั้ว PPy-HQS ต่อ pH ของสารละลายมีความสัมพันธ์เชิงเส้น ซึ่งมีความชัน -50.54 ± 1.67 mV/pH ณ อุณหภูมิ 28°C ในช่วง pH 2-12 และใช้เวลาในการตอบสนองน้อยกว่า 1 นาที ขั้ว PPy-HQS สามารถใช้ซ้ำได้หลายครั้งภายในระยะเวลาประมาณ 1 เดือน นอกจากนั้น ขั้ว PPy-HQS ยังมีความสามารถในการวัดซ้ำ และผลิตซ้ำได้ ผลการวิเคราะห์การตอบสนองต่อ H^+ เมื่อมีไอออนอื่นรบกวน แสดงให้เห็นว่าขั้ว PPy-HQS มีความเจาะจงต่อ H^+ สูง การวิเคราะห์ด้วยเทคนิค Cyclic voltammetry, UV-Visible spectroscopy, XPS และ ToF-SIMS สามารถอธิบายกลไกของฟิล์ม PPy-HQS ในการตอบสนองต่อ pH ว่าประกอบด้วยกระบวนการ Protonation-Deprotonation ในสายโซ่พอลิไพร์โรลเอง และกระบวนการรีดอกซ์ของหมู่ HQS ที่ติดกับสายโซ่พอลิไพร์โรล โดยกระบวนการทั้งสองเป็นกระบวนการผันกลับได้

การพัฒนาผลการตอบสนองต่อ pH ของฟิล์มพอลิไพร์โรลทำโดยใช้สารได้ปร่วมชนิด Oxalic acid การเติมสารได้ปร่วมลงในปฏิกิริยาพอลิเมอร์ไรเซชันทำให้เกิดชั้นของ Iron oxalate dihydrate ในช่วงเริ่มต้นปฏิกิริยา ทำให้การยึดติดระหว่างฟิล์มพอลิเมอร์และขั้วเหล็กกล้าไร้สนิมดีขึ้น ส่งผลให้ความชันของกราฟเทียบปรับของฟิล์มพอลิไพร์โรลที่มีสารได้ปร่วมดีขึ้นเป็น -54.67 ± 0.70 mV/pH และยังช่วยให้ฟิล์มดังกล่าวมีอายุการใช้งานนานกว่า 50 วัน โครงการวิจัยนี้แสดงให้เห็นถึงความเป็นไปได้ในการเตรียมอุปกรณ์วัด pH ชนิดฟิล์มพอลิไพร์โรล เนื่องจากมีกระบวนการเตรียมที่ง่ายบนขั้วเหล็กกล้าไร้สนิมซึ่งมีราคาถูก และในอนาคตยังอาจพัฒนาการประกอบฟิล์มพอลิไพร์โรลให้มีลักษณะเป็นขั้วไฟฟ้าสำเร็จ ดังเช่นขั้วไฟฟ้าเยื่อแก้ว เพื่อความสะดวกในการใช้งาน

This research project aims to develop a pH sensor based on conducting polypyrrole (PPy). Polypyrrole film was prepared by a simple one-step electropolymerization of an aqueous solution containing pyrrole and hydroquinone monosulfonate (HQS) as a dopant. Potentiometric pH responses of the PPy-HQS electrodes showed a response slope of -50.54 ± 1.67 mV/pH (28 °C), a linear working range of pH 2 to 12 and a response time less than 1 minute. The electrode stability was maintained over the period of a month. The PPy-HQS electrode exhibited good repeatability and reproducibility. Interference studies with several ions showed minimal effects on the potentiometric response of the PPy-HQS electrode. A combination of cyclic voltammetry, UV-Visible spectroscopy, XPS and ToF-SIMS revealed that the mechanism of pH sensitivity of the PPy-HQS film involved the protonation and deprotonation of polypyrrole itself and the redox reaction of the incorporated HQS. Both processes were reversible.

Potentiometric response of the polypyrrole film was improved by using oxalic acid as a co-dopant. By adding oxalic acid, the adhesion between the polypyrrole film and the supported stainless steel electrode was improved via the formation of iron oxalate dihydrate at the initial stage of polymerization, leading to better potentiometric responses. The co-doped PPy electrodes exhibited the greater slope response of -54.67 ± 0.70 mV/pH (28 °C) and were stable over 50 days after the first use. The research project revealed excellent potential of polypyrrole film as a novel pH sensor with simple preparation on cheap stainless steel electrode. Further development can be made on fabrication of a combined electrode, like a commercial pH glass electrode, for convenient use.