

49403207 : สาขาวิชาเทคโนโลยีอาหาร

คำสำคัญ : เชลลูโลส/ เปลือกข้าวโพดข้าวเหนียว/ โซเดียมไฮดรอกไซด์/ การระเบิดด้วยไอน้ำ/
น้ำมันทอด/ สารดูดซับผสม/ เชลลูโลสอะซิเตท

นิติพร จารัสจำเริญดี : การพัฒนาแผ่นกรองและไส้กรองน้ำมันทอดจากวัสดุทาง
ธรรมชาติและสารดูดซับ. อาจารย์ที่ปรึกษาวิทยานิพนธ์ : ผศ.ดร.บัณฑิต อินดวงศ์,
ผศ.ดร.ปราโมทย์ คูวิจิตรจารุ และ ผศ.ดร.จันทร์ฉาย ทองปิ่น. 100 หน้า.

วัตถุดิบที่ใช้ในการพัฒนาแผ่นกรองจากวัสดุทางธรรมชาติที่เหมาะสมคือเปลือกข้าวโพด
ข้าวเหนียว และเมื่อนำมาทำเป็นเชลลูโลสอะซิเตท พบว่าเปลือกข้าวโพดข้าวเหนียวเกิดเป็นฟิล์ม
ของเชลลูโลสอะซิเตทที่ดีที่สุด และเกิดฟิล์มได้มากที่สุด ส่วนการสกัดเชลลูโลสออกมาจากเปลือก
ข้าวโพดที่ใช้ในการทดลองนี้มี 3 วิธีคือ การใช้สารละลายโซเดียมไฮดรอกไซด์ที่ระดับความเข้มข้น
1 โมลาร์ การระเบิดด้วยไอน้ำที่ความดัน 15 บาร์ อุณหภูมิ 200 องศาเซลเซียส เป็นระยะเวลา 1.5
นาทีก และการแช่ในสารละลายโซเดียมไฮดรอกไซด์ที่ระดับความเข้มข้น 0.25, 0.50 และ 0.75
โมลาร์ ตามลำดับ ก่อนนำไปผ่านการระเบิดด้วยไอน้ำ พบว่า ปริมาณโซลเชลลูโลสและปริมาณ
แอลฟา-เชลลูโลสที่ได้จากการสกัดแต่ละวิธีนั้นไม่แตกต่างกัน แต่ปริมาณผลผลิตที่ได้นั้นมีความ
แตกต่างกันอย่างมีนัยสำคัญ ($p < 0.05$) และเชื้อที่ได้จากการสกัดด้วยสารละลายโซเดียมไฮดรอกไซด์
มีความสว่าง (L^*) ของเชลลูโลสที่ได้เพิ่มมากขึ้น โดยวิธีที่ใช้ในการสกัดเชลลูโลสที่ดีที่สุด คือการ
ระเบิดด้วยไอน้ำ

การทดสอบประสิทธิภาพของกระดาษกรองจากเปลือกข้าวโพดที่ผ่านการระเบิดด้วย
ไอน้ำและผสมสารดูดซับผสมร้อยละ 25 และ 35 ของน้ำหนักเยื่อกระดาษ ในการกรองน้ำมันที่ทอด
นักเก็ตไก่เป็นเวลา 36 ชั่วโมง พบว่า กระดาษกรองจากเปลือกข้าวโพดที่ผสมสารดูดซับร้อยละ 35
สามารถลดปริมาณกรดไขมันอิสระ (FFA) ค่าเปอร์ออกไซด์ (PV) ปริมาณสารประกอบที่มีขี้
(TPM) ได้เท่ากับร้อยละ 22.67, 60.16 และ 29.73 ตามลำดับ และมีความเข้มข้นของน้ำมันทอดจางลง
เมื่อเทียบกับสถานะควบคุม จึงนำอัตราส่วนของการผสมสารดูดซับนี้ไปใช้ในการผสมกับเชลลูโลส
อะซิเตท และพบว่า กระดาษกรองที่ผสมสารดูดซับผสมร้อยละ 35 และเชลลูโลสอะซิเตท สามารถ
ปรับปรุงคุณภาพของน้ำมันทอดได้ดียิ่งขึ้น

49403207 : MAJOR : FOOD TECHNOLOGY

KEY WORD : CELLULOSE/ CORN HUSK/ SODIUM HYDROXIDE/ STEAM EXPLOSION/
FRYING OIL/ ADSORBENT COMBINATION/ CELLULOSE ACETATE

NITIPORN JUMRUSJUMROENDEE : DEVELOPMENT OF FRYING OIL FILTER
PAPER AND TUBE FROM AGRICULTURAL MATERIALS AND ADSORBENT. THESIS

ADVISORS : ASST.PROF.BHUNDIT INNAWONG, Ph.D., ASST.PROF.PRAMOTE
KHUWIJITJARU, Ph.D., AND ASST. PROF.CHANCHAI THONGPIN, Ph.D. 100 pp.

In this experiment, the corn husk was founded to be the most suitable material for filter paper production due to higher yield of cellulose acetate than other agricultural materials. Three different methods for cellulose extraction from corn husk, comprising of alkaline soaking (A), steam explosion at 200°C, 15 bar for 1.5 min (S), and pretreatment by sodium hydroxide at various concentration (0.25, 0.50, and 0.75 M) prior to steam explosion (AS), were studied. An appropriate cellulose extraction technique was steam explosion. The results showed that α -cellulose and holocellulose contents of all pulp residues were not significant difference among the cellulose extraction techniques. All of extraction treatments except pretreatment with 0.25, and 0.50 M NaOH provided significant difference ($p < 0.05$) in yield pulps. The fiber obtained from steam explosion technique was better in physical property. In addition, the lightness (L^*) of AS pulps at 0.25, 0.50, and 0.75 M NaOH were 46.89, 48.27, and 51.26, respectively. Thus, the AS pulps exhibited lighter in color.

The filtration with corn husk + adsorbent papers (CAC papers) sufficiently decreased the oil deterioration rate and finally extended the oil life cycle. In this experiment, the CAC papers were then mixed with 25%, and 35% of adsorbent combinations in paper pulps. Then, the efficiency of CAC papers was further evaluated by frying chicken nuggets and subsequently filtering the used oil with CAC papers. The oil filtration schedule was applied every 3 hour for 6 days. After 36h continuous frying, the filtrated oil with 35% CAC papers could reduce free fatty acid (%FFA), peroxide value (PV), and total polar material (TPM) as following 22.67%, 60.16%, and 29.73%, respectively. In addition, the filtrated oil with 35% CAC papers were lighter, less yellowness, and redness ($p < 0.05$) than the control.

For the next experiment, the used oil filtrated by using the 35% CAC + cellulose acetate papers (called CACA papers) predominantly improved its overall quality as indicating by %FFA, PV, TPM, and color parameters for L^* , a^* , and b^* . In addition, the CACA papers potentially decelerated the oil deterioration and successfully attained better oil quality than the oil filtered by only CAC papers.