

โครงสร้างโมเลกุลของยางอีพอกซีที่เตรียมได้โดยใช้สารไฮโดรเจนเปอร์ออกไซด์กับกรดฟอร์มิค ตรวจสอบได้โดยใช้เทคนิค FTIR และ NMR พบว่าเกิดหมู่อีพอกซีขึ้นในโมเลกุลยาง จากการทดลองพบว่า ยางที่มีน้ำหนักโมเลกุลต่ำเกิดปฏิกิริยาเพิ่มหมู่อีพอกซีมากขึ้น นอกจากนี้ปริมาณสารเคมีที่ใช้และเวลาในการทำปฏิกิริยามีผลต่อการเพิ่มปริมาณของหมู่อีพอกซี จากการศึกษาสมบัติทางกายภาพโดยเปรียบเทียบกับยางธรรมชาติ(LA0) พบว่ายางอีพอกซีมีปริมาณสิ่งระเหย และได้น้อยกว่า แต่มีสิ่งปนเปื้อนและมีค่าความหนืดมูนิสูงกว่ายางธรรมชาติ โดยที่ปริมาณไนโตรเจนและสี(Lovibond scale)ไม่แตกต่างกัน จากการศึกษาสมบัติทางความร้อนพบว่า ค่าอุณหภูมิกลายแก้ว (T_g) ของยางอีพอกซีมีค่าสูงขึ้นเมื่อปริมาณอีพอกซีมากขึ้น ในขณะที่ค่าอุณหภูมิการสลายตัว (T_d) ของยางอีพอกซีไม่แตกต่างกัน ค่าดัชนีความอ่อนตัว P_0 และ PRI ของยางอีพอกซี มีค่าน้อยกว่ายางธรรมชาติ ยกเว้นค่าPRI ของยางอีพอกซี ที่มีปริมาณหมู่อีพอกซี 4% mole(ENR0) มีค่ามากที่สุด ลักษณะการเกิดเดือยของยางอีพอกซีที่มีน้ำหนักโมเลกุลต่ำจะใช้เวลาในการขึ้นรูปมากกว่า LA0 และ ENR0 2เท่า จากการศึกษาสมบัติเชิงกลของยางอีพอกซี พบว่า ยางอีพอกซีซึ่งมีปริมาณอีพอกซี 12 % (ENR4) มีค่า Elongation at break สูงกว่า LA0, ENR0 และยางอีพอกซี ซึ่งมีปริมาณอีพอกซี 14% mole (ENR3) โดยยางอีพอกซีโมเลกุลต่ำ ENR3 และ ENR4 มีค่า Hardness และค่า Tensile strength ลดลง การทนต่อการขีดสีของยางธรรมชาติต่ำกว่ายางอีพอกซี ถึงแม้ว่าจะมีค่า Modulus ไม่แตกต่างกันมากนัก ยกเว้นยางอีพอกซี ENR3 จะมีค่า Modulus สูงสุด

The preparation of epoxidized natural rubbers (ENR) using hydrogen peroxide and formic acid were structural analyzed using FTIR and NMR techniques. The epoxy groups were confirmed to present in the rubber molecules. It was found that the lower molecular weight of natural rubber molecules, the higher epoxy content was obvious. In addition, the reaction reactant concentration and reaction time were found to be influential on epoxy content. From the study of physical properties as compared with natural rubber (LA0), the amount of volatile matter and ash in the obtained ENRs were found to be less than those of LA0 where as the contaminant was also higher and the mooney viscosity was significantly higher than LA0. However the nitrogen content and the Lovibond scale of color were more or less the same as those of LA0. From the study of thermal properties, the glass transition temperature, T_g , of ENR increased when the amount of epoxy content was increased whereas the decomposition temperature, T_d , remained the same. The values of P_0 and PRI of ENRs were found to be lower than those of LA0, except the PRI of epoxidized rubber with 4% mole epoxy content (ENR0) which was found to be highest value. Concerning the cure characteristics of ENRs, it was found that ENRs of lower molecular weight natural rubbers were cured two-time slower than that of LA0 and ENR0. From the mechanical property study, the elongation at break of the epoxidized rubbers with 12% mole epoxy content (ENR4) was higher than those of LA0, ENR0 and ENR3 (14% mole epoxy content) ENR3 and ENR4 with lower molecular weight showed lower hardness and tensile strength. Furthermore, the abrasion resistance of LA0 was found to be superiour to epoxidized natural rubbers LA0 though their modulus were almost the same except the modulus of ENR3 was to be the highest.