

งานวิจัยนี้มีวัตถุประสงค์เพื่อศึกษาการสังเคราะห์วัสดุจีโอพอลิเมอร์จากดินไคอะตอม โดยศึกษาผลของความละเอียดและอุณหภูมิในการเผาดินไคอะตอม, ความเข้มข้นของสารละลายโซเดียมไฮดรอกไซด์และโพแทสเซียมไฮดรอกไซด์, อัตราส่วนโดยโมลของโซเดียมออกไซด์ต่ออะลูมินา, อุณหภูมิและระยะเวลาการบ่มที่มีต่อสมบัติทางกล, โครงสร้างทางจุลภาค, องค์ประกอบทางแร่, ดัชนีการควมแน่นซึ่งระบุโดย Si-O-Si stretching จากเทคนิคการดูดกลืนแสงอินฟราเรด (FTIR) ที่ช่วงความถี่ 1200-950 ซม.⁻¹ และความสามารถในการนำความร้อนของจีโอพอลิเมอร์เพสต์ จากผลการศึกษาพบว่า อุณหภูมิที่เหมาะสมในการเผาดินไคอะตอมคือ 800 องศาเซลเซียส การเพิ่มความละเอียดของดินไคอะตอมและความเข้มข้นของสารอัลคาไลน์จะทำให้กำลังรับแรงอัดของจีโอพอลิเมอร์เพสต์เพิ่มขึ้น จีโอพอลิเมอร์ที่กระตุ้นด้วยสารละลายโซเดียมไฮดรอกไซด์จะให้กำลังรับแรงอัดที่ดีกว่าสารละลายโพแทสเซียมไฮดรอกไซด์ อุณหภูมิและระยะเวลาการบ่มที่เหมาะสม คือ 75 องศาเซลเซียส เป็นระยะเวลา 5 วัน ซึ่งทำให้วัสดุจีโอพอลิเมอร์ที่ได้มีความหนาแน่นรวมเท่ากับ 0.88 กรัมต่อลูกบาศก์เซนติเมตร ให้กำลังรับแรงอัด 15' กิโลกรัมต่อตารางเซนติเมตร และมีค่าการนำความร้อน 0.30 วัตต์ต่อเมตรเคลวิน เมื่ออัตราส่วนโดยโมลของโซเดียมออกไซด์ต่ออะลูมินาเพิ่มขึ้นเป็น 3 โดยที่อัตราส่วนของซิลิกาต่ออะลูมินาเท่ากับ 13 จีโอพอลิเมอร์ให้กำลังรับแรงอัดและความหนาแน่นรวมเพิ่มขึ้นเท่ากับ 60 กิโลกรัมต่อตารางเซนติเมตรและ 1.5 กรัมต่อลูกบาศก์เซนติเมตร ตามลำดับ การวิเคราะห์ด้วยเทคนิคการเลี้ยวเบนรังสีเอกซ์และการดูดกลืนแสงอินฟราเรดสามารถบ่งบอกได้ว่า จีโอพอลิเมอร์จากดินไคอะตอมประกอบด้วยเฟสที่เป็นออสฐานรวมอยู่กับน้ำที่ดูดซับบนพื้นผิวและองค์ประกอบบางส่วนที่เนื่องต่อการทำปฏิกิริยาของดินไคอะตอม

ส่วนที่สองได้ทำการศึกษาผลกระทบเนื่องจากอัตราส่วนของดินไคอะตอมผสมเถ้าแกลบที่มีต่อสมบัติเชิงกล, โครงสร้างทางจุลภาค, องค์ประกอบทางแร่ และความสามารถในการนำความร้อนของจีโอพอลิเมอร์ พบว่าการผสมเถ้าแกลบร้อยละ 40 โดยน้ำหนัก ทำให้อัตราส่วนโดยโมลของซิลิกาต่ออะลูมินาและโซเดียมออกไซด์ต่ออะลูมินาเปลี่ยนแปลงเป็น 22.6 และ 1.7 ซึ่งจีโอพอลิเมอร์ที่ได้ให้กำลังรับแรงอัด 24 กิโลกรัมต่อตารางเซนติเมตร โดยมีความหนาแน่นรวม 1.01 กรัมต่อลูกบาศก์เซนติเมตร และมีค่าการนำความร้อน 0.32 วัตต์ต่อเมตรเคลวิน

The aim of this work was to study the synthesis of geopolymeric materials from diatomaceous earth (DE). The effects of fineness and calcination temperature of DE, concentration of NaOH and KOH, $\text{Na}_2\text{O}/\text{Al}_2\text{O}_3$ molar ratio, curing temperature and time on the mechanical properties, microstructure, mineralogical compositions, degree of condensation defined by Si-O-Si stretching from Fourier Transform Infrared Spectrometry (FTIR) at frequency of $1200\text{--}950\text{ cm}^{-1}$ and thermal conductivity of the synthesized geopolymer paste were studied. The results revealed that the optimum calcination temperature of diatomaceous earth is $800\text{ }^\circ\text{C}$. The increases in fineness of DE and in alkali concentration resulted in an increase in compressive strength of geopolymer paste. Geopolymer with NaOH activation gave higher compressive strength than that with KOH. The optimum curing temperature and time were found to be $75\text{ }^\circ\text{C}$ and 5 days. The obtained geopolymeric material had 0.88 g/cm^3 of bulk density, 15 kg/cm^2 of compressive strength and 0.30 W/m.K of thermal conductivity. When the $\text{Na}_2\text{O}/\text{Al}_2\text{O}_3$ molar ratio increased to 3.0 with $\text{SiO}_2/\text{Al}_2\text{O}_3$ of 13, the compressive strength and bulk density increased to 60 kg/cm^2 and 1.5 g/cm^3 respectively. XRD diffractogram and IR spectrum indicated that the DE geopolymer material is composed of amorphous phase containing surface adsorbed water and some part of inert ingredients originated from the DE.

In the second part, the effect of proportion of DE and rice husk ash (RHA) on the mechanical properties, microstructure, mineralogical compositions and thermal conductivity of the geopolymer paste were examined. The incorporation of 40 wt% RHA that changed $\text{SiO}_2/\text{Al}_2\text{O}_3$ and $\text{Na}_2\text{O}/\text{Al}_2\text{O}_3$ molar ratios to 22 and 1.7 enhanced the compressive strength to 24 kg/cm^2 , bulk density to 1.01 g/cm^3 and thermal conductivity to 0.32 W/m.K .