

ชื่อเรื่องวิทยานิพนธ์

การหาจุดเหมาะสมสำหรับการย่ำหมุดอลูมิเนียมโดยใช้
เทคนิคการออกแบบการทดลอง

ผู้เขียน

นายสมชาย ม้วน โกลสูง

ปริญญา

วิศวกรรมศาสตรมหาบัณฑิต (วิศวกรรมอุตสาหการ)

อาจารย์ที่ปรึกษาวิทยานิพนธ์

ผศ.ดร.สันติชัย ชีวสุทธิศิลป์

บทคัดย่อ

งานวิจัยนี้มีจุดประสงค์เพื่อหาความสัมพันธ์ระหว่างตัวแปรที่มีอิทธิพล และค่าที่เหมาะสมที่สุดของตัวแปร ต่อแรงเฉือนสูงสุดของหมุดย่ำอลูมิเนียม ขึ้นทดสอบถูกเลือกด้วยวิธีการย่ำหมุดแบบต่อแถวเดียวตามขนาดที่กำหนดด้วยหมุดย่ำเกรดมาตรฐานทั่วไป ขนาดความโตของหมุดย่ำเท่ากับ 4.5 มิลลิเมตร ที่สามารถรับแรงเฉือนได้ 1,113.30 นิวตัน นำขึ้นทดสอบไปทดสอบหาคุณสมบัติทางกล ด้วยการทดสอบหาค่าความต้านทานแรงเฉือน ด้วยการดึงขึ้นงานให้หมุดย่ำขาดออกจากกัน โดยวิธีการออกแบบการทดลองเชิงแฟกทอเรียลเต็มจำนวน (2^5) เพื่อคัดกรองตัวแปร ซึ่งมี 5 ตัวแปร มี 2 ระดับได้แก่ 1) แรงกดหมุดย่ำ 5000 และ 8000 นิวตัน 2) ขึ้นงานทดสอบหนา 2.5 มิลลิเมตร และ 4.0 มิลลิเมตร 3) รูเจาะขนาด 4.7 และ 5.2 มิลลิเมตร 4) หมุดย่ำยาวเลยขึ้นงาน 4.5 และ 6.7 มิลลิเมตร 5) เวลาในการกดแช่ 5 และ 15 วินาที ซึ่งเหลือตัวแปรที่มีผลอย่างมีนัยสำคัญ ต่อความต้านทานแรงเฉือนของหมุดย่ำอลูมิเนียมจำนวน 3 ตัวแปร จากนั้นเลือกใช้การทดลอง แบบ บล็อกซ์-เบห์นเคน ซึ่งสามารถทดลองบนค่าใน 3 ระดับ คือ ขึ้นงานหนา 2.5, 3.2 และ 4.0 มิลลิเมตร 2) รูเจาะขนาด 4.7, 4.9 และ 5.2 มิลลิเมตร 3) ความยาวของหมุดย่ำยาวเลยขึ้นงาน 4.5, 5.6 และ 6.7 มิลลิเมตร เพื่อวิเคราะห์หาความต้านทานแรงเฉือนสูงสุด ผลการทดลองพบว่าค่าที่เหมาะสมของตัวแปรคือ ขนาดรูเจาะ 5.2 มิลลิเมตร ความหนาขึ้นงาน 2.8 มิลลิเมตร และความยาวหมุดย่ำ 6.30 มิลลิเมตร และพบว่า แรงเฉือนสูงสุดที่หมุดย่ำรับได้มีค่าเท่ากับ 1,417.55 นิวตัน เพิ่มขึ้นจากเดิม 304.25 นิวตัน หรือประมาณ 27.32 เปอร์เซ็นต์ ทำให้สามารถลดจำนวนการใช้หมุดย่ำ ลดต้นทุน และลดเวลาการผลิตลง

Thesis Title	Optimization of the Aluminum Riveting Process Using an Experimental Design Technique
Author	Mr. Somchai Muankhoksoong
Degree	Master of Engineering (Industrial Engineering)
Thesis Advisor	Asst. Prof. Dr. Santichai Shevasuttisilp

ABSTRACT

The purpose of this research is to determine the optimal factors existing in the aluminum riveting process. First, a 2^5 full-factorial design was used to screen five factors and two levels by selecting a lapping-joint method using only one rivet which exhibited significant riveting shear. The five riveting parameters used were press force 5,000 and 8,000 newtons, a thickness of material of 2.5 and 4mm, a size of hole of 4.7 and 5.2 mm, over long rivets of 4.7 and 5.2 mm and press times of 5 and 15 seconds. There were three parameter levels: thickness of the metal (2.5, 3.2 and 4.0 mm), size of the hole (2.5, 3.2 and 4.0 mm) and size of the over-long rivet (4.5, 5.6 and 6.7mm), then a Box-Behnken design was used in order to analyze the data and find the optimization point.

The experiment found that a standard rivet has a shear strength resistance of 1,113.30 newtons. The study methodology was to prepare the riveting specimens use by selecting a lapping joint per one rivet to test the mechanical quality and shear.

The results of the experiment show that the optimal conditions (to a statistically significant degree) were to use a 5.2 mm hole, a 2.8 mm level of thickness and a 6.3 mm over-long rivet. The optimal point for the shear test was 1,417.55 newtons, and an over-shear strength of 303 newtons could be increased by 27.32 percent.