

ในงานวิจัยนี้ ได้ทำการศึกษาและเปรียบเทียบประสิทธิภาพของสารประกอบออร์กานิก 4 ชนิด ที่ใช้เป็นตัวเริ่มปฏิกิริยาในการเกิดพอลิเมอร์แบบเปิดวงของแอล-แลคไทด์ โดยสารประกอบออร์กานิกที่ใช้ได้แก่ ไอคลอเรท, สแคนน์สออกโตเอต, สแคนน์สออกซานเดต และไตรบิวทิลทิน เมหอกไซด์ ซึ่งได้มีการรายงานว่าสามารถนำมาระดับน้ำมาใช้ในการพอลิเมอร์ไซซ์ชันแบบเปิดวงของพากເອສເຫອຣ์ได้ โดยทำการสังเคราะห์พอลิ(แอล-แลคไทด์) ที่อุณหภูมิ 140°C นาน 72 ชั่วโมง แล้วทำการศึกษาลักษณะเชิงทางของพอลิ(แอล-แลคไทด์) ที่ได้หลังจากทำให้บริสุทธิ์แล้ว ด้วยเทคนิคการวิเคราะห์หล่ายิฐร์รัมกัน (เทคนิคอินฟรา-เรคสเปกโตรกราฟี และโปรดอนนิวเคลียร์แมกเนติกเรโซแนนซ์) และการวิเคราะห์ทางความร้อน (ดิฟเฟอเรนเชียลสแกนนิ่ง แคลอริเมตري แคลกราวิเมตري) และทำการศึกษาน้ำหนักโมเลกุลของพอลิเมอร์ที่ได้ (ด้วยวิธีวัดความหนืดของสารละลายเจือจาง) พบว่า น้ำหนักโมเลกุลของพอลิเมอร์ที่สังเคราะห์ได้มีค่าแตกต่างกัน โดยที่น้ำหนักโมเลกุลเฉลี่ยโดยความหนืดของพอลิ(แอล-แลคไทด์) ที่สังเคราะห์ได้มีเมื่อใช้ไอคลอเรท, สแคนน์ส ออส โถเอต, สแคนน์สออกซานเดต และไตรบิวทิลทิน เมหอกไซด์ เป็นตัวเริ่มปฏิกิริยามีน้ำหนักโมเลกุลมากที่สุด เมื่อพิจารณาอัตราเร็วของการเกิดปฏิกิริยาในการพอลิเมอร์ไซซ์ชันพบว่า เมื่อเวลาผ่านไป ความหนืดของสารจะเพิ่มมากขึ้น โดยที่อัตราเร็วในการเกิดปฏิกิริยาเมื่อใช้สแคนน์สออกโตเอตเป็นตัวเริ่มปฏิกิริยา มีอัตราเร็วสูงที่สุด รองลงมาเป็น ไคลอเรท, สแคนน์สออกซานเดต และไตรบิวทิลทิน เมหอกไซด์ ตามลำดับ และเมื่อเปรียบเทียบค่าคงเหลือรั้นของพอลิ(แอล-แลคไทด์) ที่ได้มีเมื่อทำให้บริสุทธิ์แล้วอยู่ในช่วง 82-98% จากงานวิจัยนี้เมื่อทำการพิจารณาผลการทดลองที่ได้เทียบกับทฤษฎีที่มีอยู่ในปัจจุบัน คาดว่ากลไกในการเกิดปฏิกิริยาในการเกิดพอลิเมอร์ไซซ์ชันแบบเปิดวง จะเป็นแบบโคอร์ดิเนชัน-อินซอร์ทชัน ดังที่ได้แสดงไว้ในงานวิจัยนี้

In this research project, the efficiencies of four organotin compounds as initiators for the ring-opening polymerisation of L-lactide have been studied and compared. The organotin compounds studied were dibutyltin dilaurate (DD), stannous octoate (SnOct_2), stannous oxalate (SnOx) and tributyltin methoxide (TM), all of which have been reported in the literature as being effective in the ring-opening polymerisation of cyclic esters. Poly(L-lactide) (PLL) was synthesized via the ring-opening polymerisation of L-lactide in bulk at 140°C for 72 hours. The PLL samples obtained were first purified and then characterized by a range of analytical techniques combining together spectroscopy (IR and $^1\text{H-NMR}$), thermal analysis (DSC and TGA) and molecular weight determination (dilute-solution viscometry). The main differences were in molecular weight. The viscosity-average molecular weights (\overline{M}_v) of the PLL samples synthesized using DD, SnOct_2 , SnOx and TM as initiator were 86000, 99000, 69000 and 67000 respectively. These results showed that, under the reaction conditions used, SnOct_2 gave the highest molecular weight. Regarding the kinetics of the polymerisation reaction, visual observations of the increase in viscosity with time suggested that the rates of reaction were in the order of $\text{SnOct}_2 > \text{DD} > \text{SnOx} > \text{TM}$. The final yields of the purified PLL products were all in the range of 82-98%. The results are discussed within the light of current theories regarding the exact nature of the coordination-insertion ring-opening mechanism via which these organotin compounds are believed to act.