

ได้ทำการเตรียมผลึกพหุพันธ์ของสารกึ่งตัวนำ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.20$) ได้จากปฏิกิริยาการเกิดเป็นสารละลายของแข็ง จากสารตั้งต้นที่เป็นผงผลึกของสารประกอบ CuO , Al_2O_3 และ $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ ที่มีความบริสุทธิ์ โดยเริ่มต้นจากการบดสารตั้งต้นให้ละเอียดและคลุกเคล้าให้เข้ากันดี จากนั้นจึงนำมาขึ้นรูปโดยการอัดให้เป็นเม็ดด้วยเครื่องไฮโดรลิกความดันสูงที่อุณหภูมิห้อง ผงผลึกที่อัดเป็นเม็ดแล้วจะนำไปเผาในอากาศความดันปกติที่อุณหภูมิ 1,100 องศาเซลเซียส เป็นเวลา 24 ชั่วโมง ส่วนฟิล์มหนาของ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.10$) ได้จากการเคลือบสารตั้งต้นที่เป็นผลึกผงของ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ลงบนกระจกสไลด์ โดยวิธีพิมพ์สกรีน โดยที่ผงผลึกจะละลายในเอทิลีนไกลคอล แล้วจากนั้นจึงพิมพ์สกรีนลงบนกระจกสไลด์ที่อุณหภูมิห้อง การแอนนัลในอากาศที่อุณหภูมิ 500 องศาเซลเซียส เป็นเวลา 30 นาที จะช่วยทำให้เนื้อฟิล์มแน่นขึ้น และนำมาตรวจสอบโครงสร้างผลึกของผลึกพหุพันธ์และฟิล์มหนา $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ที่เตรียมได้โดยวิธีการเลี้ยวเบนของรังสีเอ็กซ์ ส่วนภาพถ่ายของผิวหน้าผลึกของสารตัวอย่างทั้งสองแบบได้จากการบันทึกด้วยกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกราด แล้วทำการวัดสภาพต้านทานไฟฟ้าของผลึกพหุพันธ์ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ และความต้านทานแผ่น $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ของฟิล์มหนานี้ค่าพลังงานกระตุ้นสามารถคำนวณได้จากการวัดความต้านทานไฟฟ้าที่อุณหภูมิต่างๆ จากค่าพลังงานกระตุ้นเหล่านี้สามารถระบุได้ว่าชนิดการนำไฟฟ้าแบบพีของผลึกพหุพันธ์และฟิล์มหนา $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ มีสาเหตุมาจาก แวเลนซ์ของอะตอมโลหะและอะตอมออกซิเจนส่วนเกินที่อยู่ในโครงผลึก รวมทั้งได้มีการศึกษาสมบัติเชิงไฟฟ้า-ความร้อนด้วยโดยการวัดสัมประสิทธิ์ซีเบกที่อุณหภูมิต่างๆ ด้วย

In this research, polycrystalline of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.20$) were prepared by a solid state reaction method. The mixture of high purity of CuO , Al_2O_3 and $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ powder was ground and then pressed by using uniaxial pressure. The obtained pellets were sintered in air at 1100°C for 24 h. Thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.10$) were deposited on slide glass substrates by screen printing method and using $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ phase in powder form as a precursor. The powders were dispersed in ethylene glycol and immediately depositing the screen on the glass substrate. In order to obtain the higher dense material, the as-deposited thick films were annealed in air at 500°C for 30 min. The crystal structures of polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ were checked by X-ray diffraction method. Surface morphology of the samples was observed by scanning electron microscope (SEM). Electrical resistivity and sheet resistance were performed on the polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ respectively. The activation energy values of the samples were estimated by the resistivity measurements as a function of temperature. From the activation energy values, the origin p-type conduction in polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ was attributed to metal deficit and excess oxygen atoms within the crystallite sites of the material. The variation of Seebeck coefficient as a function of temperature was also investigated.