

รหัสโครงการ: DIG180020
ชื่อโครงการ: การออกแบบและปรับปรุงเครื่องตรวจวัดอุณหภูมิโดยดูการเปลี่ยนแปลงของสีจากพอลิไดอะเซทิลีนที่ประกอบด้วยหมู่เอไมด์
ชื่อนักวิจัย: อาจารย์ ดร. สัมฤทธิ์ วัชรสินธุ์ หน่วยวิจัยเคมีอินทรีย์สังเคราะห์ ภาควิชาเคมี คณะวิทยาศาสตร์ จุฬาลงกรณ์มหาวิทยาลัย
Email-Address: sumrit.w@chla.ac.th
ระยะเวลาโครงการ: 3 มีนาคม 2551- 2 มีนาคม 2553

ไดอะเซทิลีนลิปิดถูกเตรียมจากการควบแน่นระหว่าง 10, 12-pentacosadiynoic acid (PCDA) กับ สารประกอบไดเอมีนโดยใช้ 1-ethyl-3-(3'-dimethylamino)carbodiimide hydrochloride salt เป็นรีเอเจนต์ควบแน่น เมื่อใช้สารประกอบไดเอมีนมากเกินไปจะได้รับไดอะเซทิลีนที่มี 1 หมู่เอไมด์ในปริมาณผลผลิตปานกลาง (47-55 % ผลผลิต) เมื่อใช้ PCDA เป็น 2 เท่าภายใต้ภาวะของปฏิกิริยาคลายกันจะได้รับอนุพันธ์ไดอะเซทิลีนที่มี 2 หมู่เอไมด์ในปริมาณผลผลิตที่ดี (52-75% ผลผลิต) ไดอะเซทิลีนลิปิดที่สังเคราะห์ได้สามารถกระจายตัวในน้ำได้โดยกระบวนการอัลตราโซนิกชั้นได้คอลลอยด์โปร่งแสงซึ่งเมื่อได้รับแสงอัลตราไวโอเล็ต ลิปิดเกิดการโฟโตพอลิเมอไรซ์เป็นพอลิไดอะเซทิลีน (PDAs) ที่มีสีน้ำเงิน สมบัติการเปลี่ยนสีตามอุณหภูมิของ PDAs ศึกษาได้ด้วยเครื่อง UV-Vis สเปกโตรมิเตอร์และบันทึกด้วยภาพถ่าย ผลที่ได้แสดงให้เห็นว่าอุณหภูมิการเปลี่ยนสีและการผันกลับได้ของสีขึ้นอยู่กับโครงสร้างของไดอะเซทิลีนลิปิดคือ PDAs ที่เตรียมจากไดอะเซทิลีนที่มีตัวเชื่อมระหว่างหมู่เอไมด์ 2 หมู่ทั้งเป็นวงแหวนอะโรมาติกหรือสายโซ่อะลิฟาติกแสดงสมบัติการผันกลับได้ของสีน้ำเงิน-แดง ในขณะที่ PDAs ที่เตรียมจากไดอะเซทิลีนที่มีหมู่เอไมด์เพียง 1 หมู่แสดงการผันกลับได้เพียงบางส่วนหรือผันกลับไม่ได้เลย นอกจากนี้ไดอะเซทิลีนที่มี 2 หมู่เอไมด์ให้ PDAs ที่มีช่วงการเปลี่ยนสี (70-95 °C) ที่สูงกว่าเมื่อเทียบกับ PDAs ที่ได้จากไดอะเซทิลีนที่มี 1 หมู่เอไมด์ (65-75 °C) การเปลี่ยนสีตามอุณหภูมิของ PDAs ที่มีไซโคเฮกเซนหรือบิส(โพรพิลีนออกไซด์เอทิลีนออกไซด์)เป็นตัวเชื่อมระหว่างเอไมด์ 2 หมู่เป็นแบบผันกลับไม่ได้และมีช่วงการเปลี่ยนสีที่อุณหภูมิต่ำ (25-60 °C) จากผลการทดลองแสดงว่าจำนวนพันธะไฮโดรเจนที่น้อยที่สุด 2 พันธะจากหมู่เอไมด์จำเป็นสำหรับการผันกลับได้ของสีอย่างสมบูรณ์ตามอุณหภูมิ และรายงานการวิจัยได้ให้ข้อมูลเกี่ยวกับการออกแบบโครงสร้างควบคุมการผันกลับได้ของสีและการปรับอุณหภูมิการเปลี่ยนสีของพอลิไดอะเซทิลีน

Project Code: DIG180020
Project Title: Design and Modification of Thermochromic Sensor Based on Polydiacetylenes Containing Amide Groups
Investigator: Sumrit Wacharrasindhu, Organic Synthesis Research Unit, Chemistry Department, Faculty of Science, Chulalongkorn University
Email Address: sumrit.w@chula.ac.th
Project period: 3rd March 2008 – 2nd March 2010

Amidodiacetylene lipids are prepared from the condensation of 10, 12-pentacosadiynoic acid (PCDA) and diamine compounds in the presence of 1-ethyl-3-(3'-dimethylamino)carbodiimide hydrochloride salt as a coupling reagent. The monoamindiacetylenes are obtained in moderate yields (47-55 % yield) when using excess amount of diamines. Using the similar reaction with two equivalents of PCDA, the diamidodiacetylene derivatives are obtained in good yields (52-75% yield). The synthesized amidodiacetylene lipids can be dispersed in water by ultrasonication, giving translucent sol. Upon exposure with UV light, the dispersed lipids undergo photopolymerization to generate the desired blue polydiacetylenes (PDAs). The thermochromic properties of the PDAs are observed by UV-Vis spectrometer and photograph recorder. The observation reveals the structural dependence of the color transition temperatures and their reversibility. The PDAs prepared from diamidodiacetylenes with either aromatic ring or aliphatic chain linkers exhibit complete reversibility of the blue-red color transition while those prepared from the corresponding monoamido derivatives display only partial or no reversibility. The diamidodiacetylenes also gave PDAs with higher color transition temperature (70-95 °C) comparing to the monoamido analogues (65-75 °C). The thermochromism of PDAs having cyclohexyl or bis(propylenoxide ethylenoxide) as linkers between the diamide groups is virtually irreversible and has low color transition temperature (25-60 °C). The results suggest that at least two well-developed hydrogen bonds from amide groups are required for complete thermochromic reversibility. This report provides useful structural design for controlling color reversibility and tuning color transition temperature of PDAs.