

หัวข้อวิทยานิพนธ์	สมบัติและการทวนน้ำมันแก๊สโซชอล์ของวัสดุยางผสมยางเย็นบีอาร์กับยาง เอชเย็นบีอาร์สำหรับประยุกต์ใช้เป็นผลิตภัณฑ์ชีลในงานยนต์
หน่วยกิต	15
ผู้เขียน	นางสาวจันทรพร พรหมนิม
อาจารย์ที่ปรึกษา	ศ. ดร.ณรงค์ฤทธิ์ สมบัติสมกพ
หลักสูตร	วิศวกรรมศาสตรมหาบัณฑิต
สาขาวิชา	เทคโนโลยีวัสดุ
สาขาวิชา	เทคโนโลยีวัสดุ
คณะ	พลังงานสิ่งแวดล้อมและวัสดุ
พ.ศ.	2555

### บทคัดย่อ

งานวิจัยนี้เป็นการศึกษาสัดส่วนของยางผสมระหว่างยางเย็นบีอาร์และยางเอชเย็นบีอาร์ สำหรับผลิตภัณฑ์ยางซีลกันรั่วที่ใช้งานยานยนต์ที่ต้องสัมผัสน้ำมันแก๊สโซชอล์ โดยศึกษาผลสัดส่วนของยางเอชเย็นบีอาร์ที่เติมในยางเย็นบีอาร์ที่ 0, 25, 50, 75 และ 100 ส่วน ที่มีพงเขม่าดำเนินมา 60 ส่วนในร้อยส่วนของยางเป็นสารเติมแต่งหลัก ที่มีต่อสมบัติการไหล สมบัติการบ่มสุก สมบัติเชิงกล สมบัติทางกายภาพ และการทวนต่อน้ำมันแก๊สโซชอล์ที่อุณหภูมิห้องและอุณหภูมิ 100 องศาเซลเซียส และศึกษาผลของสารตัวเติมพريซิพิเตตซิลิกาที่เป็นสารเติมแต่งรอง โดยทำการปรับเปลี่ยนปริมาณพงพريซิพิเตตซิลิกาที่ 0, 10, 20, 30 และ 40 ส่วนในร้อยส่วนของยาง เพื่อการปรับปรุงสมบัติเชิงกล และการทวนต่อน้ำมันแก๊สโซชอล์ของวัสดุยางผสมให้เพิ่มขึ้น และนำวัสดุยางผสมจากสูตรวิจัยขึ้นรูป เป็นชิ้นงาน ໂອริง เปรียบเทียบสมบัติเชิงกล สมบัติทางกายภาพ และการทวนต่อน้ำมันแก๊สโซชอล์กับผลิตภัณฑ์ໂອริงทางการค้า ผลการวิจัยพบว่า การเติมปริมาณยางเอชเย็นบีอาร์ในยางเย็นบีอาร์ไม่ส่งผลต่อระยะเวลาสกอร์ของยางผสม แต่ส่งผลให้เวลาในการบ่มสุกและความหนืดของยางคอมปาร์ต์เพิ่มขึ้น และส่งผลให้สมบัติเชิงกลโดยรวมของยางผสมมีแนวโน้มเพิ่มขึ้น ยกเว้น ค่าการยุบตัวหลังได้รับแรงอัด มอคูลัส และความแข็ง ส่วนการทวนต่อน้ำมันแก๊สโซชอล์ทางการค้าที่มีปริมาณเอทานอลสูงๆ ชนิด E85 ได้ดี โดยเฉพาะยางผสมระหว่างยางเย็นบีอาร์กับยางเอชเย็นบีอาร์ที่สัดส่วน 50:50 โดยผลการทดสอบยางผสมที่อุณหภูมิ 100 องศาเซลเซียส ทำให้สมบัติเชิงกลโดยรวมเปลี่ยนแปลงจากการทดสอบที่อุณหภูมิห้องเพียงเล็กน้อย ส่วนผลการทดสอบการบ่มเร่งสภาพะด้วยความร้อนของยางพบว่า ยางเอชเย็นบีอาร์มีความทนต่อความร้อนที่ดีกว่ายางเย็นบีอาร์ ส่วนผลของการเติมพงพريซิพิเตต

ชีลิกาในวัสดุยางผสม พบว่า การเติมปริมาณพรีซิพิเตตชีลิกาที่ 30 ส่วนในร้อยส่วนของยาง สามารถช่วยปรับปรุงสมบัติเชิงกลทางด้านมอดูลัส ความด้านทานแรงดึง ความด้านแรงนีกขาด ความแข็ง และความทนทานต่อน้ำมันแก๊สโซหอล์ได้เพิ่มขึ้น โดยสูตรยางที่มีสมบัติโดยรวมที่เหมาะสมในงานวิจัยนี้คือ ยางผสมระหว่างยางอีนบีอาร์และยางเอชอีนบีอาร์ที่สัดส่วน 50:50 ที่มีผงเข้มดำเป็นสารตัวเติมหลักที่ปริมาณ 60 ส่วนในร้อยส่วนของยาง และมีสารตัวเติมพรีซิพิเตตชีลิกาเป็นสารตัวเติมรองที่ปริมาณ 30 ส่วนในร้อยส่วนของยาง ส่วนผลการทดสอบเบรยบเทียบกับผลิตภัณฑ์โอริงทางการค้าพบว่า ชิ้นงานยาง โอริงที่ได้จากการวิจัยให้สมบัติเชิงกลด้านมอดูลัส ความแข็ง และความสามารถด้านทานต่อการบวนตัวในน้ำมันแก๊สโซหอล์ได้ดีกว่าผลิตภัณฑ์โอริงทางการค้า

**คำสำคัญ:** น้ำมันแก๊สโซหอล์/พรีซิพิเตตชีลิกา/ยางอีนบีอาร์/ยางเอชอีนบีอาร์/สมบัติเชิงกล

Thesis Title	Properties and Gasohol Oil Resistance of NBR / HNBR Blends for Vehicle Seals Applications
Thesis Credits	15
Candidate	Miss Jantaraporn Promchim
Thesis Advisor	Prof. Dr. Narongrit Sombatsompob
Program	Master of Engineering
Field of Study	Materials Technology
Department	Materials Technology
Faculty	School of Energy, Environment and Materials
B.E.	2555

### **Abstract**

This work studied the effect of blend ratio between acrylonitrile-butadiene rubber (NBR) and hydrogenated acrylonitrile-butadiene rubber (HNBR) for vehicle seal applications in contact with gasohol fuel. The NBR:HNBR blending ratios used were 100:0, 75:25, 50:50, 25:75 and 0:100 (wt%) and all blends were added with 60 parts per hundred of rubber (phr) of carbon black. The monitored properties compound viscosity, cure characteristics, mechanical and physical properties, and gasohol oil resistant properties at room temperature and at 100 °C. In addition, the effect of precipitated silica loadings at 0, 10, 20, 30 and 40 phr in the selected blends was also carried out to improve the mechanical and gasohol oil resistant properties. The rubber blend with the optimum weight fraction of the silica was then prepared in form of the O-ring products and their properties were compared with the commercial O-ring products. The results suggested that the addition of HNBR into NBR did not affect the scorch time of the rubber compounds, but the cure time and the viscosity increased with HNBR content. The addition of HNBR could improve the overall mechanical properties of the blends, except for tensile modulus, hardness and compression set. When testing the rubber blends with commercial gasohol oils with 10, 20 and 85% ethanol, the lowest swelling of NBR/HNBR blends was given for gasohol oil E85, and the recommended blend ratio of NBR/HNBR in this work was 50:50, based on optimum overall mechanical and gasohol oil resistant properties. At 100 °C, the overall mechanical properties changed slightly. HNBR was found to have more thermal aging than NBR. For the effect of precipitated silica loading, it was found that the amount of precipitated silica at 30 phr could improve the mechanical properties and

the gasohol oil resistances. The most appropriate NBR:HNBR blend ratio proposed in this work were the NBR:HNBR blending ratio at 50:50 with the precipitated silica content of 30 phr. When comparing with the properties of commercial O-ring products, it was found that the modulus, hardness and gasohol oil resistant properties of the O-ring products manufactured in this work were comparable with those of the commercial O-ring products.

**Keywords:** Gasohol oil/Precipitated silica/NBR/HNBR/Mechanical properties