

## บทที่ 4

### สรุป

ได้ทำการตัดแปรความเป็นไฮโดรโฟบิกของผ้าฝ้ายด้วยวิธีการต่างๆ พบว่าการตัดแปรผ้าฝ้ายด้วยสารลดแรงตึงผิวทั้งชนิดบวกและชนิดลบ ไม่ได้ช่วยเพิ่มความเป็นไฮโดรโฟบิกให้กับผ้าฝ้ายเนื่องค่ามุมสัมผัสของน้ำระหว่างผ้าที่ผ่านและไม่ผ่านการตัดแปรมีค่าที่ใกล้เคียงกันมาก ส่วนการตัดแปรผ้าฝ้ายโดยการเคลือบด้วยพอลิเมอร์ชนิดบวกก่อนจะนำมาเคลือบด้วยอนุภาคนาโนของซิลิกาและตัดแปรต่อด้วยไอของ POTS สามารถช่วยเพิ่มความเป็นไฮโดรโฟบิกได้มากจนเรียกได้ว่ามีความเป็นซูเปอร์ไฮโดรโฟบิก โดยเมื่อพิจารณาจากค่ามุมสัมผัสของน้ำบนผ้าที่ผ่านการตัดแปรจะมีค่า  $151^{\circ}$  อย่างไรก็ตามเมื่อมีการนำผ้าไปทดสอบการดูดซับน้ำมัน จะพบว่า อนุภาคซิลิกาที่เคลือบอยู่บนหลอดออกมาเป็นจำนวนมากเป็นผลให้ไม่สามารถนำผ้าที่ตัดแปรด้วยวิธีนี้ไปใช้ได้จริง ส่วนการตัดแปรผ้าฝ้ายด้วยวิธีไอเคมีตกสะสมโดยใช้ไอซิลิกอนเตตระคลอไรด์และถูกตัดแปรด้วยไอของฟีนอลและไดเมทิลไดคลอโรไซเลน(ดีเอ็มดีซีเอส) พบว่าสามารถเพิ่มความเป็นไฮโดรโฟบิกให้ผ้าฝ้ายได้ โดยมีมุมสัมผัสของน้ำเท่ากับ  $158^{\circ}$  และ  $138^{\circ}$  สำหรับผ้าที่ตัดแปรด้วย POTS และ DMDCS ตามลำดับ ส่วนการตัดแปรด้วยกรดสเตียริกก็สามารถเพิ่มความเป็นไฮโดรโฟบิกให้กับผ้าฝ้ายได้เช่นกันโดยมีค่ามุมสัมผัสของน้ำประมาณ  $140^{\circ}$  อย่างไรก็ตามถึงแม้ว่าการตัดแปรผ้าฝ้ายด้วย POTS DMDCS และกรดสเตียริก จะสามารถเพิ่มความเป็นไฮโดรโฟบิกให้กับผ้าได้มาก แต่เมื่อทดสอบสมบัติเชิงกลของผ้าก่อนและหลังการตัดแปรถูกทดสอบโดยใช้เครื่องยูนิเวอร์แซลเมคคานิคอลเทสติง ความแข็งแรงของเส้นใยฝ้ายมีแนวโน้มที่ลดลงหลังการตัดแปรด้วยสารลดแรงตึงผิว  $\text{SiCl}_4$  POTS DMDCS และ กรดสเตียริก พบว่าการตัดแปรด้วยสารลดแรงตึงผิว ส่งผลต่อความแข็งแรงของเส้นใยให้น้อยลงไม่มาก หากเป็นการตัดแปรด้วยวิธีไอเคมีตกสะสมทั้ง POTS และ DMDCS และการจุ่มในกรดสเตียริก จะสังเกตได้ว่า ความแข็งแรงของเส้นใยฝ้ายจะมีค่าลดลงค่อนข้างมาก ดังนั้นในการพิจารณาเพื่อนำไปประยุกต์กับงานอื่นๆ อาจจะต้องนำข้อมูลทั้งการเพิ่มขึ้นของความเป็นไฮโดรโฟบิก และความแข็งแรงของวัสดุไปพิจารณาร่วมกันเพื่อนำไปใช้ประโยชน์ต่อไป

## References

- [1] Groudeva VI, Groudev SN, Doycheva AS. Bioremediation of Waters Contaminated with Crude oil and Toxic Heavy Metals. Int J Miner Process 2001;62:293-299.
- [2] Kuyukina MS, Ivshina IB, Makarov SO, Litvinenko LV, Cumming CJ, Philp JC. Effect of Biosurfactants on Crude Oil Desorption and Mobilization in a Soil System. Environ Int 2005;31:155-161.

- [3] Goi A, Kulik N, Trapido M. Combined Chemical and Biological Treatment of Oil Contaminated Soil. *Chemosphere* 2006;63:1754-1763.
- [4] Jou CG, Huang GC. A Pilot Study for Oil Refinery Wastewater Treatment Using a Fixed-Film Bioreactor. *Adv Environ Res* 2003;7:463-469.
- [5] กรมควบคุมมลพิษ กระทรวงทรัพยากรธรรมชาติและสิ่งแวดล้อม. คู่มือการใช้ถังดักไขมัน การติดตั้งการใช้ประโยชน์ และการดูแลรักษา. ISBN 974-9878-09-4.
- [6] Deschamp G, Caruel H, Boredon M E, Bonnin C, Vignoles C. Oil Removal from Water by Sorption on hydrophobic Cotton Fibres. 1. Study of Sorption Properties and Comparison with other Cotton Fibre-Based Sorbents, *Environ Sci Technol* 2003; 37:1013-1015.
- [7] Cambiella A, Ortea E, Rios G, Benito JM, Pazos C, Coca J. Treatment of Oil-in-water Emulsion: Performance of a Sawdust bed filter, *J Hazard Mater* 2006;B131:195-199.
- [8] Shukla A, Zhang YH, Dubey P, Margrave JL, Shukla SS. The Role of Sawdust in the Removal of Unwanted Materials from Water. *J Hazard Mater* 2002;B95:137-152.
- [9] Dalmacija B, Tamas Z, Karlovic E, Miskovic D. Tertiary Treatment of Oil-Field Brine in a Biosorption system with Granulated Activated Carbon. *Water Res* 1996; 30(5): 1065-1068.
- [10] Rattanawong O, Kaewsichan L, Gridanuruk N, Yuasa A. Sorption of Oil Emulsified in Water on Oil Palm Fibres. *Korean J Chem Eng* 2007; 24(1): 67-71.
- [11] Deschamp G, Caruel H, Boredon M E, Bonnin C, Vignoles C. Oil Removal from Water by Sorption on hydrophobic Cotton Fibres. 2. Study of Sorption Properties in Dynamic Mode. *Environ Sci Technol* 2003; 37:5034-5039.
- [12] Ahmad AL, Sumathi S, Hameed BH. A Natural Biopolymer for the Adsorption of Residue Oil from Oily Wastewater. *Adsorpt Sci Technol* 2004; 22(11): 75-88.
- [13] Ahmad AL, Sumathi S, Hameed BH. Residual Oil and Suspended Solid Removal using Natural Adsorbents Chitosan, Bentonite and Activated Carbon: a Comparative study. *Chem Eng J* 2005; 108: 179-185.
- [14] Ahmad AL, Sumathi S, Hameed BH. Adsorption of Residue Oil from Palm Oil Mill Effluent using Powder and Flake Chitosan: Equilibrium and Kinetic Studies. *Water Res* 2005; 39: 2483-2494.
- [15] Aloulou F, Boufi S, Charkchouk M. Adsorption of Octadecyltrimethylammonium Chloride and Adsolubilization onto cellulosic fibers. *Colloid Polym Sci* 2004; 282: 699-707.
- [16] Dankovich TA, Hsieh YL. Surface Modification of Cellulose with Plant Triglycerides for Hydrophobicity. *Cellulose* 2007; 14: 469-480.
- [17] Sreekala MS, Thomas S. Effect of Fibre Surface Modification on Water-sorption

Characteristics of Oil Palm Fibres. *Compos Sci Technol* 2003; 63: 861-869.

[18] Yu M, Gu G, Meng WD, Qing FL. Superhydrophobic Cotton Fabric Coating Based on a Complex Layer of Silica Nanoparticles and Perfluorooctylated quaternary ammonium silane Coupling Agent. *Appl Surf Sci* 2007; 253: 3669-3673.

[19] Annis PA, Marshall WE, Akin DE, Knopp J A, Wartelle LH. The use of Citric Acid Treated Nonwoven Cotton -flax mats for Metal ion Adsorption. *Proceedings - Beltwide Cotton Conferences* 2007, 1846-1852.

[20] Stana-Kleinschek K, Ribitsch V. Electrokinetic Properties of Processed Cellulose Fibers. *Colloid Surface A* 1998;140(1-3):127-138.

[21] Janhom S, Griffiths P, Watanesk R, Watanesk S. Enhancement of lac dye adsorption on cotton fibres by poly(ethyleneimine). *Dyes Pigments* 2004; 63: 231-237.

[22] Goethals EJ. *Polymeric Amines and Ammonium Salts*; Oxford and New York:Pergamon,1980.

[23] Spence MD, Kozaruk JM, Melvin M, Gardocki SM. *US Patent* 1988;4,758,353.

[24] Hansen MR, Young Sr, Richard H. *US Patent* 1996;5,547,541.

[25] Meszaros R, Thompson L, Bos M, Groot P. Adsorption and Electrokinetic Properties of Polyethyleneimine on Silica Surfaces. *Langmuir* 2002;18:6164-6169.

[26] Meszaros R, Thompson L, Varga I, Gilanyi T. Adsorption Properties of Polyethyleneimine on Silica Surfaces in the Presence of Sodium Dodecyl Sulfate. *Langmuir* 2003;19:9977-9980.

[27] Winnik MA, Bystryak SM, Chassenieux C. Study of Interaction of Poly(ethyleneimine) with Sodium Dodecyl Sulfate in Aqueous Solution by Light Scattering, Conductometry, NMR, and Microcalorimetry, *Langmuir* 2000 ;16 :4495-4510.

[28] Li Y, Ghoreishi SM, Warr J, Bloor DM, Holzwarth JF, Wyn-Jones E. Binding of Sodium Dodecyl Sulfate to Some Polyethyleneimines and Their Ethoxylated Derivatives at Different pH Values. *Langmuir* 2000; 16: 3093-3100.

[29] Urum K, Grigson S, Pekdemir T, McMenamy S. A comparison of the efficiency of different surfactants for removal of crude oil from contaminate soils. *Chemosphere* 2006;9:1403-1410.

[30] Ito H, Hayashi H, Sasaki H. Rapid separation of oil particles from low-concentrated O/W emulsions in the presence of anionic surfactants using fibrous slag. *J Colloid Interf Sci* 2002;252:214-221.