

งานวิจัยนี้ศึกษาอิทธิพลของปริมาณและชนิดสารช่วยประสาน สารเติมแต่งเสริมแรงซิลิกา (ซิลิกา เกรดการค้าและซิลิกาในถ่านหิน) ที่มีต่อสมบัติการไหล สมบัติเชิงกล สมบัติทางความร้อน และ โครงสร้างจุลภาคของยางพาราห่วงยางธรรมชาติกับยางเอ็นบีอาร์ที่สัดส่วน 20:80 โดยใช้สารช่วยประสานยางคลอโรพրีน และยางธรรมชาติอิพอกซิไดซ์ปรับเปลี่ยนปริมาณที่ 0 ถึง 7 ส่วนต่อยางหนึ่ง ร้อยส่วน พบว่า การเติมสารช่วยประสานยางคลอโรพรีน และยางธรรมชาติอิพอกซิไดซ์ทำให้ค่าความหนืดของยางพาราเพิ่มขึ้น อย่างไรก็ตาม การเติมสารช่วยประสานไม่ส่งผลต่อเวลาการไหลก่อนอบสูญ และเวลาคงรูป แต่เพิ่มสมบัติเชิงกลโดยรวม โดยสารช่วยประสาน 5 ส่วนต่อยางหนึ่งร้อยส่วน เป็นปริมาณที่เหมาะสม การเติมปริมาณซิลิกาเพิ่มขึ้นทำให้มีค่าความหนืดของยางพาราสูงขึ้น ซึ่งซิลิกา เกรดการค้าส่งผลให้ยางพารามีค่าความหนืดมากกว่าซิลิกาในถ่านหิน ปริมาณซิลิกาที่เพิ่มขึ้นทำให้มีเวลาไหลก่อนอบสูญ และเวลาคงรูปลดลง ในกรณีของเวลาคงรูปการเติมซิลิกาในถ่านหินมีเวลาคงรูปเร็วกว่าซิลิกาเกรดการค้า และสารช่วยประสานยางคลอโรพรีน ยางธรรมชาติอิพอกซิไดซ์ไม่ส่งผลต่อเวลาการไหลก่อนอบสูญ และเวลาในการคงรูป ผลการศึกษาสมบัติเชิงกล พบว่า การเติมซิลิกาเกรดการค้ามีสมบัติเชิงกลโดยรวมดีกว่าซิลิกาในถ่านหิน ภายหลังบ่มเร่งด้วยความร้อน ส่งผลให้สมบัติเชิงกลมีค่าเพิ่มขึ้น ในขณะที่ภายหลังบ่มเร่งในน้ำมัน ส่งผลให้สมบัติเชิงกลโดยรวมมีค่าลดลง ผลจากการศึกษาโดยสรุป พบว่า การเติมสารช่วยประสานยางคลอโรพรีน และยางธรรมชาติอิพอกซิไดซ์ ร่วมกับสารเสริมแรงซิลิกา สามารถเพิ่มสมบัติเชิงกลในยางพารา โดยสารช่วยประสานยางธรรมชาติอิพอกซิไดซ์ มีประสิทธิภาพมากกว่าสารช่วยประสานยางคลอโรพรีน

## Abstract

208159

This work studied the effect of content and type of compatibilizer, and silica (Commercial silica and silica in fly ash) on the rheological, mechanical, thermal and morphological properties of rubber blend of Natural Rubber (NR) and Acrylonitrile-Butadiene Rubber (NBR) (using 20:80 ratio of NR/NBR). The compatilizers used in this work were Chloroprene Rubber (CR) and Epoxidized Natural Rubber (ENR), the dosages varying from 0 to 7 phr. The experimental results suggested that adding both compatilizers resulted in an increase in complex viscosity of the blend. The use of compatilizers did not affect scorch time and cure time of the blend. The incorporations of these two compactabilizers were found to improve the mechanical properties of the blend, the recommended dosage of the compatilizers being 5 phr. Adding silica contents increased the complex viscosity of the blend, the effect being more pronounced for the commercial silica. Increasing silica content resulted in a decrease in scorch time and cure time. Cure time of the blend with silica in fly ash was faster than that with the commercial silica. Chloroprene rubber and epoxidized natural rubber did not affect scorch time and cure time of the blend. It was found that the mechanical properties of the commercial silica blends were better than those of the silica in fly ash of the blend. After thermal aging, the mechanical properties increased, but immersion in oil decreased the overall mechanical properties. It can be concluded that both compatibilizers with silica improved the mechanical properties in the blend, the ENR compatibilizer being the more effective compatibilizer than the CR compatibilizer.