52402241 : สาขาวิชาวิทยาการและวิศวกรรมพอลิเมอร์

คำสำคัญ : หวายสังเคราะห์/พอลิเอทธิลีนความหนาแน่นสูง/พอลิแลคติกแอซิด/สารประสานคู่ ควบ/สารช่วยฟู

อรุณ ภูกริ่งศรี : การเตรียมและผลของสารเติมแต่งที่มีต่อสมบัติของเส้นหวายเทียม. อาจารย์ที่ปรึกษาวิทยานิพนธ์ : ผศ.ดร.ณัฐกาญจน์ หงส์ศรีพันธ์. 184 หน้า.

งานวิจัยนี้แบ่งการศึกษาออกเป็น 2 ส่วน ในส่วนแรกทำการศึกษาหาสภาวะที่ เหมาะสมและวิเคราะห์อิทธิพลของสารประสานคู่ควบของเส้นหวายเทียมที่ทำจากพอลิเมอร์ผสม ระหว่างHDPEกับยาง EPDM โดยทำการปรับสภาพผิวผงไม้สนด้วย Vinyltriethoxy silane ที่ความ เข้มข้น 2.5 และ 3 %โดยน้ำหนักเทียบกับน้ำหนักของผงไม้ จากนั้นนำผงไม้ที่ผ่านการปรับสภาพ แล้วปริมาณ 1 , 2 และ 3 phr ผสมกับพอลิเมอร์ผสมระหว่างHDPEกับยาง EPDM เพื่อหาสูตรการ ผสมที่เหมาะสม จากผลการศึกษาพบว่าผงไม้สนที่ผ่านการปรับปรุงผิวด้วย Vinyltriethoxy silane ที่ความเข้มข้น 2.5 %โดยน้ำหนักเทียบกับน้ำหนักของผงไม้ปริมาณ 2 phr ให้ผลการทดสอบสมบัติ เชิงกลที่ดีและทำให้เส้นหวายเทียมมีสีใกล้เคียงกับเส้นหวายธรรมชาติ จากนั้นจึงนำอัตราส่วนที่ได้ ไปผสมกับสารช่วยฟูที่ปริมาณ 0.5-2.0 phr จากผลการศึกษาพบว่าการเติมสารช่วยฟูสามารถลด น้ำหนักของเส้นหวายเทียมลงได้ 16 % เมื่อเปรียบเทียบกับเส้นหวายเทียมที่ไม่มีการเติมสารช่วยฟ

ในส่วนที่สองทำการศึกษาหาสภาวะที่เหมาะสมและวิเคราะห์อิทธิพลของสาร ประสานคู่ควบของเส้นหวายเทียมที่ทำจากพอลิเมอร์ผสมระหว่างPLAกับPBAT โดยทำการปรับ สภาพผิวผงไม้สนด้วย 3-Aminopropyltriethoxy silane ที่ความเข้มข้น 4 และ 6 เปอร์เซ็นต์โดย น้ำหนักเทียบกับน้ำหนักของผงไม้ จากนั้นนำผงไม้ที่ผ่านการปรับสภาพแล้วปริมาณ 3 , 5 และ 7 phr ผสมรวมกับเม็ด PLAและPBAT เพื่อหาสูตรการผสมที่เหมาะสม จากผลการศึกษาพบว่าผงไม้ สนที่ผ่านการปรับปรุงผิวด้วย 3-Aminopropyltriethoxy silane ที่ความเข้มข้น 6 % โดยน้ำหนักเทียบ กับน้ำหนักของผงไม้ปริมาณ 5 phr ให้ผลการทดสอบสมบัติเชิงกลที่ดีและทำให้เส้นหวายเทียมมีสี ใกล้เกียงกับเส้นหวายธรรมชาติ จากนั้นจึงนำอัตราส่วนที่ได้ไปผสมกับสารช่วยฟูที่ปริมาณ 0.5-2.0 phr จากผลการศึกษาพบว่าการเดิมสารช่วยฟูสามารถลดน้ำหนักของเส้นหวายเทียมลงได้ 40 % เมื่อ เปรียบเทียบกับเส้นหวายเทียมที่ไม่มีการเดิมสารช่วยฟู

ภาควิชาวิทยาการและวิศวกรรมวัสดุ บัณฑิตวิทยาลัย มหาวิทยาลัยศิลปากร ปีการศึกษา 2554 ลายมือชื่อนักศึกษา.....

ลายมือชื่ออาจารย์ที่ปรึกษาวิทยานิพนธ์

52402241 : MAJOR : POLYMER SCIENCE AND ENGINEERING

KEY WORDS : SYNTHETIC RATTAN/HIGH-DENSITY POLYETHYLENE/POLY LACTIC ACID/COUPLING AGENT/FOAMING AGENT

ARUN PHUKRINGSRI : PREPARATION AND EFFECT OF ADDITIVES ON PROPERTIES OF SYNTHETIC RATTAN. THESIS ADVISOR : ASST.PROF.DR. NATTAKARN HONGSRIPHAN. 184 pp.

This research was divided into 2 sections. The first section was aimed to determine the optimized conditions and effect of coupling agent on synthetic rattan made from polymer blend of HDPE and EPDM rubber. Composites were prepared by mixing wood flour of 1, 2 and 3phr treated with vinyltriethoxysilane (VTES) of 2.5 and 3 wt% (based on wood flour) with optimized HDPE/EPDM blend to determine the optimum formula. It is found that the optimized wood content was 2 phr with silane treatment of 2.5 wt% (respect to the fiber weight) giving desired mechanical properties and showing color closed to natural rattan. After mixing the optimized formula with Azodicarbonamide of 0.5-2.0 phr, the results show that adding Azodicarbonamide could reduce composite weight up to 16 % compared to non-added ones.

The second section was aimed to determine the optimized conditions and effect of coupling agent on synthetic rattan made from polymer blend of PLA and PBAT. Composites were prepared by mixing wood flour of 3, 5 and 7phr treated with 3-Aminopropyltriethoxy silane of 4 and 6 wt% (based on wood flour) with PLA/PBAT blends to determine the optimum formula. It is found that the optimized wood content was 5 phr with silane treatment of 6 wt% (respect to the fiber weight) giving desired mechanical properties and showing color closed to natural rattan. After mixing the optimized formula with Azodicarbonamide of 0.5-2.0 phr, the results show that adding Azodicarbonamide could reduce composite weight up to 40 % compared to non-added ones.

Department of Materials Science and Engineering Graduate School, Silpakorn University Academic Year 2011 Student's signature

Thesis Advisor's si	gnature	