

งานวิจัยนี้เป็นการศึกษาหาธาตุมลทินที่แทรกอยู่ภายในเพชรและศึกษาผลการอาบรังสีนิวตรอนต่อสมบัติของเพชรด้วยเครื่อง ESR สเปกโตรมิเตอร์ ตัวอย่างเพชรที่ใช้ในงานวิจัยเป็นเพชรธรรมชาติสีเขียวแกมเหลือง สเปกตรัม ESR ที่ได้จากตัวอย่างเพชรพบว่ามีธาตุไนโตรเจน จำนวน 3 อะตอม อยู่ในตำแหน่งใกล้เคียงกัน เป็นธาตุมลทิน เนื่องจากที่มุม  $\varphi = 0, 90$  และ  $180$  องศา สเปกตรัม ESR จะมี 3 พีคใหญ่ และที่มุม  $\varphi = 15, 30, 45, \dots, 75, 105, 120, \dots, 165$  องศา จะมี 7 พีค ซึ่งเกิดจากการคัปปลิงระหว่างอิเล็กตรอนสปิน( $S=1/2$ ) และ นิวเคลียสสปิน( $I=1$ )ของอะตอมไนโตรเจน เรียกว่าเป็นการแตกตัวแบบไฮเปอร์ไฟน์ โดยไนโตรเจนทั้ง 3 อะตอม จะอยู่ในแนวทแยงมุมของยูนิเซลล์ สเปกตรัม ESR ที่ได้หลังการอาบรังสีนิวตรอนจะคล้ายคลึงกับสเปกตรัมก่อนการอาบรังสี แต่พีคตรงกลางจะมีค่าเพิ่มสูงขึ้น เนื่องจากการแตกออกของพันธะคาร์บอนกับคาร์บอน ทำให้เกิดช่องว่างภายในโครงผลึก มีผลให้ชั้น donor level ในช่องว่างพลังงานเปลี่ยนแปลง ทำให้สีของตัวอย่างเพชรที่สังเกตก่อนอาบรังสีจากสีเหลืองอ่อนเปลี่ยนไปเป็นสีเขียวเข้มและ เปลี่ยนกลับมาเป็นสีเหลืองอีกครั้ง เมื่อเก็บตัวอย่างเพชรหลังอาบรังสีไว้นาน 1 ปี

In this research, the impurities in a natural diamond and the effects of neutron irradiation on diamond physical properties were studied by electron spin resonance (ESR) spectrometer. The ESR spectra of a natural yellowish diamond sample before neutron irradiation indicated that three atoms of nitrogen were in a neighbor position. From the results, ESR spectra demonstrated three peaks and seven peaks at  $\Phi = 0, 90, 180$  degree and  $\Phi = 15, 30, 45, \dots, 75, 105, 120, \dots, 165$  degree, respectively. These peaks, generated from a coupling between the electron spin ( $S = 1/2$ ) and the nuclear spin ( $I = 1$ ) of the nitrogen atom, exhibited the hyperfine splitting phenomenon. Consequently, three atoms of nitrogen were confirmed to be diagonally positioned in a unit cell. Although the peaks of ESR spectra before and after neutron irradiation were comparable, the middle peak of ESR spectra after neutron irradiation was higher than that before neutron irradiation, due to the broken C-C bonds. This characteristic is called the dangling bonds, generally correlated to the vacancies in the diamond structure. The donor level in energy gap was then shifted. Hence, the color of the diamond, after neutron irradiation, was altered from yellow to dark-green, and returned to approximately original appearance within a year.