

ภาคผนวก

ภาคผนวก 1

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มควบคุม / Transbond™ XT

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	174.64	16.46	1
2	172.08	16.22	1
3	205.78	19.40	0
4	264.06	24.89	1
5	183.08	17.26	1
6	193.13	18.20	1
7	166.63	15.71	1
8	150.06	14.14	1
9	164.82	15.53	1
10	221.28	20.86	1
11	174.02	16.40	1
12	161.23	15.20	3

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มได้ก / Transbond™ XT

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	213.41	20.16	1
2	168.56	15.89	1
3	190.45	17.95	1
4	183.06	17.25	1
5	186.38	17.57	1
6	141.66	13.35	3
7	211.86	19.97	1
8	190.62	17.97	3
9	168.29	15.86	1
10	190.55	17.96	1
11	102.96	9.70	1
12	117.81	11.10	3

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มชาเขียวโออิชิ / Transbond™ XT

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	192.3	18.13	1
2	187.18	17.64	2
3	134.95	12.72	1
4	172.81	16.29	2
5	195.08	18.39	1
6	140.15	13.21	2
7	165.71	15.62	1
8	195.42	18.42	1
9	167.40	15.78	3
10	170.23	16.04	1
11	158.81	14.97	1
12	197.85	18.65	0

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มควบคุม / Transbond™ Plus SEP

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	92.13	8.68	0
2	238.16	22.45	1
3	110.61	10.42	0
4	82.47	7.77	1
5	124.44	11.73	1
6	75.40	7.11	1
7	144.07	13.58	0
8	115.30	10.87	1
9	173.04	16.31	1
10	179.39	16.91	1
11	102.68	9.68	0
12	82.79	7.80	0

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มโค้ก / Transbond™ Plus SEP

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	64.08	6.04	0
2	65.08	6.13	1
3	110.74	10.44	0
4	60.32	5.69	0
5	21.78	2.05	0
6	23.78	2.24	0
7	76.48	7.21	0
8	127.78	12.04	0
9	25.68	2.42	0
10	61.67	5.81	0
11	30.27	2.85	0
12	128.96	12.15	1

ข้อมูลดิบเกี่ยวกับกำลังแรงยึดเหนี่ยว (shear bond strength: SBS) และ ARI Scores

กลุ่มชาเขียวโออิชิ / Transbond™ Plus SEP

No.	SBS (Newtons)	SBS (MPa)	ARI Scores
1	36.27	3.42	1
2	111.99	10.56	0
3	73.25	6.90	0
4	137.13	12.92	0
5	79.75	7.52	0
6	118.80	11.20	0
7	114.83	10.82	0
8	64.34	6.06	1
9	155.10	14.62	1
10	104.98	9.89	1
11	148.19	13.97	1
12	19.65	1.85	0

ภาคผนวก 2

Test of Normality and Test of Homogeneity of Variances

Tests of Normality

Groups		Kolmogorov-Smirnov ^a			Shapiro-Wilk		
		Statistic	df	Sig.	Statistic	df	Sig.
Shear Bond Strength (MPa)	Control/ XT	.223	12	.103	.861	12	.050
	Coke/ XT	.206	12	.170	.892	12	.125
	Greentea/ XT	.161	12	.200*	.910	12	.211
	Control/ SEP	.185	12	.200*	.888	12	.111
	Coke/ SEP	.180	12	.200*	.884	12	.098
	Greentea/ SEP	.157	12	.200*	.954	12	.699

a. Lilliefors Significance Correction

*. This is a lower bound of the true significance.

Test of Homogeneity of Variances

Shear Bond Strength (MPa)

Levene Statistic	df1	df2	Sig.
1.526	5	66	.194