

## References

- [1] Department of alternative energy development and efficiency ministry of energy. Gasohol[online]. 2009. Available from:  
<http://www.dede.go.th/dede/index.php?id=517> [2010, February 5]
- [2] Agarwal, A.K. 2007. Biofuels (alcohols and biodiesel) applications as fuels for internal combustion engines. Progress in Energy and Combustion Science 33: 233-271.
- [3] Biofuel[online]. 2009. Available from:  
<http://en.wikipedia.org/wiki/Biofuel> [2010, February 5]
- [4] Gonsalves, J.B. 2006. An Assessment of the Biofuels Industry in Thailand United Nations Conference on Trade and Development
- [5] Jia, L.-W., et al. 2005. Influence of ethanol-gasoline blended fuel on emission characteristics from a four-stroke motorcycle engine. Journal of Hazardous Materials 123: 29-34.
- [6] Knapp, G.G., and Rouge, B.L. 1985. Corrosion inhibitor for alcohol and gasohol fuels. United States Patent: 4509951
- [7] Aksonwong, W. 2009. Impact of gasohols on glass fiber reinforced HDPE composite. Master Thesis. Chemical Engineering, Chulalongkorn University, Bangkok, Thailand.
- [8] Jones, B., Mead, G., and Steevens, P. 2008. The effects of E20 on plastic automotive fuel system components. Minnesota center for automotive research at Minnesota State University, Minnesota, USA.
- [9] Chooseng, P. 2009. Influences of gasohol on glass fiber reinforced polyamide 6 composite. Master Thesis. Chemical Engineering, Chulalongkorn University, Bangkok, Thailand.
- [10] Smith, J.L., and Workman, J.P. Alcohol for motor fuels[online]. 2008. Available from:  
<http://www.ext.colostate.edu/pubs/farmmgmt/05010.html> [2010, February 5]

- [11] Gullu, A., Ozdemir, A., and Ozdemir, E. 2006. Experimental investigation of the effect of glass fibres on the mechanical properties of polypropylene (PP) and polyamide 6 (PA6) plastic. Materials and Design: 316-323.
- [12] Fyrwald, E. 1995. Specialty grades widen performance envelope and challenge other resins. Modern Plastic EnCyClopedia' 96, B 61-B 62.
- [13] PTT Group. Gasohol fuels[online]. 2008. Available from:  
<http://www.pttplc.com> [2010, February 4]
- [14] Ethanol[online]. 2008. Available from: [http:// www.energy.go.th](http://www.energy.go.th) [2010, February 24]
- [15] Kim, S., and Dale, B. 2005. Environmental aspects of ethanol derived from no-tilled corn grain: nonrenewable energy consumption and greenhouse gas. Biomass Bioenergy: 485-489.
- [16] Guerrieri, D.A., Caffrey, P.J., and Roa, V. 1995. Investigation into the vehicular exhaust emission of high percentage Ethanol blends. SAE International
- [17] Taylor, A.B., Mocan, D.P., and Bell, A.J. 1996. Gasoline/Alcohol Blends: Exhaust Emissions, Performance and Burn-Rate in a Multi-Valve Production Engine. SAE International
- [18] Toluene[online]. 2010. Available from:  
<http://en.wikipedia.org/wiki/Toluene> [2010, March 1]
- [19] Toluene uses and market data[online]. 2008. Available from:  
<http://www.icis.com/v2/chemicals/9076550/toluene/uses.html> [2010, March 1]
- [20] The Science of Nylon[online]. 2009. Available from:  
<http://www.chemheritage.org/educationalservices/nylon/chem/name.html>  
[2010, February 24]
- [21] Roger, F.J., Michell, R., and Donald, V.R. 1998. Guide to Start Fiber Reinforced Plastics
- [22] IDES. Nylon[online]. 2010. Available from:  
<http://www.ides.com/generics/Nylon.htm> [2010, February 20]
- [23] Hegde, R.R., Dahiya, A., and Kamath, M.G. Nylon fibers[online]. 2004.  
Available from: <http://www.engr.utk.edu/mse/Textiles/Nylon%20fibers.htm>  
[2010, February 27]

- [24] Nylon[online]. 2009. Available from: <http://en.wikipedia.org/wiki/Nylon.html>  
[2010, February 22]
- [25] Macrogalleria. Making nylon 6 and 6,10[online]. 1998. Available from:  
<http://www.pslc.ws/macrog/lab/lab01.htm> [2010, February 24]
- [26] Mewborn, J.W. 1996. Nylons:Semi-aromatic grades add market share and stimulate demand. Modern Plastic EnCyClopedia' 97, B 54-B 55.
- [27] Rapra. Nylon 6[online]. 2001. Available from:  
<http://www.azom.com/Details.asp?ArticleID=442> [2010, February 20]
- [28] Polyamide 6 and polyamide 6,6[online]. 1995. Available from:  
<http://www.Omnexus.com/tc/polyamides-center/index.aspx?id=pa6.html>  
[2010, February 20]
- [29] Marin, J. 1942. Mechanical properties of materials and design. 1942. New york and London: McGRAW-HILL BOOK
- [30] UBE chemicals (Asia). Technical data sheet. Nylon 6 natural color UBE NYLON 1015B. Bangkok. UBE Group (Thailand).
- [31] UBE chemicals (Asia). Technical data sheet. Nylon 6 natural color UBE NYLON 1015GC3. Bangkok. UBE Group (Thailand).
- [32] UBE chemicals (Asia). Technical data sheet. Nylon 6 natural color UBE NYLON 1015GC6. Bangkok. UBE Group (Thailand).
- [33] Thomas Publishing Company. Properties of glass fiber reinforced nylon 6 composites[online]. 2009. Available from: <http://www.efunda.com.html>  
[2010, February 27]
- [34] Mark, H.F. 2007. Encyclopedia of Polymer Science and Technology.
- [35] Whelan, A., and Craft, J.L. The physical testing of plastics and rubber. England: J.J. Lloyd instrument.
- [36] Kagan, V.A., McPherson, R., and Chung, J.S. 2003. An Advanced High Modulus (HMG) Short Glass-Fiber Reinforced Nylon 6: Part I - Role and Kinetic of Fiber-Glass Reinforcements. Journal of Reinforced Plastics and Composites 22: 1035-1044

- [37] Wu, S.-H., et al. 2001. Mechanical, thermal and morphological properties of glass fiber and carbon fiber reinforced polyamide-6 and polyamide-6/clay nanocomposites. Materials Letters 49: 327-333.
- [38] Morgan, P. 1954. Glass reinforced plastics. 3. New York: Philosophical library.
- [39] UBE GROUP in Thailand. Nylon application[online]. Available from:  
[http://www.ube.co.th/ubegroupinthailand\\_UNT.php](http://www.ube.co.th/ubegroupinthailand_UNT.php) [2010, March 10]
- [40] Wikipedia foundation. Tensile strength[online]. 2009. Available from:  
<http://en.wikipedia.org/wiki/Tensile> [2010, February 21]
- [41] Integrated Publishing. Destructive testing[online]. 2009. Available from:  
<http://www.tpub.com/steelworker1/78.htm> [2010, February 21]
- [42] Swallowe, G.M. 1999. Mechanical Properties and Testing of Polymer. 3. London: Kluwer Academic.
- [43] Naranjo, A., et al. 2008. Plastics Testing and Characterization. Munchen: Carl hanser verlag.
- [44] American National Standard. 2000. Standard test method for tensile properties of plastics. Designation: D 638, ASTM International.
- [45] American National Standard. Standard test method for compressive properties of rigid plastics. Designation: D695, ASTM International.
- [46] Wikipedia the free encyclopedia. Compressive strength[online]. 2010.  
Available from: [http://en.wikipedia.org/wiki/Compressive\\_strength](http://en.wikipedia.org/wiki/Compressive_strength)  
[2010, February 20]
- [47] American National Standard. 2001. Standard test method for flexural properties of unreinforced and reinforced plastics and electrical insulating materials. Desination: D 790, ASTM International.
- [48] Bramer, A. Plastic welding: Inspection and testing of plastic welds[online].  
Available from: <http://www.plasticmag.com/welding.asp?fIssue=Mar/Apr-02&aid=3501> [2010, February 20]
- [49] Instron (Thailand). Instron the difference is mesurable[online]. 2008. Available from:  
<http://www.instron.co.th/wa/applications/test> [2010, February 20]
- [50] Grellmann, W., Seidler, S., and Anderson, P.I. 2007. Polymer testing. Canada: Hanser Gradner Publications.

- [51] Intertex Plastics Technology. Plastic testing[online]. 2008. Available from: [http:// www.ptli.com.html](http://www.ptli.com.html) [2010, February 21]
- [52] American National Standard. 2004. Standard test methods for determining the izod pendulum impact resistance of plastics. Designation: D 256, ASTM International.
- [53] Menard, K.P. 1999. Dynamic mechanical analysis: a practical introduction. CRC Press.
- [54] American National Standard. 2008. Standard test method for glass transition temperature (DMA  $T_g$ ) of polymer matrix composites by dynamic mechanical analysis (DMA). Designation: D 7028, ASTM International.
- [55] American National Standard. 2001. Standard test method for deflection temperature of plastics under flexural load in edgewise position. Designation: D 648-01, ASTM International.
- [56] Vlasveld, D.P.N., et al. 2007. Continuous fibre composites with a nanocomposite matrix: Improvement of flexural and compressive strength at elevated temperatures. Composites Part A: Applied Science and Manufacturing: 703-738.
- [57] Vlasveld, D.P.N., et al. 2005. Moisture absorption in polyamide-6 silicate nanocomposites and its influence on the mechanical properties. Polymer 46: 12567-12576.
- [58] Baschek, G., Hartwig, G., and Zahradnik, F. 1999. Effect of water absorption in polymers at low and high temperatures. Polymer 40: 3433-3441.
- [59] Jiang, T., et al. 2005. Study on solvent permeation resistance properties of nylon 6/clay nanocomposite. European Polymer Journal 41: 459-466.
- [60] Li, C., and Liu, X. 2007. Mechanical and thermal properties study of glass fiber reinforced polyarylene ether nitriles. Materials Letters 61: 2239-2242.
- [61] Sun, L., et al. 2007. Crystallization and thermal properties of polyamide 6 composites filled with different nanofillers. Materials Letters 61: 3963-3966.
- [62] Brostow, W., and Corneliussen, R.D. 1986. Failure of plastics. New York: Hanser.
- [63] Cartledge, H.C.Y., Baillie, C., and Mai, Y.W. 1996. Friction and wear mechanisms of a thermoplastic composite GF/PA6 subjected to different thermal histories. Wear 194: 178-184.

- [64] Laura, D.M., et al. 2002. Effect of glass fiber surface chemistry on the mechanical properties of glass fiber reinforced, rubber-toughened nylon 6. Polymer 43: 4673-4687.
- [65] Lebaron, P.C., Wang, Z., and Pinnavaia, T.J. 1999. Polymer-layered silicate nanocomposites: an overview. Applied Clay Science 15: 11-29.
- [66] Sun, C.T., and Vaidya, R.S. 1996. Prediction of composite properties from a representative volume element. Composites Science and Technology 56: 171-179.
- [67] Pirotesak, N. 2006. Analysis of Young's modulus of polypropylene/clay nanocomposites. Master Thesis. Chemical Engineering, Chulalongkorn University, Bangkok, Thailand.
- [68] Gibson, R.F. Principles of composite material mechanics. Mechanical Engineering, Wayne State University, Michigan, USA.
- [69] Folkes, M. 1982. Short fibre reinforced thermoplastics. Wiley: 192.



## APPENDICES

APPENDIX A  
THE EXPERIMENTAL DATA OF PHYSICAL PROPERTIES

## Appendix A1 Water absorption

Table A1-1 Water absorption of PA6 and PA6/GF composites

Week	Material	Mass (g)					Average (g)
		1	2	3	4	5	
0	PA6	6.7888	6.8071	7.0092	6.6943	6.8287	6.8256±0.1147
	PA6/GF (15 wt%)	7.5789	7.5234	7.4908	7.5270	7.7368	7.5714±0.0977
	PA6/GF (30 wt%)	8.4333	8.4525	8.4209	8.3947	8.4838	8.4376±0.0327
1	PA6	7.0564	7.1025	7.1948	7.0735	7.1084	7.1071±0.0534
	PA6/GF (15 wt%)	7.8488	7.7885	7.7579	7.8005	8.0066	7.8405±0.0985
	PA6/GF (30 wt%)	8.6835	8.7028	8.6676	8.6386	8.7278	8.6841±0.0339
2	PA6	7.2540	7.2670	7.4582	7.1462	7.2782	7.2807±0.1124
	PA6/GF (15 wt%)	7.9376	7.8754	7.8458	7.8883	8.0910	7.9276±0.0972
	PA6/GF (30 wt%)	8.7467	8.7608	8.7325	8.7035	8.7927	8.7472±0.0331
3	PA6	7.2843	7.2970	7.4885	7.1763	7.3084	7.3109±0.1124
	PA6/GF (15 wt%)	7.9980	7.9355	7.9049	7.9479	8.1549	7.9882±0.0990
	PA6/GF (30 wt%)	8.7916	8.8069	8.7777	8.7485	8.8383	8.7926±0.0334
5	PA6	7.2846	7.2970	7.4888	7.1764	7.3085	7.3111±0.1125
	PA6/GF (15 wt%)	8.0231	7.9631	7.9322	7.9734	8.1846	8.0153±0.1001
	PA6/GF (30 wt%)	8.8158	8.8471	8.8119	8.7863	8.8725	8.8267±0.0335
7	PA6	7.2842	7.3014	7.4912	7.1775	7.3202	7.3149±0.1130
	PA6/GF (15 wt%)	8.0247	7.9617	7.9306	7.9729	8.1856	8.0151±0.1012
	PA6/GF (30 wt%)	8.8342	8.8527	8.8373	8.8067	8.8936	8.8449±0.0319
10	PA6	7.2746	7.2933	7.4846	7.1690	7.3132	7.3069±0.1139
	PA6/GF (15 wt%)	8.0393	7.9750	7.9440	7.9873	8.1996	8.0290±0.1014
	PA6/GF (30 wt%)	8.8348	8.8543	8.8397	8.8079	8.8934	8.8460±0.0314
13	PA6	7.2742	7.2922	7.4832	7.1686	7.3116	7.3060±0.1135
	PA6/GF (15 wt%)	8.0235	7.9601	7.9287	7.9707	8.1852	8.0136±0.1018
	PA6/GF (30 wt%)	8.8380	8.8575	8.8429	8.8111	8.8966	8.8492±0.0314

Week	Material	Mass (g)					Average (g)
		1	2	3	4	5	
16	PA6	7.2737	7.2910	7.4819	7.1683	7.3099	7.3050±0.1131
	PA6/GF (15 wt%)	8.0268	7.9646	7.9348	7.9752	8.1886	8.0180±0.1010
	PA6/GF (30 wt%)	8.8401	8.8575	8.8457	8.8118	8.8969	8.8504±0.0309

## Appendix A2 Mass change

Table A2-1 Mass of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
0	Aggressive Ethanol	6.7582	6.8205	6.7421	6.9603	6.6771	6.7916±0.0956
	Ethanol	6.8659	6.8867	6.8186	6.9262	6.7677	6.8530±0.0615
	Isooctane	6.8077	6.7542	6.7517	6.7820	6.7314	6.7654±0.0297
	Toluene	6.8532	6.7308	6.7872	6.7305	6.9258	6.8055±0.0841
1	Aggressive Ethanol	6.9287	6.9754	6.8887	7.0970	6.8379	6.9455±0.0987
	Ethanol	6.9899	7.0305	6.9435	7.0238	6.9021	6.9780±0.0547
	Isooctane	6.8180	6.7618	6.7593	6.7882	6.7347	6.7724±0.0318
	Toluene	6.8690	6.7465	6.803	6.7469	6.9423	6.8216±0.0842
2	Aggressive Ethanol	7.0950	7.1227	7.0329	7.2215	6.9980	7.0940±0.0866
	Ethanol	7.1131	7.1691	7.0673	7.1185	7.0329	7.1002±0.0521
	Isooctane	6.8220	6.7692	6.7662	6.7959	6.7458	6.7798±0.0296
	Toluene	6.8993	6.7759	6.8298	6.7749	6.9668	6.8493±0.0831
3	Aggressive Ethanol	7.1408	7.1618	7.0712	7.2523	7.0451	7.1342±0.0816
	Ethanol	7.1464	7.2059	7.1019	7.1434	7.0713	7.1338±0.0509
	Isooctane	6.8306	6.7712	6.7698	6.7994	6.7541	6.7850±0.0303
	Toluene	6.9074	6.7833	6.8380	6.7829	6.9758	6.8575±0.0836
5	Aggressive Ethanol	7.1953	7.2044	7.1152	7.2848	7.0983	7.1796±0.0753
	Ethanol	7.1770	7.2432	7.1320	7.1642	7.1054	7.1644±0.0522
	Isooctane	6.8412	6.7851	6.7830	6.8122	6.7623	6.7968±0.0305
	Toluene	6.9134	6.7891	6.8436	6.7885	6.9871	6.8643±0.0856

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
7	Aggressive Ethanol	7.3398	7.3462	7.2587	7.3922	7.2376	7.3149±0.0646
	Ethanol	7.2915	7.3852	7.2632	7.2410	7.2538	7.2869±0.0580
	Isooctane	6.8555	6.7975	6.7961	6.8254	6.7746	6.8098±0.0313
	Toluene	6.9260	6.8012	6.8554	6.8004	6.9935	6.8753±0.0837
10	Aggressive Ethanol	7.3543	7.3930	7.2966	7.4729	7.2526	7.3539±0.0855
	Ethanol	7.3957	7.4666	7.3589	7.3162	7.3294	7.3734±0.0604
	Isooctane	6.8630	6.8094	6.8030	6.8343	6.7867	6.8193±0.0298
	Toluene	6.9427	6.8195	6.8745	6.8178	7.0109	6.8931±0.0833
13	Aggressive Ethanol	7.3619	7.4037	7.3050	7.4981	7.2595	7.3656±0.0921
	Ethanol	7.4255	7.4793	7.3795	7.3840	7.3403	7.4017±0.0528
	Isooctane	6.8859	6.8264	6.8250	6.8604	6.8068	6.8409±0.0317
	Toluene	6.9575	6.8330	6.8872	6.8294	7.0260	6.9066±0.0846
16	Aggressive Ethanol	7.3686	7.4109	7.3121	7.5096	7.2657	7.3734±0.0940
	Ethanol	7.4353	7.4858	7.3861	7.4196	7.3463	7.4146±0.0524
	Isooctane	6.9021	6.8442	6.8428	6.8715	6.8212	6.8564±0.0312
	Toluene	6.9615	6.8363	6.8908	6.8354	7.0283	6.9105±0.0837

Table A2-2 Mass of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
0	Aggressive Ethanol	7.5358	7.6150	7.4853	7.5167	7.6153	7.5536±0.0590
	Ethanol	7.5380	7.7000	7.6169	7.5046	7.5567	7.5832±0.0770
	Isooctane	7.6822	7.5820	7.6674	7.5583	7.6644	7.6309±0.0565
	Toluene	7.5531	7.3676	7.5942	7.4106	7.5131	7.4877±0.0957
1	Aggressive Ethanol	7.6723	7.7569	7.6226	7.6504	7.7482	7.6901±0.0598
	Ethanol	7.6403	7.8102	7.7416	7.6225	7.6724	7.6974±0.0777
	Isooctane	7.7147	7.6066	7.6989	7.5939	7.6977	7.6624±0.0573
	Toluene	7.6319	7.4038	7.5867	7.4443	7.5491	7.5232±0.0962
2	Aggressive Ethanol	7.7147	7.8010	7.6644	7.6916	7.7878	7.7319±0.0599
	Ethanol	7.6723	7.8448	7.7788	7.6593	7.7067	7.7324±0.0781
	Isooctane	7.7188	7.6148	7.7050	7.5990	7.7038	7.6683±0.0566
	Toluene	7.6403	7.4118	7.5948	7.4531	7.5563	7.5313±0.0961
3	Aggressive Ethanol	7.7608	7.8475	7.7100	7.7362	7.8312	7.7771±0.0598
	Ethanol	7.7075	7.8835	7.8196	7.6985	7.7452	7.7709±0.0790
	Isooctane	7.7254	7.6218	7.7119	7.6032	7.7083	7.6741±0.0570
	Toluene	7.6469	7.4185	7.6015	7.4596	7.5623	7.5378±0.0961
5	Aggressive Ethanol	7.8275	7.9118	7.7734	7.7986	7.8930	7.8409±0.0597
	Ethanol	7.7534	7.9352	7.8723	7.7497	7.8051	7.8231±0.0799
	Isooctane	7.7355	7.6362	7.7240	7.6163	7.7246	7.6873±0.0564
	Toluene	7.6566	7.4369	7.6113	7.4724	7.5686	7.5492±0.0926

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
7	Aggressive Ethanol	7.8907	7.9696	7.8319	7.8549	7.9477	7.8990±0.0589
	Ethanol	7.8438	7.9821	7.9233	7.7977	7.7952	7.8684±0.0820
	Isooctane	7.7524	7.6433	7.7280	7.6222	7.7359	7.6964±0.0592
	Toluene	7.6678	7.4403	7.6223	7.5835	7.4796	7.5587±0.0960
10	Aggressive Ethanol	7.9903	8.0605	7.9234	7.9424	8.0378	7.9909±0.0591
	Ethanol	7.8568	8.0571	8.0056	7.8701	7.9188	7.9417±0.0870
	Isooctane	7.7600	7.6572	7.7411	7.6331	7.7409	7.7065±0.0571
	Toluene	7.6851	7.4546	7.6374	7.5973	7.4918	7.5732±0.0974
13	Aggressive Ethanol	8.0344	8.1064	7.9649	7.9911	8.0996	8.0393±0.0633
	Ethanol	7.9161	8.1270	8.0774	7.9361	7.9889	8.0091±0.0908
	Isooctane	7.7622	7.6574	7.7449	7.6364	7.7437	7.7089±0.0576
	Toluene	7.687	7.4579	7.6418	7.6012	7.4983	7.5772±0.0965
16	Aggressive Ethanol	8.0483	8.1228	7.9791	8.0076	8.1263	8.0568±0.0666
	Ethanol	7.9584	8.1585	8.0946	7.9594	8.0116	8.0365±0.0879
	Isooctane	7.7683	7.6664	7.7541	7.6441	7.7514	7.7169±0.0572
	Toluene	7.6973	7.4662	7.6506	7.6093	7.5074	7.5862±0.0970

Table A2-3 Mass of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
0	Aggressive Ethanol	8.3688	8.3692	8.4209	8.3218	8.3381	8.3638±0.0379
	Ethanol	8.4018	8.2692	8.4253	8.3624	8.4041	8.3726±0.0621
	Isooctane	8.4827	8.4007	8.3882	8.3696	8.4088	8.4100±0.0432
	Toluene	8.3427	8.3753	8.3900	8.4471	8.3590	8.3828±0.0401
1	Aggressive Ethanol	8.5524	8.5569	8.6024	8.4995	8.5273	8.5477±0.0382
	Ethanol	8.4832	8.3144	8.4911	8.4403	8.4988	8.4456±0.0767
	Isooctane	8.5108	8.4256	8.4229	8.4034	8.4435	8.4412±0.0414
	Toluene	8.3745	8.4071	8.4218	8.4789	8.3908	8.4146±0.0401
2	Aggressive Ethanol	8.5815	8.5808	8.6515	8.5494	8.5874	8.5901±0.0374
	Ethanol	8.5304	8.3982	8.5495	8.5241	8.8531	8.5171±0.0703
	Isooctane	8.5138	8.4318	8.4272	8.4075	8.4481	8.4457±0.0407
	Toluene	8.3855	8.4190	8.4456	8.4991	8.4119	8.4322±0.0431
3	Aggressive Ethanol	8.6308	8.6201	8.6757	8.5887	8.6094	8.6249±0.0324
	Ethanol	8.5631	8.4309	8.5822	8.5568	8.6158	8.5498±0.0703
	Isooctane	8.5153	8.4330	8.4285	8.4089	8.4497	8.4471±0.0408
	Toluene	8.3878	8.4227	8.4480	8.5013	8.4140	8.4348±0.0430
5	Aggressive Ethanol	8.6590	8.6494	8.7053	8.6161	8.6384	8.6536±0.0330
	Ethanol	8.5910	8.4586	8.6088	8.5852	8.6436	8.5774±0.0702
	Isooctane	8.5171	8.4345	8.4298	8.4106	8.4511	8.4486±0.0409
	Toluene	8.3895	8.4245	8.4499	8.5031	8.4156	8.4365±0.0430

Week	Chemical	Mass (g)					Average (g)
		1	2	3	4	5	
7	Aggressive Ethanol	8.6803	8.6688	8.7490	8.6515	8.6828	8.6865±0.0371
	Ethanol	8.6058	8.4839	8.6316	8.6590	8.7227	8.6206±0.0879
	Isooctane	8.5206	8.4383	8.4337	8.4144	8.4553	8.4525±0.0408
	Toluene	8.3905	8.4253	8.4520	8.5050	8.4178	8.4381±0.0433
10	Aggressive Ethanol	8.6715	8.6908	8.7942	8.6881	8.7076	8.7104±0.0485
	Ethanol	8.6613	8.5462	8.6901	8.7284	8.7879	8.6828±0.0899
	Isooctane	8.5361	8.4536	8.4532	8.4326	8.4736	8.4698±0.0398
	Toluene	8.4024	8.4314	8.4628	8.5153	8.4274	8.4479±0.0434
13	Aggressive Ethanol	8.6994	8.7347	8.8290	8.7352	8.7411	8.7479±0.0483
	Ethanol	8.7051	8.5880	8.7310	8.7697	8.8282	8.7244±0.0892
	Isooctane	8.5454	8.4618	8.4603	8.4405	8.4811	8.4778±0.0404
	Toluene	8.4152	8.4445	8.4749	8.5270	8.4388	8.4601±0.0430
16	Aggressive Ethanol	8.7257	8.7493	8.8447	8.7515	8.7602	8.7663±0.0457
	Ethanol	8.7445	8.6267	8.7683	8.8092	8.8643	8.7626±0.0885
	Isooctane	8.5515	8.4682	8.4670	8.4464	8.4869	8.4840±0.0404
	Toluene	8.4367	8.4682	8.4993	8.5509	8.4622	8.4835±0.0438

## Appendix A3 Volume change

Table A3-1 Volume of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	5.9154	5.9551	5.8814	6.0550	5.8168	5.9247±0.0794
	Ethanol	6.0854	6.2015	6.1023	6.2078	6.0643	6.1323±0.0675
	Isooctane	5.9376	5.9016	5.8861	5.9694	5.8714	5.9132±0.0399
	Toluene	6.0043	5.8797	5.9229	5.9156	6.0497	5.9544±0.0701
1	Aggressive Ethanol	6.1055	6.1425	6.0473	6.2103	6.0089	6.1264±0.0714
	Ethanol	6.1553	6.2064	6.1373	6.2494	6.1260	6.1828±0.0601
	Isooctane	5.9442	5.9071	5.8977	5.9769	5.8734	5.9199±0.0408
	Toluene	6.0702	5.9049	5.9350	5.8892	6.0293	5.9657±0.0798
2	Aggressive Ethanol	6.3432	6.3323	6.2504	6.3805	6.2328	6.3078±0.0634
	Ethanol	6.3011	6.3463	6.2525	6.2674	6.2407	6.2816±0.0427
	Isooctane	5.9508	5.9127	5.9190	5.9854	5.8714	5.9278±0.0428
	Toluene	6.0483	5.9245	5.9845	5.9122	6.0640	5.9867±0.0693
3	Aggressive Ethanol	6.3863	6.3771	6.2979	6.4207	6.2798	6.3523±0.606
	Ethanol	6.3184	6.3755	6.2843	6.2697	6.2669	6.3030±0.0454
	Isooctane	5.9562	5.9147	5.9211	5.9866	5.8728	5.9303±0.0432
	Toluene	6.0553	5.9281	6.0029	5.9162	6.0825	5.9970±0.0742
5	Aggressive Ethanol	6.4654	6.4381	6.3768	6.4820	6.3502	6.4225±0.0569
	Ethanol	6.3530	6.4262	6.3255	6.3115	6.3272	6.3487±0.0458
	Isooctane	5.9758	5.9369	5.9217	6.0066	5.8939	5.9470±0.0445
	Toluene	6.0603	5.9299	5.9925	5.9409	6.0912	6.0029±0.0714

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	6.5743	6.5424	6.4900	6.5603	6.4591	6.5252±0.0488
	Ethanol	6.4943	6.5759	6.4816	6.3890	6.4859	6.4853±0.0663
	Isooctane	5.9692	5.9385	5.9404	6.0264	5.9057	5.9560±0.0453
	Toluene	6.0424	5.9775	5.9981	5.9468	6.0738	6.0077±0.0507
10	Aggressive Ethanol	6.6083	6.6393	6.5909	6.6767	6.5046	6.6039±0.0644
	Ethanol	6.6245	6.6662	6.5958	6.4829	6.5808	6.5900±0.0682
	Isooctane	5.9751	5.9489	5.9259	6.0279	5.9125	5.9581±0.0457
	Toluene	6.0766	5.9610	6.0159	5.9572	6.1067	6.0235±0.0673
13	Aggressive Ethanol	6.6983	6.6204	6.6981	6.4408	6.6422	6.6199±0.1059
	Ethanol	6.6616	6.7026	6.6280	6.5673	6.6099	6.6339±0.0513
	Isooctane	6.0315	5.9680	5.9585	6.0640	5.9490	5.9942±0.0507
	Toluene	5.9682	6.0148	5.9680	6.1574	6.0036	6.0224±0.0783
16	Aggressive Ethanol	6.7166	6.5839	6.7130	6.4460	6.6454	6.6210±0.11
	Ethanol	6.6707	6.7293	6.6259	6.5921	6.6248	6.6485±0.0531
	Isooctane	6.0462	5.9751	5.9654	6.0717	5.9568	6.0030±0.0522
	Toluene	5.9750	6.0017	5.9926	6.1554	6.0054	6.0260±0.0732

Table A3-2 Volume of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	6.0286	6.0920	5.9882	6.0134	6.0922	6.0429±0.0472
	Ethanol	6.0304	6.1600	6.0935	6.0037	6.0454	6.0666±0.0616
	Isooctane	6.1458	6.0656	6.1339	6.0466	6.1315	6.1047±0.0452
	Toluene	6.0425	5.8941	6.0754	5.9285	6.0105	5.9902±0.0766
1	Aggressive Ethanol	6.1378	6.2055	6.0981	6.1203	6.1986	6.1521±0.0478
	Ethanol	6.1122	6.2482	6.1933	6.0908	6.1379	6.1579±0.0622
	Isooctane	6.1718	6.0853	6.1591	6.0751	6.1582	6.1299±0.0458
	Toluene	6.1055	5.9230	6.0694	5.9554	6.0393	6.0185±0.0769
2	Aggressive Ethanol	6.1817	6.2408	6.1315	6.1533	6.2302	6.1855±0.0480
	Ethanol	6.1378	6.2758	6.2230	6.1274	6.1654	6.1859±0.0625
	Isooctane	6.1750	6.0918	6.1640	6.0792	6.1630	6.1346±0.0453
	Toluene	6.1122	5.9294	6.0758	5.9625	6.0450	6.0250±0.0769
3	Aggressive Ethanol	6.2086	6.2780	6.1680	6.1890	6.2650	6.2217±0.0479
	Ethanol	6.1660	6.3068	6.2557	6.1588	6.1962	6.2167±0.0632
	Isooctane	6.1803	6.0974	6.1695	6.0826	6.1666	6.1393±0.0456
	Toluene	6.1175	5.9348	6.0812	5.9677	6.0498	6.0302±0.0768
5	Aggressive Ethanol	6.2620	6.3294	6.2187	6.2389	6.3144	6.2727±0.0478
	Ethanol	6.2027	6.3481	6.2978	6.1998	6.2441	6.2585±0.0639
	Isooctane	6.1884	6.1090	6.1792	6.0930	6.1797	6.1499±0.0451
	Toluene	6.1253	5.9495	6.0890	5.9779	6.0549	6.0393±0.0741

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	6.3126	6.3757	6.2655	6.2839	6.3582	6.3192±0.0471
	Ethanol	6.2750	6.3857	6.3386	6.2382	6.2362	6.2947±0.0656
	Isooctane	6.2019	6.1146	6.1824	6.0978	6.1887	6.1571±0.0474
	Toluene	6.1342	5.9522	6.0978	6.0668	5.9837	6.0470±0.0768
10	Aggressive Ethanol	6.3922	6.4484	6.3387	6.3539	6.4302	6.3927±0.0472
	Ethanol	6.2854	6.4457	6.4045	6.2961	6.3350	6.3533±0.0696
	Isooctane	6.2080	6.1258	6.1929	6.1065	6.1927	6.1652±0.0457
	Toluene	6.1481	5.9637	6.1099	6.0778	5.9934	6.0586±0.0779
13	Aggressive Ethanol	6.4275	6.4851	6.3719	6.3929	6.4797	6.4314±0.0506
	Ethanol	6.3329	6.5016	6.4619	6.3489	6.3911	6.4073±0.0726
	Isooctane	6.2098	6.1259	6.1959	6.1091	6.1950	6.1671±0.0461
	Toluene	6.1496	5.9663	6.1134	6.0810	5.9986	6.0618±0.0772
16	Aggressive Ethanol	6.4386	6.4982	6.3833	6.4061	6.5010	6.4455±0.0532
	Ethanol	6.3667	6.5268	6.4757	6.3675	6.4093	6.4292±0.0703
	Isooctane	6.2146	6.1331	6.2033	6.1153	6.2011	6.1735±0.0457
	Toluene	6.1578	5.9730	6.1205	6.0874	6.0059	6.0689±0.0776

Table A3-3 Volume of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	6.1991	6.1994	6.2377	6.1643	6.1764	6.1954±0.0281
	Ethanol	6.1778	6.0803	6.1951	6.1488	6.1795	6.1563±0.0457
	Isooctane	6.2373	6.1770	6.1678	6.1541	6.1829	6.1838±0.0318
	Toluene	6.1343	6.1583	6.1691	6.2111	6.1463	6.1638±0.0295
1	Aggressive Ethanol	6.3351	6.3384	6.3721	6.2959	6.3165	6.3316±0.0283
	Ethanol	6.2376	6.1135	6.2435	6.2061	6.2491	6.2100±0.0564
	Isooctane	6.2579	6.1953	6.1933	6.1790	6.2085	6.2068±0.0304
	Toluene	6.1577	6.1817	6.1925	6.2345	6.1697	6.1872±0.0295
2	Aggressive Ethanol	6.3567	6.3561	6.4085	6.3329	6.3611	6.3631±0.0277
	Ethanol	6.2724	6.1751	6.2864	6.2677	6.3111	6.2625±0.0517
	Isooctane	6.2601	6.1999	6.1965	6.1820	6.2118	6.2100±0.0300
	Toluene	6.1658	6.1904	6.2100	6.2493	6.1852	6.2002±0.0317
3	Aggressive Ethanol	6.3932	6.3853	6.4264	6.3620	6.3773	6.3888±0.0240
	Ethanol	6.2964	6.1992	6.3104	6.2918	6.3351	6.2866±0.0517
	Isooctane	6.2613	6.2007	6.1974	6.1830	6.2130	6.2111±0.0300
	Toluene	6.1675	6.1932	6.2118	6.2510	6.1868	6.2020±0.0316
5	Aggressive Ethanol	6.4140	6.4070	6.4484	6.3823	6.3988	6.4101±0.0245
	Ethanol	6.3169	6.2196	6.3300	6.3126	6.3556	6.3069±0.0516
	Isooctane	6.2626	6.2018	6.1984	6.1843	6.2140	6.2122±0.0301
	Toluene	6.1688	6.1945	6.2132	6.2523	6.1879	6.2033±0.0316

Week	Chemical	Volume (cm <sup>3</sup> )					Average (cm <sup>3</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	6.4298	6.4213	6.4807	6.4085	6.4317	6.4344±0.0275
	Ethanol	6.3278	6.2382	6.3468	6.3669	6.4138	6.3387±0.0647
	Isooctane	6.2651	6.2046	6.2013	6.1871	6.2171	6.2150±0.0300
	Toluene	6.1695	6.1951	6.2147	6.2537	6.1896	6.2045±0.0319
10	Aggressive Ethanol	6.4233	6.4376	6.5142	6.4356	6.4500	6.4522±0.0360
	Ethanol	6.3686	6.2840	6.3898	6.4179	6.4617	6.3844±0.0661
	Isooctane	6.2765	6.2159	6.2156	6.2004	6.2306	6.2278±0.0293
	Toluene	6.1782	6.1996	6.2227	6.2613	6.1966	6.2117±0.0319
13	Aggressive Ethanol	6.4440	6.4710	6.5400	6.4705	6.4749	6.4799±0.0357
	Ethanol	6.4008	6.3147	6.4199	6.4483	6.4913	6.4150±0.0656
	Isooctane	6.2834	6.2219	6.2208	6.2063	6.2361	6.2337±0.0297
	Toluene	6.1876	6.2092	6.2316	6.2699	6.2050	6.2206±0.0316
16	Aggressive Ethanol	6.4635	6.4810	6.5516	6.4826	6.4890	6.4935±0.0338
	Ethanol	6.4298	6.3432	6.4473	6.4774	6.5179	6.4431±0.0651
	Isooctane	6.2879	6.2266	6.2257	6.2106	6.2404	6.2382±0.0297
	Toluene	6.2035	6.2266	6.2495	6.2874	6.2222	6.2378±0.0322

APPENDIX B  
THE EXPERIMENTAL DATA OF THERMAL PROPERTIES

## Appendix B1 Heat distortion temperature

Table B1-1 Heat distortion temperature of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Heat distortion temperature (°C)			Average (°C)
		1	2	3	
0	Aggressive Ethanol	83.9	82.9	84.5	83.77±0.81
	Ethanol				
	Isooctane				
	Toluene				
2	Aggressive Ethanol	59.7	56.5	60.2	58.80±2.01
	Ethanol	60.1	58.7	63.7	60.83±2.58
	Isooctane	82.8	80.8	81.1	81.57±1.08
	Toluene	74.3	73.4	74.2	73.97±0.49
5	Aggressive Ethanol	56.7	55.2	54.5	55.47±1.12
	Ethanol	58.2	57.4	59.2	58.27±0.90
	Isooctane	78.4	79	75.9	77.77±1.64
	Toluene	69.7	71.7	71.8	71.07±1.18
10	Aggressive Ethanol	54.4	56.2	55.4	55.33±0.90
	Ethanol	54.9	55.1	56.3	55.43±0.76
	Isooctane	73.3	72.7	72.3	72.77±0.50
	Toluene	68.2	66	65.8	66.67±1.33
16	Aggressive Ethanol	54.4	51.2	53.9	53.17±1.72
	Ethanol	53.9	53.6	52.2	53.23±0.91
	Isooctane	70.7	70	62.5	67.73±4.55
	Toluene	64.3	61.9	60.6	62.27±1.88

**Table B1-2** Heat distortion temperature of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Heat distortion temperature (°C)			Average (°C)
		1	2	3	
0	Aggressive Ethanol	176.3	176.5	176.7	176.5±0.20
	Ethanol				
	Isooctane				
	Toluene				
2	Aggressive Ethanol	119.4	117.5	114.8	117.23±2.31
	Ethanol	125.9	126.4	131.6	127.97±3.16
	Isooctane	160.1	156.5	160.1	158.90±2.08
	Toluene	150.2	150	141.2	147.13±5.14
5	Aggressive Ethanol	95.2	101.6	109.6	102.13±7.21
	Ethanol	115.1	116.6	105.9	112.53±5.79
	Isooctane	145.3	150.2	146.5	147.33±2.55
	Toluene	129.2	134.5	137.8	133.83±4.34
10	Aggressive Ethanol	92.4	89.1	93.2	91.57±2.17
	Ethanol	103	102	103.3	102.77±0.68
	Isooctane	142.4	138	133.5	137.97±4.45
	Toluene	118.3	112.3	113.7	114.77±3.14
16	Aggressive Ethanol	82.1	85.7	80.5	82.77±2.66
	Ethanol	81.5	91.1	89.8	87.47±5.21
	Isooctane	122.7	119.2	117.6	119.83±2.61
	Toluene	109.4	108.5	106.2	108.03±1.65

**Table B1-3** Heat distortion temperature of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Heat distortion temperature (°C)			Average (°C)
		1	2	3	
0	Aggressive Ethanol	181.8	183	183.2	182.67±0.76
	Ethanol				
	Isooctane				
	Toluene				
2	Aggressive Ethanol	153.2	147	142.7	147.63±5.28
	Ethanol	149.5	156.5	150.5	152.17±3.79
	Isooctane	174.1	176.1	174.2	174.80±1.13
	Toluene	174	171.2	167.4	170.87±3.31
5	Aggressive Ethanol	142.3	141.9	137.3	140.50±2.78
	Ethanol	140.5	144.9	139.7	141.70±2.80
	Isooctane	173.1	173.8	172.1	173.00±0.85
	Toluene	166	166.9	166.6	166.50±0.46
10	Aggressive Ethanol	134.4	135.9	134.9	135.07±0.76
	Ethanol	130.8	136.8	137.7	135.10±3.75
	Isooctane	172.8	170.3	170.1	171.07±1.50
	Toluene	162.1	164.9	161.1	162.70±1.97
16	Aggressive Ethanol	130.3	133	124.6	129.30±4.29
	Ethanol	125.5	127.7	121.2	124.80±3.31
	Isooctane	167.5	169.1	166.7	167.77±1.22
	Toluene	161.6	164.8	159.8	162.07±2.53

## Appendix B2 Glass transition temperature

Table B2-1 Glass transition temperature of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Glass transition temperature (°C)		Average (°C)
		1	2	
0	Aggressive Ethanol	72.60	74.70	73.65±1.48
	Ethanol			
	Isooctane			
	Toluene			
2	Aggressive Ethanol	-5.20	-5.10	-5.15±0.07
	Ethanol	-3.10	-3.40	-3.25±0.21
	Isooctane	61.60	62.40	62.00±0.57
	Toluene	57.10	57.30	57.20±0.14
5	Aggressive Ethanol	-8.00	-10.30	-9.15±1.63
	Ethanol	-5.10	-6.50	-5.80±0.99
	Isooctane	52.90	53.10	53.00±0.14
	Toluene	49.60	49.00	49.30±0.42
10	Aggressive Ethanol	-11.20	-12.70	-11.95±1.06
	Ethanol	-11.80	-10.80	-11.30±0.71
	Isooctane	47.90	46.40	47.15±1.06
	Toluene	45.50	44.40	44.95±0.78
16	Aggressive Ethanol	-11.70	-14.70	-13.20±2.12
	Ethanol	-14.90	-12.20	-13.55±1.91
	Isooctane	30.60	32.70	31.65±1.48
	Toluene	31.70	30.50	31.10±0.85

**Table B2-2** Glass transition temperature of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Glass transition temperature (°C)		Average (°C)
		1	2	
0	Aggressive Ethanol	72.90	74.50	73.70±1.13
	Ethanol			
	Isooctane			
	Toluene			
2	Aggressive Ethanol	-5.80	-5.10	-5.45±0.49
	Ethanol	-4.00	-5.40	-4.70±0.99
	Isooctane	63.60	63.90	63.75±0.21
	Toluene	54.60	54.30	54.45±0.21
5	Aggressive Ethanol	-6.70	-7.60	-7.15±0.63
	Ethanol	-6.10	-7.90	-7.00±1.27
	Isooctane	48.10	48.60	48.35±0.35
	Toluene	46.20	46.50	46.35±0.21
10	Aggressive Ethanol	-10.90	-7.60	-9.25±2.33
	Ethanol	-6.60	-8.00	-7.30±0.99
	Isooctane	47.60	39.40	43.50±5.80
	Toluene	46.20	39.90	43.05±4.45
16	Aggressive Ethanol	-10.60	-9.00	-9.80±1.13
	Ethanol	-12.50	-13.90	-13.20±0.99
	Isooctane	31.30	33.80	32.55±1.77
	Toluene	34.50	31.10	32.80±2.40

**Table B2-3** Glass transition temperature of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Glass transition temperature (°C)		Average (°C)
		1	2	
0	Aggressive Ethanol	76.10	73.70	74.90±1.70
	Ethanol			
	Isooctane			
	Toluene			
2	Aggressive Ethanol	-1.40	-1.30	-1.35±0.07
	Ethanol	-5.70	-4.30	-5.00±0.99
	Isooctane	64.50	64.70	64.60±0.14
	Toluene	45.80	48.00	46.90±1.56
5	Aggressive Ethanol	-6.30	-5.90	-6.10±0.28
	Ethanol	-6.00	-5.20	-5.60±0.57
	Isooctane	53.50	53.90	53.70±0.28
	Toluene	45.30	44.90	45.10±0.28
10	Aggressive Ethanol	-9.30	-8.80	-9.05±0.35
	Ethanol	-5.60	-6.40	-6.00±0.57
	Isooctane	50.60	49.90	50.25±0.49
	Toluene	46.50	43.80	45.15±1.91
16	Aggressive Ethanol	-10.70	-9.60	-10.15±0.78
	Ethanol	-5.60	-6.50	-6.05±0.64
	Isooctane	35.70	37.20	36.45±1.06
	Toluene	36.30	32.60	34.45±2.62



APPENDIX C  
THE EXPERIMENTAL DATA OF MECHANICAL PROPERTIES

## Appendix C1 Tensile Strength

Table C1-1 Tensile strength of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	66.50	65.36	65.62	66.76	66.71	66.27±0.61
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	43.85	43.35	43.56	44.41	44.22	43.88±0.44
	Ethanol	57.35	57.64	56.83	57.39	56.96	57.23±0.33
	Isooctane	62.71	62.82	62.96	63.51	62.70	62.94±0.34
	Toluene	61.78	61.25	62.38	60.63	62.15	61.64±0.71
2	Aggressive Ethanol	40.49	39.50	40.15	39.87	39.81	39.96±0.37
	Ethanol	52.19	53.17	53.91	53.11	53.64	53.00±0.64
	Isooctane	59.61	58.83	60.47	57.41	57.97	58.86±1.23
	Toluene	58.21	59.00	58.38	58.25	58.11	58.39±0.36
3	Aggressive Ethanol	34.29	33.92	33.94	33.95	34.02	34.02±0.18
	Ethanol	37.07	37.58	36.01	38.38	36.45	37.10±0.93
	Isooctane	51.82	52.81	49.87	52.93	51.88	51.86±1.22
	Toluene	48.65	47.50	51.28	54.23	50.85	50.50±2.60
5	Aggressive Ethanol	28.41	27.60	28.23	27.42	28.04	27.94±0.42
	Ethanol	33.42	31.92	33.11	31.41	33.48	32.67±0.94
	Isooctane	48.55	49.65	49.87	47.48	47.17	48.55±1.22
	Toluene	49.57	48.18	47.66	48.47	47.43	48.26±0.84

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	26.18	26.80	26.64	25.86	25.63	26.22±0.50
	Ethanol	26.03	26.34	26.10	26.00	26.31	26.16±0.16
	Isooctane	46.97	44.26	46.61	44.46	44.30	45.32±1.35
	Toluene	43.11	43.66	43.31	43.70	44.05	43.57±0.37
10	Aggressive Ethanol	25.79	25.52	25.90	25.45	26.28	25.79±0.33
	Ethanol	25.81	25.74	25.97	26.22	26.65	26.08±0.36
	Isooctane	43.48	43.13	42.51	43.53	42.88	43.12±0.43
	Toluene	43.79	42.24	43.00	42.99	42.95	43.00±0.55
13	Aggressive Ethanol	26.57	26.92	24.76	25.24	25.00	25.70±0.98
	Ethanol	25.88	25.79	25.83	25.50	25.79	25.76±0.15
	Isooctane	41.50	42.03	41.44	41.94	42.54	41.89±0.44
	Toluene	41.07	40.86	41.96	41.64	40.46	41.20±0.60
16	Aggressive Ethanol	25.23	24.45	25.78	24.65	24.42	24.91±0.59
	Ethanol	24.59	23.86	24.04	24.29	24.29	24.26±0.30
	Isooctane	40.20	38.87	39.11	38.83	39.09	39.22±0.57
	Toluene	38.55	35.96	36.81	38.32	37.77	37.48±1.08

Table C1-2 Tensile strength of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	123.09	125.89	120.73	123.75	123.71	123.43±1.85
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	87.52	85.86	87.74	85.28	85.20	86.32±1.23
	Ethanol	87.35	87.60	86.33	86.21	87.78	87.05±0.73
	Isooctane	109.97	106.14	108.7	105.29	106.31	107.22±1.86
	Toluene	101.87	101.29	100.18	103.55	100.50	101.48±1.33
2	Aggressive Ethanol	80.23	76.18	82.47	82.75	75.14	79.35±3.52
	Ethanol	83.93	77.25	81.86	74.15	77.13	78.86±3.95
	Isooctane	100.43	98.5	99.50	99.43	102.99	100.17±1.71
	Toluene	93.58	93.81	95.76	96.15	93.63	94.59±1.26
3	Aggressive Ethanol	69.93	69.62	70.62	69.55	68.39	69.62±0.93
	Ethanol	75.27	72.65	72.87	74	75.35	74.03±1.28
	Isooctane	78.42	77.60	80.37	79.88	78.56	78.96±1.13
	Toluene	77.27	76.85	76.23	76.53	77.32	76.84±0.47
5	Aggressive Ethanol	61.25	60.38	60.33	61.32	61	60.86±0.48
	Ethanol	64.05	64.64	64.17	62.52	63.97	63.87±0.80
	Isooctane	77.09	77.46	77.06	77.57	76.88	77.21±0.29
	Toluene	74.96	75.92	74.92	75.06	74.45	75.06±0.53

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	53.50	56.93	55.71	54.53	54.16	54.97±1.36
	Ethanol	47.71	53.78	51.30	51.99	52.00	51.36±2.24
	Isooctane	76.12	76.98	76.3	77.46	75.36	76.44±0.81
	Toluene	72.35	75.23	74.25	74.74	73.47	74.01±1.12
10	Aggressive Ethanol	50.36	50.60	49.89	50.39	50.30	50.31±0.26
	Ethanol	50.54	52.05	51.50	52.64	50.98	51.54±0.83
	Isooctane	73.49	74.84	75.15	74.47	76.29	74.85±1.02
	Toluene	72.73	73.23	72.96	73.03	73.83	73.16±0.42
13	Aggressive Ethanol	49.80	48.34	48.43	49.81	48.96	49.07±0.71
	Ethanol	50.58	50.31	51.96	50.55	50.44	50.77±0.67
	Isooctane	73.82	71.93	72.42	72.55	73.31	72.81±0.75
	Toluene	71.82	73.59	73.43	70.53	73.52	72.58±1.36
16	Aggressive Ethanol	48.14	47.94	48.06	47.85	47.96	47.99±0.11
	Ethanol	51.44	50.58	49.22	51.79	50.70	50.75±0.99
	Isooctane	71.44	72.09	72.38	69.69	71.78	71.48±1.06
	Toluene	70.59	68.93	70.93	71.9	71.81	70.83±1.20

Table C1-3 Tensile strength of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	164.61	165.27	168.81	167.28	169.56	167.11±2.16
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	129.35	127.20	128.95	131.23	130.88	129.52±1.62
	Ethanol	132.51	133.26	133.12	133.79	136.27	133.79±1.68
	Isooctane	144.03	143.66	142.86	143.34	144.80	143.74±1.01
	Toluene	150.76	151.35	151.77	149.34	145.44	149.73±2.89
2	Aggressive Ethanol	118.04	119.00	118.86	122.08	115.17	118.63±2.47
	Ethanol	125.97	120.73	124.80	125.00	123.09	123.92±2.06
	Isooctane	140.13	132.86	149.84	131.47	146.36	140.13±9.33
	Toluene	141.45	137.43	140.92	142.39	145.00	141.44±3.16
3	Aggressive Ethanol	109.74	110.10	110.18	112.67	110.89	110.72
	Ethanol	112.36	114.35	110.55	109.62	111.95	111.77±1.81
	Isooctane	139.12	138.87	136.24	139.18	141.56	138.99±1.89
	Toluene	133.15	132.62	132.28	133.19	131.64	132.58±0.65
5	Aggressive Ethanol	91.74	89.38	87.17	92.50	92.14	90.59±2.26
	Ethanol	96.49	97.64	98.78	98.12	97.50	97.70±0.84
	Isooctane	136.00	130.24	128.77	125.93	135.01	131.19±4.25
	Toluene	120.89	132.23	119.88	126.75	126.84	125.32±5.03

Week	Chemical	Tensile Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	91.37	90.29	89.61	89.76	89.99	90.20±0.70
	Ethanol	92.96	93.06	89.62	88.76	94.03	91.69±2.33
	Isooctane	127.73	124.83	127.60	130.54	131.81	128.50±2.74
	Toluene	118.93	121.42	122.58	126.22	123.34	122.50±2.66
10	Aggressive Ethanol	88.05	87.74	87.74	86.94	89.73	88.04±1.03
	Ethanol	88.44	88.69	88.05	91.55	92.21	89.79±1.94
	Isooctane	127.60	127.04	127.46	128.49	128.64	127.85±0.62
	Toluene	118.31	115.65	118.44	117.07	117.72	117±1.14
13	Aggressive Ethanol	87.75	87.56	86.59	86.89	88.17	87.39±0.64
	Ethanol	89.22	88.29	90.11	91.77	89.71	89.82±1.28
	Isooctane	122.34	121.99	122.73	122.76	120.86	122.14±0.78
	Toluene	118.3	118.17	117.9	116.58	118.43	117.88±0.75
16	Aggressive Ethanol	83.38	87.37	83.89	80.89	87.92	85.69±2.93
	Ethanol	86.49	90.46	90.06	88.61	88.78	88.88±1.56
	Isooctane	119.75	119.56	119.09	120.63	120.56	119.92±0.66
	Toluene	111.9	112.81	112.2	111.04	112.54	112.10±0.68

## Appendix C2 Tensile Modulus

Table C2-1 Tensile Modulus of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	2229	2207	2215	2213	2192	2204±22
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	1484	1410	1448	1475	1505	1464±37
	Ethanol	1867	1908	1904	1824	1906	1882±37
	Isooctane	1995	1997	2002	1955	1974	1985±20
	Toluene	1949	1951	2000	1987	1924	1949±47
2	Aggressive Ethanol	1240	1194	1231	1236	1232	1227±19
	Ethanol	1689	1727	1698	1756	1727	1719±27
	Isooctane	1700	1858	1777	1737	1826	1780±64
	Toluene	1732	1791	1778	1777	1761	1768±22
3	Aggressive Ethanol	963	943	903	947	980	947±33
	Ethanol	1068	1137	1013	1103	1062	1077±47
	Isooctane	1699	1673	1571	1711	1648	1649±78
	Toluene	1496	1479	1560	1738	1565	1567±102
5	Aggressive Ethanol	361	325	315	329	295	325±24
	Ethanol	884	731	875	778	878	829±70
	Isooctane	1519	1493	1605	1591	1463	1534±62
	Toluene	1487	1493	1367	1471	1343	1432±71

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	178	192	200	208	195	195±13
	Ethanol	227	224	223	215	225	223±5
	Isooctane	1298	1156	1320	1182	1155	1222±80
	Toluene	1146	1126	1121	1177	1147	1144±22
10	Aggressive Ethanol	197	182	195	181	190	189±7
	Ethanol	187	195	186	189	196	191±5
	Isooctane	1150	1148	1094	1172	1088	1130±37
	Toluene	1106	1065	1063	1051	1090	1075±22
13	Aggressive Ethanol	175	183	182	197	184	184±8
	Ethanol	182	183	181	185	190	184±4
	Isooctane	1029	990	990	990	1022	1004±20
	Toluene	964	995	1063	964	994	996±40
16	Aggressive Ethanol	204	172	169	166	206	184±19
	Ethanol	182	196	182	184	182	185±6
	Isooctane	848	863	890	877	890	874±18
	Toluene	885	777	901	879	903	869±52

Table C2-2 Tensile modulus of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	3945	3943	3984	3908	3908	3937±28
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	2975	2960	2979	3019	2962	2979±24
	Ethanol	3012	2984	2998	2970	2932	2979±31
	Isooctane	3643	3702	3633	3655	3638	3654±28
	Toluene	3490	3491	3487	3559	3533	3512±32
2	Aggressive Ethanol	2250	2350	2340	2326	2318	2317±39
	Ethanol	2786	2767	2862	2886	2638	2788±97
	Isooctane	3373	3362	3340	3352	3379	3361±16
	Toluene	3119	3127	3197	3185	3298	3186±72
3	Aggressive Ethanol	2226	2250	2233	2207	2229	2229±18
	Ethanol	2457	2369	2371	2344	2268	2362±68
	Isooctane	2493	2492	2649	2603	2631	2573±76
	Toluene	2384	2461	2471	2488	2425	2446±42
5	Aggressive Ethanol	1928	1956	1951	1961	1926	1944±16
	Ethanol	2258	2247	2247	2147	2176	2215±50
	Isooctane	2488	2402	2485	2446	2472	2459±36
	Toluene	2426	2423	2410	2416	2406	2416±8

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	1760	1766	1761	1728	1628	1728±58
	Ethanol	1671	1879	1711	1623	1849	1746±112
	Isooctane	2306	2360	2392	2417	2472	2389±62
	Toluene	2307	2334	2308	2337	2393	2336±35
10	Aggressive Ethanol	1370	1333	1395	1309	1411	1364±42
	Ethanol	1452	1516	1522	1417	1493	1480±44
	Isooctane	2403	2273	2316	2322	2346	2332±48
	Toluene	2322	2286	2295	2319	2386	2322±39
13	Aggressive Ethanol	1367	1334	1348	1331	1327	1342±16
	Ethanol	1350	1335	1351	1472	1359	1374±56
	Isooctane	2305	2360	2392	2416	2471	2389±62
	Toluene	2307	2272	2303	2307	2307	2299±15
16	Aggressive Ethanol	1344	1340	1336	1302	1344	1333±18
	Ethanol	1363	1369	1349	1351	1362	1359±9
	Isooctane	2261	2184	2279	2205	2287	2243±46
	Toluene	2201	2140	2245	2245	2295	2225±58

Table C2-3 Tensile modulus of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	5622	5592	5757	5601	5560	5626±76
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	4246	4388	4347	4319	4424	4345±68
	Ethanol	4646	4632	4642	4598	4694	4642±40
	Isooctane	5007	5005	4890	5135	4991	5006±123
	Toluene	5067	5260	4897	5152	4951	5066±170
2	Aggressive Ethanol	3792	4094	4123	4001	3660	3934±201
	Ethanol	4253	3956	4072	4270	4247	4160±139
	Isooctane	4840	4785	4865	4723	4973	4837±108
	Toluene	4905	4907	4868	4877	4962	4904±42
3	Aggressive Ethanol	3715	3694	3764	3737	3718	3725±26
	Ethanol	3827	3876	3822	3870	3887	3856±30
	Isooctane	4823	4778	4880	4655	4756	4779±83
	Toluene	4735	4705	4697	4668	4706	4702±24
5	Aggressive Ethanol	3281	3101	3217	3300	3062	3192±106
	Ethanol	3446	3538	3400	3576	3516	3495±64
	Isooctane	4956	4694	4712	4522	4938	4764±182
	Toluene	4664	4555	4749	4270	4534	4555±181

Week	Chemical	Tensile Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	3029	3013	2982	2892	2924	2968±58
	Ethanol	3074	3231	3140	3090	3236	3154±77
	Isooctane	4306	4124	4323	4456	4259	4294±120
	Toluene	4113	4136	3961	3998	4146	4071±85
10	Aggressive Ethanol	2784	2855	2653	2616	2595	2701±113
	Ethanol	2864	2726	2941	2787	2861	2836±82
	Isooctane	4234	4308	4274	4166	4455	4287±96
	Toluene	3983	4048	3924	4118	4066	4028±75
13	Aggressive Ethanol	2506	2547	2476	2530	2580	2528±40
	Ethanol	2694	2624	2628	2668	2678	2659±31
	Isooctane	4185	4223	4192	4235	4141	4195±37
	Toluene	3902	3978	3925	3959	3823	3917±60
16	Aggressive Ethanol	2567	2452	2530	2532	2458	2508±51
	Ethanol	2528	2623	2649	2551	2621	2594±52
	Isooctane	3978	4146	4036	3987	4198	4069±98
	Toluene	3781	3810	3784	3832	3817	3805±22

## Appendix C3 Flexural Strength

Table C3-1 Flexural strength of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	99.05	100.83	101.02	100.70	99.53	100.23±0.88
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	50.61	51.16	51.39	52.49	50.89	51.31±0.72
	Ethanol	55.74	55.50	54.91	55.46	54.42	55.21±0.53
	Isooctane	70.01	76.87	76.49	76.90	76.33	75.32±2.98
	Toluene	68.01	68.88	69.18	70.11	69.53	69.14±0.78
2	Aggressive Ethanol	46.78	46.96	48.57	46.07	47.78	47.10±1.06
	Ethanol	45.89	49.97	49.13	46.85	47.96	47.98±1.14
	Isooctane	59.26	59.75	58.04	59.83	59.50	59.28±0.73
	Toluene	59.90	60.59	60.38	59.79	58.73	59.87±0.72
3	Aggressive Ethanol	31.16	31.31	31.53	31.08	31.49	31.31±0.20
	Ethanol	31.22	31.52	30.77	30.86	31.74	31.22±0.42
	Isooctane	58.42	58.65	57.82	56.45	58.95	58.06±0.99
	Toluene	56.07	59.73	57.75	56.56	57.03	57.43±1.43
5	Aggressive Ethanol	25.72	24.89	25.26	24.55	25.53	25.19±0.48
	Ethanol	30.58	30.52	30.04	29.40	28.41	29.99±1.18
	Isooctane	56.57	54.43	56.02	57.67	55.39	56.02±1.41
	Toluene	45.04	44.27	42.17	46.56	43.62	44.33±1.63

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	23.55	22.80	23.96	23.93	22.67	23.38±0.55
	Ethanol	27.18	27.98	27.72	27.15	26.83	27.37±0.47
	Isooctane	42.07	42.59	44.89	43.18	41.35	42.82±1.34
	Toluene	39.74	39.27	39.05	39.94	40.16	39.63±0.46
10	Aggressive Ethanol	22.58	22.19	22.94	23.42	22.49	22.72±0.47
	Ethanol	21.71	22.91	20.62	21.15	21.18	21.51±0.87
	Isooctane	37.39	36.05	36.97	37.28	35.69	36.68±0.76
	Toluene	34.73	35.43	34.31	35.20	34.00	34.73±0.69
13	Aggressive Ethanol	19.96	20.44	20.46	20.57	20.58	20.40±0.26
	Ethanol	21.34	20.99	21.05	20.99	21.31	21.14±0.17
	Isooctane	33.64	33.20	35.13	36.11	37.71	35.16±1.84
	Toluene	34.28	33.96	33.46	33.52	34.42	33.93±0.44
16	Aggressive Ethanol	19.62	20.73	20.01	20.16	21.10	20.33±0.59
	Ethanol	20.34	20.65	20.05	21.32	20.52	20.57±0.47
	Isooctane	34.96	33.42	34.26	35.68	34.58	34.58±0.84
	Toluene	33.71	33.67	33.68	33.86	33.55	33.70±0.11

Table C3-2 Flexural strength of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	149.78	148.77	154.20	150.60	149.12	150.49±2.19
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	124.74	128.32	126.75	121.88	130.29	126.40±3.25
	Ethanol	140.67	136.22	143.12	135.92	138.77	138.94±3.04
	Isooctane	150.33	145.38	142.88	149.19	149.84	147.53±3.25
	Toluene	145.93	141.36	139.74	142.84	145.94	143.16±2.76
2	Aggressive Ethanol	99.86	102.87	99.77	99.60	101.18	100.66±1.39
	Ethanol	100.12	103.99	102.86	103.83	104.75	103.11±1.80
	Isooctane	145.98	144.17	141.09	136.51	145.25	142.60±3.88
	Toluene	130.43	132.11	142.82	143.10	133.71	136.43±6.07
3	Aggressive Ethanol	97.73	97.24	96.52	95.37	94.86	96.34±1.22
	Ethanol	98.08	97.82	98.88	98.54	96.43	97.95±0.94
	Isooctane	139.82	140.32	138.00	144.63	144.12	141.38±2.87
	Toluene	124.26	124.81	122.73	126.57	124.90	124.65±1.38
5	Aggressive Ethanol	70.72	72.85	74.47	74.27	72.53	72.97±1.52
	Ethanol	78.35	80.29	77.87	82.78	79.82	79.82±1.94
	Isooctane	96.65	100.72	104.65	102.80	102.77	101.52±3.06
	Toluene	102.02	100.92	100.59	100.83	101.47	101.17±0.58

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	60.98	63.80	60.98	63.13	65.88	62.95±2.07
	Ethanol	66.63	68.77	67.79	68.05	65.90	67.43±1.15
	Isooctane	84.52	84.67	83.86	81.83	83.88	83.75±1.13
	Toluene	83.26	83.22	85.46	85.85	82.77	84.11±1.43
10	Aggressive Ethanol	63.56	62.76	63.12	60.85	62.25	62.51±1.04
	Ethanol	61.01	61.03	60.84	61.76	61.03	61.13±0.36
	Isooctane	85.33	83.54	84.97	84.70	79.17	83.54±2.54
	Toluene	82.74	86.99	82.60	86.11	81.68	84.03±2.36
13	Aggressive Ethanol	60.41	60.01	60.45	60.18	58.38	59.89±0.86
	Ethanol	62.72	63.58	59.16	63.07	60.00	61.71±1.99
	Isooctane	82.48	83.35	82.22	82.20	82.56	82.56±0.47
	Toluene	83.45	84.24	76.05	83.28	85.45	82.49±3.70
16	Aggressive Ethanol	58.80	58.25	58.07	58.03	59.50	58.53±0.62
	Ethanol	62.02	60.49	60.56	60.34	61.26	60.93±0.70
	Isooctane	79.60	78.52	78.22	76.74	80.62	78.74±1.47
	Toluene	74.55	73.77	72.22	74.76	73.87	73.83±1.00

**Table C3-3** Flexural strength of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	209.68	215.26	211.97	216.28	215.99	213.84±2.89
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	164.57	165.91	172.58	172.32	170.18	169.11±3.69
	Ethanol	179.36	177.97	177.23	178.25	180.15	178.71±1.15
	Isooctane	206.41	211.48	208.79	215.78	208.37	210.16±3.62
	Toluene	205.19	210.29	203.13	208.22	210.55	207.48±3.24
2	Aggressive Ethanol	142.09	142.66	144.16	141.80	140.00	142.14±1.50
	Ethanol	145.88	149.84	145.45	148.46	151.91	148.31±2.71
	Isooctane	200.48	184.60	194.46	196.52	188.14	192.84±6.41
	Toluene	176.84	179.53	175.53	180.79	178.23	178.20±2.07
3	Aggressive Ethanol	133.80	132.23	131.35	129.06	132.72	131.83±1.78
	Ethanol	141.37	140.69	141.06	140.18	140.35	140.73±0.49
	Isooctane	173.17	180.76	185.83	186.15	178.95	180.97±5.37
	Toluene	173.02	171.92	165.20	170.32	171.88	170.47±3.10
5	Aggressive Ethanol	115.78	115.13	115.66	115.44	115.19	115.44±0.28
	Ethanol	121.79	122.94	120.03	123.05	122.39	122.04±1.23
	Isooctane	169.31	167.24	165.85	164.27	168.15	166.96±1.97
	Toluene	158.48	155.79	156.97	156.26	154.93	156.48±1.34

Week	Chemical	Flexural Strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	107.77	111.97	110.31	109.50	109.83	109.88±1.51
	Ethanol	111.96	113.80	116.33	114.61	113.44	114.03±1.61
	Isooctane	159.44	160.68	162.84	161.25	157.83	160.41±1.89
	Toluene	147.22	153.05	151.85	152.62	150.28	151.01±2.37
10	Aggressive Ethanol	104.01	104.88	104.30	104.07	104.34	104.32±0.34
	Ethanol	103.66	105.60	107.71	102.70	105.66	105.07±1.95
	Isooctane	153.99	154.45	151.99	152.16	151.35	152.79±1.35
	Toluene	151.48	148.09	147.61	148.64	149.97	149.16±1.57
13	Aggressive Ethanol	104.61	103.46	103.39	104.21	103.18	103.77±0.61
	Ethanol	105.13	104.45	105.45	103.78	104.70	104.70±0.64
	Isooctane	142.62	146.14	144.66	148.74	141.36	144.71±2.91
	Toluene	139.58	136.94	137.74	139.83	139.71	138.76±1.33
16	Aggressive Ethanol	103.06	100.92	103.50	103.68	101.84	102.60±1.18
	Ethanol	103.43	104.00	105.14	107.48	103.34	104.68±1.72
	Isooctane	142.42	141.94	138.72	139.03	142.01	140.82±1.79
	Toluene	132.64	129.73	133.22	133.49	131.30	132.08±1.56



## Appendix C4 Flexural Modulus

Table C4-1 Flexural modulus of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	2544	2558	2601	2602	2586	2578±26
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	1032	961	958	959	991	980±32
	Ethanol	1154	1153	1154	1159	1158	1156±3
	Isooctane	2517	2502	2490	2470	2795	2555±135
	Toluene	2633	2677	2679	2632	2695	2663±29
2	Aggressive Ethanol	968	972	947	943	970	957±14
	Ethanol	1072	1031	1078	1036	1041	1052±21
	Isooctane	2506	2566	2461	2543	2453	2506±50
	Toluene	2504	2475	2523	2478	2534	2503±26
3	Aggressive Ethanol	651	635	655	650	649	648±9
	Ethanol	702	647	720	678	658	681±30
	Isooctane	2577	2502	2408	2490	2500	2495±60
	Toluene	2554	2410	2514	2382	2477	2467±71
5	Aggressive Ethanol	514	479	523	497	509	505±17
	Ethanol	643	634	626	629	611	629±12
	Isooctane	1238	1251	1207	1320	1240	1251±42
	Toluene	1159	1227	1154	1154	1103	1160±44

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	469	462	476	479	461	469±7
	Ethanol	520	543	522	496	502	516±18
	Isooctane	884	921	913	892	865	895±22
	Toluene	845	841	854	856	873	854±13
10	Aggressive Ethanol	440	414	444	430	422	430±13
	Ethanol	429	419	437	428	472	437±21
	Isooctane	814	853	830	814	814	825±17
	Toluene	785	764	785	764	775	775±10
13	Aggressive Ethanol	435	429	425	427	418	427±6
	Ethanol	421	435	421	447	434	432±11
	Isooctane	750	876	866	799	827	824±51
	Toluene	772	743	758	788	746	761±19
16	Aggressive Ethanol	415	424	417	410	409	415±6
	Ethanol	419	412	416	427	416	418±5
	Isooctane	767	776	809	793	821	793±22
	Toluene	740	761	753	760	773	757±12

Table C4-2 Flexural modulus of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	4068	4234	4419	4355	4213	4258±136
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	3390	3421	3492	3409	3339	3410±55
	Ethanol	3721	3603	3691	3610	3611	3647±55
	Isooctane	4319	4096	4154	4207	4205	4196±82
	Toluene	4213	4072	4121	4082	4027	4103±70
2	Aggressive Ethanol	2575	2609	2545	2507	2509	2549±44
	Ethanol	2609	2755	2680	2740	2742	2705±61
	Isooctane	4136	4055	4244	4064	4234	4146±90
	Toluene	3752	3708	4027	4251	3988	3945±221
3	Aggressive Ethanol	2605	2558	2451	2470	2429	2503±76
	Ethanol	2527	2543	2515	2543	2506	2527±16
	Isooctane	4012	3998	3965	4187	4260	4084±131
	Toluene	3606	3509	3521	3675	3662	3595±77
5	Aggressive Ethanol	1711	1671	1653	1699	1740	1695±34
	Ethanol	1881	1903	1831	1870	1870	1871±26
	Isooctane	2516	2630	2711	2737	2415	2602±135
	Toluene	2415	2594	2517	2571	2573	2534±72
7	Aggressive Ethanol	1544	1560	1541	1562	1618	1565±31
	Ethanol	1677	1674	1653	1663	1641	1661±15
	Isooctane	2330	2351	2300	2275	2358	2323±35

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
	Toluene	2232	2158	2280	2283	2198	2230±54
10	Aggressive Ethanol	1585	1591	1608	1489	1559	1567±47
	Ethanol	1599	1710	1595	1583	1758	1649±80
	Isooctane	2271	2321	2304	2289	2181	2273±54
	Toluene	2140	2367	2162	2122	2158	2190±100
13	Aggressive Ethanol	1606	1549	1555	1539	1565	1563±26
	Ethanol	1648	1653	1541	1677	1508	1605±76
	Isooctane	2222	2288	2262	2258	2315	2269±35
	Toluene	1939	2150	2202	2256	2263	2162±132
16	Aggressive Ethanol	1573	1573	1518	1542	1591	1559±29
	Ethanol	1585	1563	1561	1591	1584	1577±14
	Isooctane	2117	2068	2090	2129	2151	2111±33
	Toluene	1980	1996	1934	1983	1946	1968±26

Table C4-3 Flexural modulus of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	7001	6817	6919	6864	6924	6905±69
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	4634	4775	4764	4692	4678	4709±60
	Ethanol	4943	4854	4870	4953	4936	4911±45
	Isooctane	6341	6548	6519	6807	6594	6562±167
	Toluene	5981	6302	6205	6083	6131	6140±122
2	Aggressive Ethanol	3855	3843	3926	3878	3848	3870±34
	Ethanol	3959	4030	3975	4039	4059	4012±43
	Isooctane	5826	5796	5615	5553	6076	5773±205
	Toluene	5363	5272	5365	5264	5408	5334±63
3	Aggressive Ethanol	3618	3569	3520	3577	3625	3582±42
	Ethanol	3746	3799	3770	3744	3750	3762±23
	Isooctane	5777	5641	5813	5564	5628	5685±106
	Toluene	5165	5039	5240	5127	5193	5153±76
5	Aggressive Ethanol	3059	3060	3069	3033	3039	3052±15
	Ethanol	3245	3208	3155	3218	3150	3195±42
	Isooctane	4968	4933	4760	4789	4884	4867±90
	Toluene	4583	4594	4517	4506	4592	4558±43

Week	Chemical	Flexural Modulus (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	2977	3066	3001	3105	3079	3046±54
	Ethanol	3008	3095	3153	3168	3161	3117±67
	Isooctane	4722	4855	4845	4857	4849	4826±58
	Toluene	4448	4596	4509	4544	4592	4538±62
10	Aggressive Ethanol	2984	2950	2966	2946	2947	2959±16
	Ethanol	2917	3104	3048	3053	3029	3030±69
	Isooctane	4610	4626	4576	4634	4586	4606±25
	Toluene	4479	4403	4405	4440	4404	4426±33
13	Aggressive Ethanol	2887	2898	2939	2924	3047	2939±64
	Ethanol	2990	2922	2924	2963	2943	2948±29
	Isooctane	4322	4170	4286	4453	4514	4349±137
	Toluene	4148	4196	4172	4127	4197	4168±31
16	Aggressive Ethanol	2870	2855	2937	2912	2933	2901±37
	Ethanol	2888	2876	2885	2994	2926	2914±49
	Isooctane	4371	4405	4347	4256	4380	4352±57
	Toluene	4112	4118	4075	3944	4081	4066±71

## Appendix C5 Compressive Strength

Table C5-1 Compressive strength of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	43.24	43.53	47.18	42.88	42.34	43.83±1.92
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	32.73	30.54	27.09	28.55	28.88	29.56±2.16
	Ethanol	27.82	32.62	30.82	29.77	31.46	30.50±1.82
	Isooctane	41.31	41.42	40.49	41.38	42.07	41.33±0.56
	Toluene	42.14	39.89	41.12	40.34	42.53	41.20±1.13
2	Aggressive Ethanol	23.61	24.62	24.39	24.91	21.81	23.87±1.25
	Ethanol	24.87	24.67	25.88	25.63	24.67	25.14±0.57
	Isooctane	38.00	39.94	38.73	38.54	38.90	38.82±0.71
	Toluene	38.35	40.07	36.43	37.24	35.76	37.57±1.70
3	Aggressive Ethanol	21.13	21.48	21.05	20.59	20.62	20.97±0.38
	Ethanol	21.27	22.18	21.64	21.27	21.81	21.63±0.39
	Isooctane	35.01	36.06	36.68	34.99	35.26	35.60±0.74
	Toluene	33.20	36.06	35.32	34.10	37.03	35.14±1.53
5	Aggressive Ethanol	17.55	16.81	16.80	16.11	16.08	16.67±0.61
	Ethanol	19.93	19.84	19.40	20.08	19.21	19.69±0.37
	Isooctane	34.16	31.82	31.34	33.09	32.53	32.59±1.11
	Toluene	30.63	32.15	31.73	32.19	33.01	31.94±0.86

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	15.11	15.72	15.26	16.45	13.95	15.30±0.92
	Ethanol	20.44	18.58	19.50	19.80	18.86	19.44±0.74
	Isooctane	30.89	29.19	32.78	31.17	28.28	30.46±1.76
	Toluene	29.96	30.23	32.44	28.62	30.92	30.43±1.40
10	Aggressive Ethanol	13.48	14.00	15.90	13.84	13.62	14.17±0.99
	Ethanol	18.62	19.67	20.84	20.67	17.01	19.36±1.59
	Isooctane	28.72	26.12	29.94	25.88	27.98	27.73±1.73
	Toluene	28.26	28.40	28.61	28.85	26.65	28.15±0.87
13	Aggressive Ethanol	13.22	13.35	14.77	13.98	14.76	14.02±0.74
	Ethanol	18.44	19.82	19.72	17.91	19.29	19.04±0.83
	Isooctane	27.76	26.96	25.86	25.45	28.88	26.98±1.40
	Toluene	26.39	26.19	25.93	27.51	25.80	26.36±0.68
16	Aggressive Ethanol	12.98	13.42	13.57	14.03	14.47	13.69±0.57
	Ethanol	18.77	19.10	17.43	18.36	19.02	18.54±0.68
	Isooctane	26.70	26.24	26.36	25.95	26.23	26.30±0.27
	Toluene	26.26	24.40	26.61	25.85	25.65	25.75±0.84

Table C5-2 Compressive strength of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	70.51	70.17	63.41	67.91	78.42	70.08±5.45
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	49.16	52.25	47.99	47.66	44.56	48.32±2.78
	Ethanol	51.46	51.00	50.43	46.75	47.91	49.51±2.06
	Isooctane	66.58	67.09	66.33	65.09	64.44	65.91±1.10
	Toluene	63.79	59.63	61.59	65.16	62.13	62.46±2.12
2	Aggressive Ethanol	41.86	44.49	43.37	40.12	43.28	42.63±1.68
	Ethanol	35.87	42.69	39.76	51.79	40.44	42.11±5.94
	Isooctane	61.60	61.68	60.60	59.47	59.16	60.50±1.17
	Toluene	54.05	54.23	61.33	58.65	51.29	55.91±4.02
3	Aggressive Ethanol	36.16	39.25	34.99	34.66	31.56	35.32±2.78
	Ethanol	34.31	38.76	34.36	37.00	36.93	36.27±1.91
	Isooctane	55.43	53.13	54.62	58.54	50.51	54.45±2.96
	Toluene	54.76	56.13	49.76	47.57	53.85	52.41±3.60
5	Aggressive Ethanol	35.04	26.99	34.72	34.09	30.65	32.30±3.45
	Ethanol	35.06	34.37	34.98	34.54	35.26	34.84±0.37
	Isooctane	55.70	52.30	48.99	47.07	48.52	50.52±3.47
	Toluene	49.31	53.33	45.69	46.26	45.94	48.11±3.27

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	30.08	32.83	32.74	28.69	29.39	30.74±1.93
	Ethanol	29.87	32.69	29.76	35.79	30.44	31.71±2.57
	Isooctane	45.43	43.13	44.62	48.54	50.51	46.45±3.01
	Toluene	44.05	44.23	51.33	48.65	41.29	45.91±4.02
10	Aggressive Ethanol	26.96	27.49	28.93	27.43	27.13	27.59±0.78
	Ethanol	31.96	31.50	30.93	27.25	28.41	30.01±2.06
	Isooctane	45.70	42.30	42.99	41.07	42.52	42.92±1.71
	Toluene	43.79	39.63	41.59	46.59	42.13	42.75±2.61
13	Aggressive Ethanol	25.17	27.07	23.99	24.35	25.71	25.26±1.22
	Ethanol	29.39	29.51	29.81	25.12	30.96	28.96±2.23
	Isooctane	42.57	40.88	43.72	40.23	42.96	42.07±1.46
	Toluene	36.95	42.31	38.69	39.26	38.94	39.23±1.94
16	Aggressive Ethanol	24.37	24.02	23.17	22.98	23.68	23.64±0.58
	Ethanol	27.11	25.56	25.16	29.80	29.73	27.47±2.22
	Isooctane	42.09	40.61	41.87	41.13	42.56	41.65±0.78
	Toluene	36.79	36.63	38.59	36.16	39.13	37.46±1.31

Table C5-3 Compressive strength of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
0	Aggressive Ethanol	132.52	130.60	126.93	112.19	127.19	125.89±8.01
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	82.25	81.22	95.21	81.99	90.38	86.21±6.26
	Ethanol	94.35	84.46	97.31	89.59	88.75	90.89±5.02
	Isooctane	119.91	115.64	114.97	120.34	116.08	117.39±2.53
	Toluene	101.06	111.26	109.49	113.00	112.23	109.41±4.85
2	Aggressive Ethanol	78.99	78.75	71.57	71.51	87.53	77.67±6.62
	Ethanol	74.89	96.89	92.37	72.69	80.42	83.45±10.71
	Isooctane	102.15	111.86	105.38	100.19	109.62	105.84±4.91
	Toluene	91.03	92.93	91.56	89.64	92.52	91.54±1.30
3	Aggressive Ethanol	68.22	71.83	68.64	61.82	65.42	67.18±3.76
	Ethanol	72.07	73.23	72.25	74.11	68.22	71.98±2.25
	Isooctane	93.94	94.01	91.50	89.82	90.06	91.87±2.03
	Toluene	90.41	87.23	87.28	87.76	84.73	87.48±2.02
5	Aggressive Ethanol	66.93	66.16	60.52	63.27	64.15	64.21±2.54
	Ethanol	68.35	68.16	67.55	65.07	68.10	67.44±1.36
	Isooctane	90.65	84.74	89.68	85.83	80.69	86.32±4.02
	Toluene	85.85	75.49	78.79	82.18	85.24	81.51±4.39

Week	Chemical	Compressive strength (MPa)					Average (MPa)
		1	2	3	4	5	
7	Aggressive Ethanol	65.95	66.89	56.77	56.64	63.17	61.89±4.92
	Ethanol	55.99	59.91	58.46	65.50	63.32	60.64±3.80
	Isooctane	76.52	89.27	84.04	73.93	86.50	82.05±6.57
	Toluene	78.01	74.02	73.55	73.95	77.66	75.44±2.20
10	Aggressive Ethanol	50.26	58.98	51.41	58.05	48.14	52.78±4.85
	Ethanol	51.96	58.47	53.00	52.70	57.16	54.66±2.94
	Isooctane	84.23	77.06	77.36	80.57	81.49	80.14±3.00
	Toluene	65.59	67.81	68.84	70.64	67.97	68.17±1.83
13	Aggressive Ethanol	49.34	48.77	48.01	46.54	44.32	47.40±2.01
	Ethanol	47.44	51.72	52.37	46.92	54.71	50.63±3.35
	Isooctane	75.96	79.30	77.76	76.81	75.08	76.98±1.63
	Toluene	60.61	61.28	66.74	59.95	62.64	62.24±2.70
16	Aggressive Ethanol	47.84	44.89	45.61	43.68	44.66	45.34±1.56
	Ethanol	53.63	50.46	45.92	48.72	44.51	48.65±3.63
	Isooctane	74.32	80.11	71.32	70.01	76.42	74.44±4.04
	Toluene	62.92	59.56	58.74	57.34	62.14	60.14±2.34

## Appendix C6 Impact Strength

Table C6-1 Impact strength of PA6 immersed in chemicals of surrogate gasohol

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	8.86	9.54	6.61	9.39	7.59	8.40±1.26
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	49.57	55.91	52.27	49.12	55.44	52.46±3.17
	Ethanol	32.41	30.91	32.47	32.26	31.89	31.99±0.64
	Isooctane	18.36	17.78	19.17	18.03	18.44	18.36±0.53
	Toluene	20.07	20.07	21.17	19.64	20.27	20.24±0.57
2	Aggressive Ethanol	127.03	123.33	127.54	124.41	125.86	125.63±1.76
	Ethanol	117.63	121.99	100.03	124.40	119.29	116.67±9.65
	Isooctane	21.16	22.11	21.25	22.67	21.94	21.83±0.63
	Toluene	26.16	26.37	26.71	26.75	26.76	26.55±0.27
3	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	27.65	28.57	32.12	28.52	31.41	29.65±1.98
	Toluene	31.07	33.08	28.82	30.80	33.12	31.38±1.80
5	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	30.73	32.25	31.52	31.17	30.99	31.33±0.59
	Toluene	35.82	36.43	35.44	34.15	34.60	35.29±0.92

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	39.57	39.25	35.87	45.90	49.74	42.07±5.61
	Toluene	50.78	52.33	50.86	50.56	53.87	51.68±1.41
10	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	43.59	43.91	44.96	44.46	44.21	44.23±0.52
	Toluene	60.87	62.49	58.29	60.69	64.80	61.43±2.41
13	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	49.90	50.73	45.53	49.67	50.12	49.19±2.08
	Toluene	147.22	148.06	137.07	143.19	132.20	141.55±6.79
16	Aggressive Ethanol	-	-	-	-	-	-
	Ethanol	-	-	-	-	-	-
	Isooctane	78.82	77.64	79.79	84.36	75.57	79.24±3.27
	Toluene	-	-	-	-	-	-

Table C6-2 Impact strength of PA6/GF (15 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	10.70	10.80	10.83	10.74	11.77	10.97±0.45
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	19.35	19.85	19.83	19.09	18.48	19.32±0.57
	Ethanol	16.34	14.83	15.54	15.67	16.57	15.79±0.69
	Isooctane	11.80	12.02	11.66	12.53	12.43	12.09±0.38
	Toluene	13.21	13.11	13.18	13.08	13.29	13.17±0.09
2	Aggressive Ethanol	22.28	20.63	20.60	21.58	22.44	21.51±0.88
	Ethanol	17.22	19.93	17.42	17.28	18.94	18.16±1.22
	Isooctane	13.37	14.26	16.02	15.49	13.75	14.58±1.14
	Toluene	18.09	15.24	16.04	15.38	16.85	16.32±1.18
3	Aggressive Ethanol	27.55	27.40	27.13	26.25	27.61	27.19±0.56
	Ethanol	27.00	27.37	27.06	28.38	28.15	27.59±0.64
	Isooctane	16.62	17.15	16.60	16.02	15.95	16.47±0.50
	Toluene	20.33	20.69	19.81	18.29	19.09	19.47±1.02
5	Aggressive Ethanol	34.44	34.08	33.76	36.98	33.95	34.64±1.33
	Ethanol	32.76	31.58	29.98	33.92	32.52	32.15±1.47
	Isooctane	17.39	18.17	17.91	17.21	17.28	17.59±0.42
	Toluene	21.07	18.45	18.71	18.67	21.58	19.35±1.49

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	40.09	42.19	40.85	39.86	41.66	40.93±1.00
	Ethanol	42.73	39.44	42.09	41.53	38.87	40.93±1.69
	Isooctane	17.60	18.09	17.86	17.93	17.90	17.87±0.18
	Toluene	22.92	21.87	19.27	22.53	19.88	21.29±1.63
10	Aggressive Ethanol	47.43	47.72	51.78	48.23	47.64	48.56±1.83
	Ethanol	44.79	43.99	44.33	44.94	42.97	44.20±0.78
	Isooctane	18.39	17.89	19.13	19.56	18.95	18.78±0.65
	Toluene	22.86	23.33	22.01	23.46	24.43	23.22±0.88
13	Aggressive Ethanol	50.44	49.87	50.56	50.79	50.31	50.39±0.34
	Ethanol	46.72	47.97	48.47	48.30	48.25	47.94±0.71
	Isooctane	21.45	20.51	21.20	20.00	20.09	20.65±0.65
	Toluene	24.51	24.71	24.12	24.59	24.25	24.44±0.24
16	Aggressive Ethanol	55.22	54.84	56.24	54.38	54.84	55.11±0.70
	Ethanol	53.24	52.53	49.46	51.19	49.70	51.22±1.67
	Isooctane	24.42	25.10	24.81	24.94	24.87	24.83±0.25
	Toluene	26.41	26.26	26.23	26.83	25.12	26.17±0.64

Table C6-3 Impact strength of PA6/GF (30 wt%) composite immersed in chemicals of surrogate gasohol

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
0	Aggressive Ethanol	18.44	19.80	19.23	18.82	19.10	19.08±0.51
	Ethanol						
	Isooctane						
	Toluene						
1	Aggressive Ethanol	27.47	27.89	27.51	26.21	27.85	27.38±0.69
	Ethanol	26.05	26.25	27.66	25.95	27.40	26.66±0.80
	Isooctane	21.67	20.86	20.56	20.71	21.48	21.05±0.49
	Toluene	22.55	21.19	22.13	22.85	23.17	22.38±0.77
2	Aggressive Ethanol	30.24	29.86	29.07	30.60	29.32	29.82±0.63
	Ethanol	30.19	31.23	30.74	31.21	30.83	30.84±0.43
	Isooctane	22.20	22.45	23.45	24.78	23.63	23.30±1.03
	Toluene	24.25	24.53	24.77	25.21	24.75	24.70±0.35
3	Aggressive Ethanol	37.20	38.57	38.07	38.63	40.48	38.59±1.20
	Ethanol	31.56	34.83	31.87	34.90	36.51	33.93±2.14
	Isooctane	25.26	23.63	26.43	23.77	24.94	24.81±1.15
	Toluene	26.33	27.67	27.83	28.89	26.49	27.44±1.05
5	Aggressive Ethanol	44.04	44.38	42.37	41.50	38.98	42.26±2.18
	Ethanol	37.09	42.00	35.12	35.86	41.23	38.26±3.15
	Isooctane	25.40	25.24	24.85	26.08	26.39	25.59±0.63
	Toluene	27.73	28.19	29.83	28.98	30.52	29.05±1.15

Week	Chemical	Impact Strength (kJ/m <sup>2</sup> )					Average (kJ/m <sup>2</sup> )
		1	2	3	4	5	
7	Aggressive Ethanol	47.65	44.43	45.55	44.38	44.78	45.36±1.37
	Ethanol	39.71	37.82	37.66	40.16	40.65	39.20±1.37
	Isooctane	26.14	26.47	25.89	25.71	28.77	26.60±1.25
	Toluene	31.46	30.29	31.80	31.19	30.63	31.08±0.61
10	Aggressive Ethanol	49.27	46.30	47.64	45.37	49.18	47.55±1.73
	Ethanol	43.42	43.39	41.61	38.21	37.74	40.88±2.75
	Isooctane	30.26	25.94	26.21	28.85	27.22	27.70±1.83
	Toluene	34.57	33.24	31.47	32.60	34.78	33.33±1.38
13	Aggressive Ethanol	50.29	50.74	52.06	50.48	51.10	50.93±0.70
	Ethanol	43.36	43.58	43.22	46.25	40.93	43.47±1.89
	Isooctane	28.25	28.31	29.65	28.21	28.24	28.53±0.63
	Toluene	34.10	35.55	35.56	36.28	36.56	35.61±0.95
16	Aggressive Ethanol	52.12	51.91	53.11	51.90	50.69	51.95±0.86
	Ethanol	45.29	45.68	48.00	46.75	48.00	46.74±1.26
	Isooctane	33.23	30.74	34.30	34.99	35.85	33.82±1.97
	Toluene	37.47	39.93	38.01	39.56	38.61	1.07

APPENDIX D  
PRESENTATION

1. Siriporn Kaensri and Varun Taepaisitphongse. 2010. Influences of Chemicals in Surrogate Gasohol on Mechanical Properties of Glass Fiber Reinforced Nylon 6 Composites. Proceeding of PCT-1<sup>st</sup> Polymer Conference of Thailand: 438-442
2. Varun Taepaisitphongse and Siriporn Kaensri. 2011. Influences of Chemicals in Surrogate Gasohol on Mechanical and Thermal Properties of Glass Fiber Reinforced Nylon 6 Composites. Proceeding of 5<sup>th</sup> Srinakharinwirot Vichakarn: SWU5-1168

## VITA

Miss Siriporn Kaensri was born in Prachinburi, Thailand, on January 4<sup>th</sup>, 1986. She received her high school diploma in 2003 from Triamudomsuksanomklao Kabinburi School, Prachinburi. She received the Bachelor of Engineering Degree with a major in Chemical Engineering from the Faculty of Engineering, Burapha University, Chonburi, in 2007. She continued her study for a Master's Degree in Chemical Engineering at the Department of Chemical Engineering Faculty of Engineering, Chulalongkorn University, Bangkok, in 2008.



