

ในงานวิจัยนี้ มีการเตรียมตัวอย่างคอมโพสิตจากเซรามิกชนิดพีแชนด์ที่กับอีพอกซี และคอมโพสิตจากพีแชนด์ที่กับโคพอลิเมอร์ชื่อ พอลิไวนิลลิดีนฟลูออไรด์-ไตรฟลูออไรด์เอธิลีน ในคอมโพสิตชนิดแรก พีแชนด์ที่มีพื้นที่หน้าตัดสี่เหลี่ยมล้อมรอบด้วยอีพอกซี ความต่อเนื่องของแต่ละเฟสในคอมโพสิตจึงเป็นแบบ 1-3 ตัวอย่างที่ใช้ในงานวิจัยแบ่งตามสัดส่วนโดยปริมาตรของพีแชนด์ที่ได้ 2 กลุ่ม คือ 0.4 และ 0.6 คอมโพสิตชนิดที่สองมีลักษณะของพีแชนด์ที่เป็นก้อนหรือเม็ดกระจายอยู่ในเมทริกซ์ของโคพอลิเมอร์ ความต่อเนื่องจึงเป็นแบบ 0-3 สัดส่วนโดยปริมาตรของพีแชนด์ที่เท่ากับ 0.3

นำคอมโพสิตพีแชนด์/อีพอกซี หนา 0.45 มม. ที่มีขั้วไฟฟ้ากาวเงินมาผ่านการโหลิงด้วยสนามไฟฟ้า 10 กิโลโวลต์ต่อมิลลิเมตร เพื่อให้พีแชนด์ที่แสดงสมบัติไพโซโซเล็กตริก จากนั้นวัดค่าคงที่ไพโซโซเล็กตริก ความเครียด (d) ด้วยระบบอินเทอร์เฟอโรมิเตอร์แบบไมเคิลสัน ซึ่งจำเป็นต้องชดเชยค่าความถี่ของแสงเนื่องจากระบบนี้อาศัยลำแสงเลเซอร์ที่สะท้อนกลับจากขั้วไฟฟ้าบนผิวตัวอย่าง สำหรับคอมโพสิตพีแชนด์/โคพอลิเมอร์ ความหนา 30 ไมโครเมตร ขั้วไฟฟ้ากาวเงินหลุดลงเนื่องจากมีปริมาณเมทริกซ์ค่อนข้างมากเมื่อเทียบกับเซรามิก จึงใช้วิธีทางเรโซแนนซ์แทนวิธีอินเทอร์เฟอโรมิเตอร์ จากการทดลองได้ค่าคงที่ไพโซโซเล็กตริกเฉลี่ยของคอมโพสิตพีแชนด์/อีพอกซี และ พีแชนด์/โคพอลิเมอร์เท่ากับ $(190 \pm 10) \times 10^{-12}$ และ $(13 \pm 2) \times 10^{-12}$ เมตรต่อโวลต์ ตามลำดับ ค่าแรกสอดคล้องกับค่าที่มีการรายงานทางทฤษฎี และมีค่าประมาณครึ่งหนึ่งของค่าของพีแชนด์ที่ทางการค้า ค่าหลังมีความคลาดเคลื่อนมากเป็นเพราะอาศัยสมการของวิธีเรโซแนนซ์ซึ่งขึ้นกับตัวแปรหลายตัว อย่างไรก็ตามผลการวัดไปกันได้กับกระบวนการโหลิงที่ใช้ซึ่งได้โพลในทิศทางเดียวกันทั้งพีแชนด์ (เฟสที่มีค่าคงที่ไพโซโซเล็กตริกเป็นบวก) และโคพอลิเมอร์ (เฟสที่มีค่าคงที่ไพโซโซเล็กตริกเป็นลบ) ทำให้การตอบสนองไพโซโซเล็กตริกถูกลดทอน ค่าคงที่ไพโซโซเล็กตริกจึงต่ำกว่าค่าของคอมโพสิตพีแชนด์/อีพอกซี

มีการเปลี่ยนแปลงอุณหภูมิของคอมโพสิตเพื่อวัดประจุโพลาริซที่เพิ่มขึ้นและนำไปคำนวณค่าคงที่ไพโซโซเล็กตริก พบว่าค่าคงที่เพิ่มขึ้นตามปริมาณพีแชนด์ในคอมโพสิตพีแชนด์/อีพอกซี และมีค่าสูงสุดเท่ากับ 54×10^6 คูลอมบ์ต่อตารางเมตร . องค์ศาเซลเซียส ค่าคงที่ค่อนข้างต่ำผิดปกติสำหรับคอมโพสิตพีแชนด์/โคพอลิเมอร์ คือเท่ากับ 0.74×10^6 คูลอมบ์ต่อตารางเมตร . องค์ศาเซลเซียส พบว่าเป็นเพราะการโหลิงไม่สมบูรณ์ของพีแชนด์ จากนั้นมีการทำให้เกิดคลื่นความร้อนเดินทางผ่านเนื้อคอมโพสิตไปยังหัววัดทางความร้อนเพื่อหาค่าสภาพการแพร่ทางความร้อน ได้ค่าสภาพการแพร่เฉลี่ยของคอมโพสิตพีแชนด์/อีพอกซีเท่ากับ $(2.15 \pm 0.05) \times 10^{-7}$ ตารางเมตรต่อวินาที ซึ่งประมาณครึ่งหนึ่งของค่าของพีแชนด์ที่ทางการค้า ค่าสภาพการแพร่ความร้อนของ พีแชนด์/โคพอลิเมอร์เท่ากับ 2.0×10^{-7} ตารางเมตรต่อวินาที ไม่สามารถทำการทดลองซ้ำได้เนื่องจากคอมโพสิตมีการฉีกขาดระหว่างโหลิง จากการหาค่าคงที่ไดอิเล็กตริกด้วยวิธีวัดความจุไฟฟ้าพบว่าเมื่อปริมาณพีแชนด์ที่ลดลง คอมโพสิตพีแชนด์/อีพอกซีมีค่าคงที่ไดอิเล็กตริกลดลงอย่างมาก ในขณะที่ค่าคงที่ไพโซโซเล็กตริกความเค้น (g) ที่คำนวณได้มีค่าสูงขึ้น บ่งบอกถึงความสามารถในการตัดโค้งคอมโพสิตได้ ตลอดจนการมีค่าคงที่ไพโซโซ-ไพโรโซเล็กตริกสูง แสดงว่าคอมโพสิตเหมาะสมที่จะนำมาทำเป็นทรานสดิวเซอร์ไพโซโซเล็กตริกหรือหัววัดไพโรโซเล็กตริก ข้อควรคำนึงในการใช้งานคือการถ่ายเทความร้อนของคอมโพสิตตลอดจนสิ่งประดิษฐ์ที่มีคอมโพสิตนี้เป็นส่วนประกอบ

In the present work the composites of PZT/epoxy and PZT/copolymer of polyvinylidene trifluoroethylene were prepared. The first consisted of the PZT bars surrounded by the epoxy; the connectivity of each phase in the composite was 1-3. The samples used were divided into 2 groups according to the volume fraction of PZT, i.e., 0.4 and 0.6. The second consisted of the PZT particles dispersed in the copolymer matrix; the connectivity is 0-3 and the volume fraction of PZT was 0.3.

In order that the composite was piezoelectric 0.45 mm PZT/epoxy with silver electrode was poled at 10 kV/mm. In the piezoelectric strain constant (d) measurements using a Michelson interferometer system, the electrode was polished until it was reflective. This was because the system used a laser beam reflected from the electrode on the top of the sample surface. For the 30 μm PZT/copolymer sample, the silver electrode was easily rubbed off because the matrix content was relatively high compared to that of the ceramic. A resonance method was then used instead of the interferometer. The average piezoelectric constants were $(190 \pm 10) \times 10^{-12}$ and $(13 \pm 2) \times 10^{-12}$ m/V for the PZT/epoxy and PZT/copolymer composites, respectively. The first corresponded with the theoretical values previously reported and was about half of the value of commercial PZT. The latter was erroneous owing to the many parameters involved in the resonance equation. However, the results obtained were possible for the poling process used in which the poling direction was the same for both PZT (positive piezoelectric constant) and copolymer (negative piezoelectric constant). The resultant piezoelectric response was reduced, consequently, the piezoelectric constant was smaller than that of PZT/epoxy.

The composite was subjected to a temperature change in order to measure the polarized charges for a calculation of the pyroelectric constant. Values of the constant increased with the content of PZT in PZT/epoxy composite and the maximum value of 54×10^{-6} C/m².s was obtained. A value for the PZT/copolymer composite was unusually low, i.e., 0.74×10^{-6} C/m².s. This was found to be because of the incomplete poling of ceramic. In order to measure the thermal diffusivity, thermal waves were generated and passed through the composite to a thermal detector. The thermal diffusivity of PZT/epoxy was averaged $(2.15 \pm 0.05) \times 10^{-7}$ m²/s, which was about half of the value of commercial PZT. This value for the PZT/copolymer was 2.0×10^{-8} m²/s. Experiments could not be repeated because of the damage of the composite during the poling. From the dielectric constant measurement using the capacitance method, it was found that when the ceramic content was decreased, the constant of the PZT/epoxy composite was considerably decreased while the calculated piezoelectric stress constant (g) was increased. This indicated that the composite was flexible. Together with the relatively high values of the piezo-pyroelectric constants, the composite was suitable for making the piezoelectric transducer or pyroelectric detector. These applications need to take into account the heat transfer of the composite and the devices consisting of the composite.