

### บทคัดย่อ

งานวิจัยนี้สนใจเตรียมยางธรรมชาติดัดแปรโดยการกร้าฟอะไครลามิโด ซัลโฟนิคแอซิด ลงบนโครงสร้างของยางธรรมชาติ เพื่อประยุกต์ใช้เป็นแผ่นจับโลหะหนักในสารละลาย ศึกษาประสิทธิภาพในการจับโลหะหนักด้วยเทคนิค FAAS โดยศึกษาผลของเวลา อุณหภูมิ ความเป็นกรด-ด่าง ปริมาณความเข้มข้นของโลหะหนักในสารละลาย และการนำกลับมาใช้ซ้ำ จากผลการทดลองพบว่าเวลาที่เกิดสมดุลของการแลกเปลี่ยนไอออนของโลหะหนักกับยางธรรมชาติ และยางธรรมชาติดัดแปร คือ 1 – 2 ชั่วโมง ค่าความเป็นกรด-ด่าง และอุณหภูมิมีผลต่อความสามารถในการจับเพียงเล็กน้อย โดยสภาวะในการจับที่ดีที่สุดของ  $Pb^{2+}$ ,  $Cd^{2+}$  และ  $Cu^{2+}$  คือ  $30 - 40^{\circ}C$  ที่ความเป็นกรด-ด่าง 4 – 5 ไอโซเทอมของการจับของ  $Pb^{2+}$  and  $Cd^{2+}$  สอดคล้องกับไอโซเทอมของ Freundlich ซึ่งแสดงถึงการเกิดการจับแบบหลายชั้น ในขณะที่ไอโซเทอมของการจับของ  $Cu^{2+}$  สอดคล้องกับไอโซเทอมของ Langmuir ซึ่งแสดงถึงการเกิดการจับแบบชั้นเดียว อย่างไรก็ตามผลที่ได้จากทั้ง 2 ไอโซเทอม ให้ผลไปในทิศทางเดียวกัน และยางธรรมชาติดัดแปรมีการแลกเปลี่ยนไอออนสูงสุดกับ  $Pb^{2+}$ ,  $Cd^{2+}$  และ  $Cu^{2+}$  คือ 272.7, 267.2 และ 89.7 mg/g นอกจากนี้ยังได้ศึกษาการแลกเปลี่ยนไอออนของยางธรรมชาติกร้าฟโคพอลิเมอร์กับไอออนของโลหะหนักในน้ำเสียจากโรงงานอุตสาหกรรม โดยสนใจศึกษาถึงประสิทธิภาพและการนำกลับมาใช้ซ้ำ พบว่าการชะออกของไอออนของโลหะหนักที่เตรียมจากสารละลายมาตรฐานออกจากยางธรรมชาติดัดแปรโดยใช้ 4M ของสารละลายกรดไนตริกสามารถชะ  $Pb^{2+}$ ,  $Cd^{2+}$  และ  $Cu^{2+}$  ออกได้มากกว่า 99.5% ในขณะที่สามารถชะ  $Pb^{2+}$ ,  $Cd^{2+}$  และ  $Cu^{2+}$  ที่ถูกจับจากน้ำเสียออกจากยางธรรมชาติดัดแปรได้เพียง 98 – 100%, 97 – 100% และ 95 – 100% ตามลำดับขึ้นกับคุณภาพของน้ำ

## ABSTRACT

This work focuses on the preparation of modified natural rubber, by placing the sulfonic acid functional group on the main chain, with the aim to remove heavy metals from aqueous solution. The adsorption capacity of adsorbents was investigated by FAAS technique. To achieve the optimum adsorption conditions, time, temperatures, pH of adsorption, concentration of metal ion in aqueous solutions and regeneration were studied. The adsorption equilibrium time of these heavy metals on natural rubber and modified natural rubber were 1-2 hours. pH and temperature have only marginal effect on the adsorption capacity. The optimum conditions for adsorption of  $\text{Pb}^{2+}$ ,  $\text{Cd}^{2+}$ , and  $\text{Cu}^{2+}$  using the grafted NR are in the range of 30 – 40°C at pH 4 – 5. The isotherms of adsorption of  $\text{Pb}^{2+}$  and  $\text{Cd}^{2+}$  were fitted to the Freundlich isotherm model, while  $\text{Cu}^{2+}$  was fitted to the Langmuir isotherm. However, the results from these two isotherms resulted in a similar behavior. The maximum adsorption capacity of  $\text{Pb}^{2+}$ ,  $\text{Cd}^{2+}$  and  $\text{Cu}^{2+}$  were 272.7, 267.2 and 89.7 mg/g modified rubber, respectively. Moreover, the modified natural rubber was used for the removal of  $\text{Pb}^{2+}$ ,  $\text{Cd}^{2+}$  and  $\text{Cu}^{2+}$  ions of real samples of industries effluents where the efficiency and regeneration were also investigated. The desorption efficiencies of all metal ions adsorbed from standard solution using 4 M  $\text{HNO}_3$  solution were higher than 99.5% while the desorption efficiency of  $\text{Pb}^{2+}$ ,  $\text{Cd}^{2+}$  and  $\text{Cu}^{2+}$  adsorbed from waste water were 98 – 100%, 97 – 100% and 95 – 100%, respectively, depending on the water quality.