

Rungtiwa Chidthong 2007: Theoretical Investigation on Structural and Electronic Properties of Fluorene-Pyridine Copolymer. Doctor of Philosophy (Chemistry), Major Field: Chemistry, Department of Chemistry. Thesis Advisor: Associate Professor Supa Hannongbua, Dr.rer.nat. 176 pages.

The structural and electronic properties of the fluorene-pyridine copolymer, Poly[2,7-(9,9-diethylfluorene)-co-*alt*-2,5-pyridine] (PEFPy) and Copol(2,5-pyridine-*alt*-fluorene) (PFPy) were investigated by means of quantum chemical calculations. Geometry optimizations of these oligomers were performed for the ground state and the lowest excited state. HOMO-LUMO energy gaps, vertical excitation energies, absorption wavelengths and fluorescence energies are extrapolated to infinite chain length making use of their good linearity with respect to $1/n$. It was found that fluorene-pyridine copolymers are non-planar in their ground state whereas a more pronounced trend toward planarity are observed in the S_1 state. Additionally, the quinoid-like structures are found in their lowest excited state. HOMO-LUMO energy gap calculated at B3LYP/6-31G* level is suitable for estimate the energy gap of PEFPy (3.14 eV). Furthermore, the vertical excitation energies as obtained from ZINDO/S and TDDFT give good agreement with experimental data. Vertical excitation energies of Copol(2,5-pyridine-*alt*-fluorene) (PFPy) as calculated by TD-B3LYP/SVP and TD-B3LYP/SVP+ are 2.64 and 2.66 eV, respectively, which are in good agreement with experimental results. Fluorescence energies and radiative lifetimes are calculated as well. The $S_1 \leftarrow S_0$ electronic excitation is characterized as a HOMO to LUMO transition and dominated in terms of oscillator strength. The obtained results indicate that the fluorescence energy and radiative lifetime of (FPy)_n are 2.16 eV and 0.38 ns, respectively. The decrease of fluorescence energy and radiative lifetime with the increase in the chain length is discussed.

Rungtiwa Chidthong
Student's signature

Supa Hannongbua
Thesis Advisor's signature

08 / 02 / 07