

วิทยานิพนธ์นี้ได้ทำการเตรียมผลึกพหุพันธ์ของสารกึ่งตัวนำ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.25$) ได้จากปฏิกิริยาการเกิดเป็นสารละลายของแข็ง จากสารตั้งต้นที่เป็นผลึกของสารประกอบ CuO , Al_2O_3 และ $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ ที่มีความบริสุทธิ์ โดยเริ่มต้นจากการบดสารตั้งต้นให้ละเอียดและคลุกเคล้ากันดี จากนั้นจึงนำมาขึ้นรูปโดยการอัดให้เป็นเม็ดด้วยเครื่องไฮโดรลิคความดันสูงที่อุณหภูมิห้อง ผลึกที่อัดเป็นเม็ดแล้วจะเอาไปเผาในอากาศความดันปกติที่อุณหภูมิ 1,100 องศาเซลเซียส เป็นเวลา 24 ชั่วโมง ส่วนฟิล์มหนาของ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.25$) ได้จากการเคลือบสารตั้งต้นที่เป็นผลึกผงของ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ลงบนกระจกสไลด์ โดยวิธีพิมพ์สกรีน โดยที่ผลึกผงจะละลายในเอทิลแอลกอฮอล์ แล้วจากนั้นจึงพิมพ์สกรีนลงบนกระจกสไลด์ที่อุณหภูมิห้อง แอนนัลในอากาศที่อุณหภูมิ 100 องศาเซลเซียส เป็นเวลา 30 นาที จะช่วยทำให้เนื้อฟิล์มแน่นขึ้น ส่วนฟิล์มบางของ CuAlO_2 เตรียมได้จากการระเหยสารด้วยความร้อนในระบบสุญญากาศ เคลือบบนกระจกสไลด์ที่ความดัน 35×10^{-5} มิลลิบาร์ โดยใช้ผลึกผง CuAlO_2 เป็นสารตั้งต้น จากนั้นจึงนำฟิล์มบางที่ได้ไปแอนนัลในอากาศความดันปกติและในบรรยากาศของแก๊สไนโตรเจนบริสุทธิ์ที่อุณหภูมิ 100-500 องศาเซลเซียส เป็นเวลา 1 ชั่วโมง ได้ทำการตรวจสอบโครงสร้างผลึกของผลึกพหุพันธ์และฟิล์มหนา $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ฟิล์มบาง CuAlO_2 ที่เตรียมได้โดยวิธีการเลี้ยวเบนรังสีเอกซ์ ส่วนภาพถ่ายของผิวหน้าผลึกของสารตัวอย่างทั้งสามแบบได้จากการบันทึกด้วยกล้องจุลทรรศน์อิเล็กตรอนแบบส่องกราด ช่องว่างแถบพลังงานของฟิล์มบาง CuAlO_2 คำนวณได้จากสัมประสิทธิ์การส่งผ่านแสง ได้ทำการวัดสภาพต้านทานไฟฟ้าของผลึกพหุพันธ์ $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ และความต้านทานแผ่น $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ของฟิล์มหนา และฟิล์มบาง CuAlO_2 นี้ค่าพลังงานกระตุ้นสามารถคำนวณได้โดยการวัดความต้านทานไฟฟ้าที่อุณหภูมิต่างๆ จากค่าพลังงานกระตุ้นเหล่านี้สามารถระบุได้ว่าชนิดการนำไฟฟ้าแบบพีของผลึกพหุพันธ์และฟิล์มหนา $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ฟิล์มบาง CuAlO_2 มีสาเหตุมาจาก แวเลนซ์ของอะตอมโลหะและอะตอมออกซิเจนส่วนเกินที่อยู่ในโครงผลึก รวมทั้งได้มีการศึกษาสมบัติเชิงไฟฟ้า-ความร้อนด้วยโดยการวัดสัมประสิทธิ์ซีเบกที่อุณหภูมิต่างๆด้วย

In this thesis, polycrystalline of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.25$) were prepared by a solid state reaction method. The mixture of high purity of CuO , Al_2O_3 and $\text{Mg}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ powder was ground and then pressed by using uniaxial pressure. The obtained pellets were sintered in air at 1100°C for 24 h. Thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ ($0 \leq x \leq 0.25$) were deposited on slide glass substrate by screen printing method and using $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ phase in powder form as a precursor. The powder were dispersed in ethylene glycol and immediately depositing the screen on the glass substrate. In order to obtain the higher dense material, the as-deposited thick films were annealed in air at 100°C for 30 min. CuAlO_2 thin film were prepared by thermal evaporation method using single phase of CuAlO_2 obtained by solid state reaction method. The films were deposited on slide glass substrate in vacuum of 3.5×10^{-5} mbar. The as-deposited thin films were annealed in air and N_2 atmosphere during $100\text{--}500^\circ\text{C}$ for 1 h. The crystal structure of polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$, thin films of CuAlO_2 was checked by X-ray diffraction method. Surface morphology of the three kinds of samples was observed by scanning electron microscope (SEM) the energy gap value of CuAlO_2 thin films was determined from the optical transmission spectra. Electrical resistivity and sheet resistance were performed on the polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ and on thin films of CuAlO_2 respectively. The activation energy value of the three kind of samples were estimated by the resistance measurements as a function of temperature. From the activation energy values, the origin p-type conduction in polycrystalline and thick films of $\text{CuAl}_{1-x}\text{Mg}_x\text{O}_2$ and in thin films of CuAlO_2 was attributed to metal deficit and excess oxygen atoms within the crystallite sites of the material. The variation of Seebeck coefficient as a function of temperature was also investigated.