

172599

จักรพงษ์ แสนชัย : การกำจัดตะกั่วและแคดเมียมจากน้ำเสียสังเคราะห์โดยใช้ถ่านกระดูก
 กระตุ้นโดยซิงค์คลอไรด์. (REMOVAL OF LEAD AND CADMIUM FROM
 SYNTHETIC WASTEWATR BY USING BONE CHARCOAL ACTIVATED BY
 ZINC CHLORIDE) อ.ที่ปรึกษา : รศ.อรทัย ขวาลภาฤทธิ์, อ.ที่ปรึกษาร่วม : รศ.ดร.
 ธารพงษ์ วิทิตสานต์, 130 หน้า. ISBN 974-17-3897-8.

งานวิจัยนี้ทำการศึกษาประสิทธิภาพของถ่านกระดูกกระตุ้นโดยซิงค์คลอไรด์เพื่อกำจัด
 โลหะหนัก 2 ชนิดจากน้ำเสียสังเคราะห์ ได้แก่ ตะกั่ว และแคดเมียม โดยศึกษาลักษณะพื้นผิว และ
 โครงสร้างของถ่านกระดูก ซึ่งถูกกระตุ้นโดยซิงค์คลอไรด์ต่อกระดูกบดที่อัตรา ส่วนเท่ากับ 1:1,
 1.5:1 และ 2:1 เพื่อศึกษาสัดส่วนที่ดีที่สุด และจะถูกเลือกเป็นตัวแทนในการศึกษาประสิทธิภาพการ
 กำจัดแบบแบดจ์ต่อไป จากผลการวิเคราะห์พบว่าถ่านกระดูกซึ่งถูกกระตุ้นด้วยสัดส่วน 1:1 ให้ค่า
 พื้นผิว ปริมาตรจำเพาะของโพรง และปริมาณผลึกอะพาไทต์ มากที่สุดโดยชนิดของผลึกส่วนใหญ่
 ที่พบภายหลังการกระตุ้นมีดังนี้ $Ca_{10}(PO_4)_6(Cl)_2$, $CaZn_2(PO_4)_2 \cdot 2H_2O$ และ $Ca_{10}Zn_x(PO_4)_6(OH)_2$
 และชนิดผลึกส่วนใหญ่ที่พบภายหลังการกำจัดตะกั่วคือ $Pb_{10}(PO_4)_6(Cl)_2$ สำหรับภายหลังกำจัด
 แคดเมียมพบว่าชนิดผลึกไม่มีการเปลี่ยนแปลง จึงสรุปได้ว่ากลไกการกำจัดตะกั่วในน้ำเสีย
 สังเคราะห์ คือ การละลายและการตกตะกอน และกลไกการกำจัดแคดเมียม คือการดูดซับผิว

จากการศึกษาแบบแบดจ์ พบว่าถ่านกระดูกสามารถกำจัดตะกั่วได้ดีกว่าแคดเมียมมาก
 สำหรับการทดสอบกับน้ำเสียสังเคราะห์ตะกั่ว 50 มก./ล. และน้ำเสียสังเคราะห์แคดเมียม 10 มก./ล.
 พบว่าพีเอชที่เหมาะสมคือ 4 และ 7 ตามลำดับ ซึ่งจากผลการทดลองสามารถสรุปได้ว่า ความ
 สามารถในการกำจัดตะกั่วโดยกลไกการละลาย และการตกตะกอน ของถ่านกระดูก มากที่สุดถึง
 1,002 มก.ตะกั่ว/ก.ถ่านกระดูก หรือ ร้อยละ 68.38 และความสามารถในการกำจัดแคดเมียม โดย
 กลไกการดูดซับผิวของถ่านกระดูก มากที่สุดถึง 22.06 มก.แคดเมียม/ก.ถ่านกระดูก หรือร้อยละ
 24.70

ภาควิชา วิศวกรรมสิ่งแวดล้อม
 สาขาวิชา วิศวกรรมสิ่งแวดล้อม
 ปีการศึกษา 2548

ลายมือชื่อนิสิต จักรพงษ์ แสนชัย
 ลายมือชื่ออาจารย์ที่ปรึกษา อรทัย ขวาลภาฤทธิ์
 ลายมือชื่ออาจารย์ที่ปรึกษาร่วม ธารพงษ์ วิทิตสานต์

172599

4670252021 : MAJOR ENVIRONMENTAL ENGINEERING

KEYWORD : BONE CHARCOAL / APATITE / ADSORPTION / LEAD / CADMIUM

JAKKAPHONG SANCHAI : REMOVAL OF LEAD AND CADMIUM FROM SYNTHETIC WASTEWATER BY USING BONE CHARCOAL ACTIVATED BY ZINC CHLORIDE. THESIS ADVISOR : ASSC. PROF. ORATHAI CHAVALPARIT, THESIS COADVISOR : ASSC. PROF. THARAPONG VITIDSANT, Ph.D., 130 pp. ISBN 974-17-3897-8.

This research studied the removal efficiency of lead and cadmium from synthetic wastewater by bone charcoal activated by zinc chloride. The ratio of zinc chloride and bone was varied at three different ratio 1:1, 1.5:1 and 2:1. The surface area and structure of bone charcoal after activated by zinc chloride were analyzed and used to determine the optimal condition for preparing the bone charcoal for the further experiment. The result showed that bone charcoal activated by zinc chloride at the ratio of 1:1 gave the best result such as high surface area and high apatite intensity. The major types of crystals composed in bone charcoal were $\text{Ca}_{10-x}\text{Zn}_x(\text{PO}_4)_6(\text{OH})_2$, $\text{CaZn}_2(\text{PO}_4)_2 \cdot 2\text{H}_2\text{O}$ and $\text{Ca}_{10}(\text{PO}_4)_6(\text{Cl})_2$. After absorption test with lead, the major crystal composition of bone charcoal was changed to $\text{Pb}_{10}(\text{PO}_4)_6(\text{Cl})_2$. The different results were shown for absorption test with cadmium, the major crystal composition was not changed. It was concluded that the mechanism of removing lead depended on dissolution and precipitation while removing cadmium depended on adsorption.

The results of batch absorption experiment showed that the removal efficiency of lead by bone charcoal was higher than that of cadmium. The synthetic wastewater contained with lead and cadmium at 50 mg L^{-1} and 10 mg L^{-1} . It was found that the highest removal efficiency of lead and cadmium were achieved at pH 4 and 7 respectively. Furthermore it was conclude that bone charcoal could remove lead and cadmium from synthetic wastewater by the dissolution and precipitation of lead with the amount of $1,002 \text{ mg g}^{-1}$ of bone charcoal or 68.38% where as the mechanism of adsorption with the amount of adsorption capacity at 22.06 mg g^{-1} of bone charcoal or 24.70%.

Department Environmental Engineering.....

Field of Study Environmental Engineering.....

Academic year 2005.....

Student's signature

Advisor's signature

Co-advisor's signature

