

หัวข้อวิทยานิพนธ์	วัสดุทดแทนไม้พอลิเมอร์คอมโพสิตจากพอลิเอทิลีนชนิดความหนาแน่นปานกลางและเชื้อความร้อนเชิงกลจากไม้ยางพารา
นักศึกษา	นายยุทธพงษ์ แซ่ตั้ง
รหัสประจำตัว	46064308
ปริญญา	วิทยาศาสตรมหาบัณฑิต
สาขาวิชา	เทคโนโลยีพอลิเมอร์
พ.ศ.	2549
อาจารย์ผู้ควบคุมวิทยานิพนธ์	รศ.ดร.อิทธิพล แจ่มจำรัส
อาจารย์ผู้ควบคุมวิทยานิพนธ์ร่วม	นายวรธรรม อุ่นจิตติชัย

บทคัดย่อ

งานวิจัยนี้เป็นการศึกษาพอลิเมอร์คอมโพสิตเส้นใยธรรมชาติ เพื่อนำมาใช้เป็นวัสดุทดแทนไม้ หรือไม้เทียม สามารถเตรียมได้จาก พอลิเอทิลีนชนิดความหนาแน่นปานกลาง (MDPE) และเส้นใยไม้ยางพารา (Rubber wood fiber) ที่เตรียมจากกระบวนการทางความร้อนเชิงกล (TMP) โดยผสมให้เข้ากันด้วยเครื่องอัดรีดชนิดเกลียวหนอนเดี่ยว แล้วนำไปขึ้นรูปด้วยเครื่องฉีดขึ้นรูป จากนั้นนำไปศึกษาสมบัติต่างๆ เช่น สมบัติทางกายภาพ สมบัติเชิงกล สมบัติทางความร้อน และ สันฐานวิทยา ในงานวิจัยนี้ได้ทำการศึกษาคัดของ MDPE (EL-Lene[®] M3204 และ EL-Lene[®] M3804) ปริมาณเส้นใยไม้ยางพาราชนิด TMP (0-70 phr) ปริมาณสารช่วยผสม (0-5 % ของเส้นใย) ชนิดของสารช่วยผสม (Polyethylene graft maleic anhydride (MAPE) และ Silquest[®] A-174 silane) เกรดของแคลเซียมคาร์บอเนต (CaCO₃) (ขนาดอนุภาค 1 และ 4 ไมครอน) ปริมาณของ CaCO₃ (0-60 phr) และเปรียบเทียบสมบัติของไม้เทียมในงานวิจัยนี้กับไม้เทียมทางการค้าและไม้ธรรมชาติ

จากการศึกษาคัดของ MDPE โดยเติมเส้นใยไม้ยางพารา 40 phr พบว่า MDPE เกรด EL-Lene[®] M3804 ให้สมบัติเชิงกลโดยรวมดีกว่าเกรด EL-Lene[®] M3204 เช่น ความแข็งแรงดึง มอดุลัส ความแข็งแรงโค้งงอ และ มอดุลัสโค้งงอ เมื่อทำการศึกษาผลของปริมาณเส้นใยไม้ยางพารา พบว่า สมบัติเชิงกลของวัสดุคอมโพสิตดีขึ้น แต่เมื่อปริมาณเส้นใยมากเกินไปการขึ้นรูปจะทำได้ยากขึ้น และเปอร์เซ็นต์การดูดซึมน้ำเพิ่มมากขึ้น ปริมาณเส้นใยไม้ยางพาราที่เหมาะสมที่สุดคือ 40 phr จากการศึกษาปริมาณของสารช่วยผสมพบว่า สมบัติเชิงกลดีขึ้นและเปอร์เซ็นต์การดูดซึมน้ำลดลง ปริมาณสารช่วยผสมที่เหมาะสมคือ 3% สมบัติเชิงกลของวัสดุคอมโพสิตที่ใส่ CaCO₃ ขนาดอนุภาค 4 μm มีแนวโน้มที่ดีกว่าวัสดุคอมโพสิตที่ใส่ CaCO₃ ขนาดอนุภาค 1 μm และปริมาณ CaCO₃ ที่เหมาะสมคือ 60 phr จากการศึกษาสมบัติทางความร้อนพบว่า อุณหภูมิหลอมเหลวผลึก (T_m) และ องค์ความเป็นผลึกใกล้เคียงกัน จากการศึกษาสันฐานวิทยาโดยใช้กล้องจุลทรรศน์อิเล็กตรอนแบบ

ส่องกวาด (SEM) พบว่า เส้นใยไม้อย่างพาราและ CaCO_3 มีการกระจายตัวที่ดี การยึดเกาะระหว่างเส้นใยและพอลิเมอร์ดีขึ้นเมื่อใช้สารช่วยผสม และจากการทดสอบสมบัติเชิงกลของไม้พอลิเมอร์คอมโพสิตขึ้นรูปจริงในงานวิจัยนี้ พบว่าสมบัติเชิงกลที่ได้มีค่าน้อยกว่าไม้จริง แต่มีค่าใกล้เคียงกับไม้เทียมเชิงพาณิชย์ที่มีจำหน่ายในประเทศ

Thesis Title	Wood Polymer Composite (WPC) from Medium Density Polyethylene and Thermo-Mechanical Pulp from Rubber Wood
Student	Mr. Yutthapong Sae-Tang
Student ID.	46064308
Degree	Master of Science
Programme	Polymer Technology
Year	2006
Thesis advisor	Assoc.Prof.Dr. Ittipol Jangchud
Thesis Co-advisor	Mr. Woratham Oonjittichai

ABSTRACT

In this research work, natural fiber-polymer composites used as an artificial wood were prepared from medium density polyethylene (MDPE) and thermo-mechanical pulp from rubber wood. The composites formula were mixed and compounded by a single screw extruder and then shaped by an injection molding machine. The samples were characterized for physical, mechanical, thermal and morphological properties. Parameters effecting to composite properties were studied, such as grades of MDPE (EL-Lene[®] M3204 and EL-Lene[®] M3804), amount of fiber loading (0-70 phr), type of compatibilizers (polyethylene graft maleic anhydride (MAPE) and Silquest[®] A-174 silane), amount of compatibilizers (0-5% fiber loading), size of calcium carbonate (CaCO₃) (1 and 4 μ m) and amount of CaCO₃ loading (0-60 phr). Comparative studies between properties of the MDPE/rubber wood fiber composites and those of commercial artificial woods and natural woods were carried out.

By studying the effects of MDPE grades by added 40 phr fiber, it was found that mechanical properties such as tensile strength, modulus, flexural strength, and flexural modulus of EL-Lene[®] M3804 were higher than those of EL-Lene[®] M3204. Mechanical properties of the MDPE/TMP composites were improved by increasing % fiber. The % water absorption of the composites was also increased as the fiber loading was increased. It was found that an optimum fiber loading in this work was 40 phr. By studying the effects of compatibilizers, it was found that the composites with MAPE 3% of fiber loading yielded better mechanical properties. The % of water absorption was also declined when the compatibilizers were incorporated. As the CaCO₃ filler was added, mechanical properties of the composites were not significantly altered. Properties of the composites with 4 μ m CaCO₃ seemed to be better than those of the composites

with 1 μm CaCO_3 . The optimum loading of the CaCO_3 was 60 phr. For thermal properties of the composites, it was found that T_m and % crystallinity were nearly same in all samples. Morphology of the fractured composites was studied by SEM. It was revealed that good dispersion of the fibers and CaCO_3 , and good interfacial bonding between the fibers and the MDPE matrix were observed. In comparative studies between properties of composites and those of commercial artificial woods and natural woods, it was found that the composite properties were less than natural wood however; they were comparable with those of commercial artificial woods in Thailand.