

พจนานุกรม : การขึ้นรูปไฮดรอกซีอะพาไทต์ชนิดพรุนโดยใช้ไดแคลเซียมฟอสเฟตไดไฮเดรตและไดแคลเซียมฟอสเฟตแอนไฮดรัสจากอุตสาหกรรมกระดูกสัตว์. (Fabrication of Porous Hydroxyapatite Using Dicalcium Phosphate Dihydrate and Dicalcium Phosphate Anhydrous from Bone Industry)

อ. ที่ปรึกษา : รศ.ดร.สุพัตรา จินาวัฒน์, 119 หน้า. ISBN 974-346-734-3.

ไฮดรอกซีอะพาไทต์เซรามิกชนิดพรุน ถูกนำมาใช้งานอย่างแพร่หลายทางการแพทย์ในด้านเป็นวัสดุเติมและทดแทนกระดูก เนื่องจากมีลักษณะใกล้เคียงกระดูกและมีสมบัติที่สามารถเข้ากันได้กับร่างกายมากกว่าวัสดุปลูกฝังเซรามิกชนิดอื่น โดยวัสดุที่ปลูกฝังนี้ต้องการทั้งขนาดรูพรุนและความแข็งแรงที่เหมาะสมซึ่งสามารถควบคุมสมบัติที่ต้องการนั้นด้วยเทคนิคที่ใช้ในการขึ้นรูป ในงานวิจัยนี้ได้ศึกษาการขึ้นรูป 2 วิธี คือการเทแบบ และการอัด สำหรับวิธีเทแบบใช้สเลอรีเตรียมจากไดแคลเซียมฟอสเฟตไดไฮเดรต(DCPD)ผสมกับแคลเซียมคาร์บอเนต โดยมี H_2O_2 เป็นตัวให้ฟองอากาศ ผลปรากฏว่าชิ้นงานหลังเผาเกิดการแยกชั้นที่มีเฟสต่างกัน เนื่องจากสารตั้งต้นทั้งสองมีขนาดอนุภาคและความหนาแน่นที่แตกต่างกันค่อนข้างมาก สำหรับการขึ้นรูปโดยการอัด ใช้ไดแคลเซียมฟอสเฟตไดไฮเดรตและไดแคลเซียมฟอสเฟตแอนไฮดรัส(DCPA) ผสมกับแคลเซียมคาร์บอเนต ติมแก้ว 0 และ 5 เปอร์เซ็นต์โดยมวล อัดเป็นชิ้นงาน ขึ้นเทอรินในอากาศที่อุณหภูมิ 1200 และ 1250 องศาเซลเซียส ศึกษาส่วนประกอบทางเคมีชิ้นงานพูนด้วยวิธี X-ray diffraction (XRD) และ Fourier-Transform Infrared Spectrometer (FT-IR) ศึกษาลักษณะเฉพาะทางกายภาพโดย scanning electron microscopy (SEM) mercury porosimetry และ วิธี Archimedes ส่วนสมบัติเชิงกลทำการทดสอบด้วยเครื่องชนิด Hounsfield ชิ้นงานพูนที่ได้พบว่ามีทั้งไฮดรอกซีอะพาไทต์ที่มีความบริสุทธิ์สูง และเป็นวัสดุเชิงประกอบระหว่างไฮดรอกซีอะพาไทต์และไตรแคลเซียมฟอสเฟตซึ่งมีสมบัติดังต่อไปนี้ ประกอบด้วยโครงสร้างรูพรุนที่มีความต่อเนื่องจากขนาดเล็ก (micropore) ถึงขนาดใหญ่ (macropore) ขนาดเส้นผ่านศูนย์กลางอยู่ในช่วง 1-200 ไมครอน มีความพรุนตัว 32.59-63.70 เปอร์เซ็นต์ ค่าความแข็งแรงอัด (compressive strength) และค่าความแข็งแรงดัด (flexural strength) อยู่ในช่วง 3.93-78.13MPa และ 2.48-17.51 MPa ตามลำดับ โดยชิ้นงานที่เตรียมจาก DCPA ให้สมบัติเชิงกลที่สูงกว่า DCPD จากผลการทดลองพบว่าสามารถปรับปรุงสมบัติเชิงกลของชิ้นงานให้สูงขึ้นได้โดยการเพิ่มแรงดันในการอัด ในขณะที่การเติมแก้วส่งเสริมการเปลี่ยนเฟสจากไฮดรอกซีอะพาไทต์ไปเป็นไตรแคลเซียมฟอสเฟต

KEY WORD: POROUS CALCIUM PHOSPHATES / HYDROXYAPATITE / BIOCERAMICS

PORNAPA SUJARIDWORAKUN: FABRICATION OF POROUS HYDROXYAPATITE USING DICALCIUM PHOSPHATE DIHYDRATE AND DICALCIUM PHOSPHATE ANHYDROUS FROM BONE INDUSTRY . THESIS ADVISOR : ASSOC. PROF. SUPATRA JINAWATH, Ph.D. 119 pp. ISBN .974-346-734-3

Porous hydroxyapatite has been increasingly used as bone filling and bone substitute because of its similarity as bone and a better biocompatibility than that of the other ceramic implants. The implant materials need an appropriate combination between pore size and strength. This requirement can be optimized by the application of fabrication technology. In this work, two methods, slip casting and powder pressing were employed. A mixture of dicalcium phosphate dihydrate (DCPD) and CaCO_3 was used as the casting slurry with H_2O_2 as a foaming agent. Sintered cast specimens with inhomogeneous phase distribution were obtained. Phase segregation was due to a big difference in particle size and density of the slurry components. In the pressing method, dicalcium phosphate dihydrate and dicalcium phosphate anhydrous (DCPA) powders were each mixed with CaCO_3 and 0.5 wt% $\text{Ca}(\text{PO}_3)_2$ glass, pressed into shape and sintered in air at temperatures of 1200 and 1250°C, respectively. The chemical characteristics of the porous compacts were determined using x-ray diffraction (XRD) and Fourier-Transform Infrared spectrometer (FT-IR), while the physical characteristics were determined using scanning electron microscopy (SEM), mercury porosimetry and Archimedes method and the mechanical characteristics by an Hounsfield-type testing machine. The typical porous compacts obtained are high-purity HAP and HAP-TCP composite with the following properties: interconnected micro to macroporous structure (1-200 μm . in diameter) porosity in the range of 32.59-63.70%, compressive and flexural strengths of 3.93-78.13 and 2.48 –17.51 MPa, respectively. In comparison, the specimens prepared from DCPA give much higher mechanical strength than those from DCPD. In this experiment it is found that mechanical strength of the specimens is significantly improved by increasing the forming pressure while the addition of glass promotes the inversion of hydroxyapatite to tricalcium phosphates.